

Bottom Ash Data

2024 Week 1

The following analytical report represents bottom ash composite results for week 1 of 2024 (December 31, 2023 to January 6, 2024).

The bottom ash meets the conditions of Metro Vancouver's 2020 Bottom Ash Management Plan and is suitable for disposal.



CERTIFICATE OF ANALYSIS

Work Order : **VA24A0540**
Client : **Covanta Burnaby Renewable Energy, ULC**
Contact : Nicole Victor
Address : 5150 Riverbend Drive
 Burnaby BC Canada V3N 4V3
Telephone : ----
Project : Weekly Bottom Ash - Suite
PO : 46693
C-O-C number : ----
Sampler : ----
Site : (includes 2.1 PH)
Quote number : Standing Offer (BC work)
No. of samples received : 12
No. of samples analysed : 12

Page : 1 of 11
Laboratory : ALS Environmental - Vancouver
Account Manager : Ian Chen
Address : 8081 Lougheed Highway
 Burnaby BC Canada V5A 1W9
Telephone : +1 604 253 4188
Date Samples Received : 10-Jan-2024 16:08
Date Analysis Commenced : 10-Jan-2024
Issue Date : 17-Jan-2024 10:41

This report supersedes any previous report(s) with this reference. Results apply to the sample(s) as submitted. This document shall not be reproduced, except in full.

This Certificate of Analysis contains the following information:

- General Comments
- Analytical Results

Additional information pertinent to this report will be found in the following separate attachments: Quality Control Report, QC Interpretive report to assist with Quality Review and Sample Receipt Notification (SRN).

Signatories

This document has been electronically signed by the authorized signatories below. Electronic signing is conducted in accordance with US FDA 21 CFR Part 11.

<i>Signatories</i>	<i>Position</i>	<i>Laboratory Department</i>
Kevin Duarte	Supervisor - Metals ICP Instrumentation	Metals, Burnaby, British Columbia
Kim Jensen	Department Manager - Metals	Metals, Burnaby, British Columbia
Kim Jensen	Department Manager - Metals	Organics, Burnaby, British Columbia
Owen Cheng		Metals, Burnaby, British Columbia



General Comments

The analytical methods used by ALS are developed using internationally recognized reference methods (where available), such as those published by US EPA, APHA Standard Methods, ASTM, ISO, Environment Canada, BC MOE, and Ontario MOE. Refer to the ALS Quality Control Interpretive report (QCI) for applicable references and methodology summaries. Reference methods may incorporate modifications to improve performance.

Where a reported less than (<) result is higher than the LOR, this may be due to primary sample extract/digestate dilution and/or insufficient sample for analysis.

Where the LOR of a reported result differs from standard LOR, this may be due to high moisture content, insufficient sample (reduced weight employed) or matrix interference.

Please refer to Quality Control Interpretive report (QCI) for information regarding Holding Time compliance.

Key : CAS Number: Chemical Abstracts Services number is a unique identifier assigned to discrete substances
LOR: Limit of Reporting (detection limit).

<i>Unit</i>	<i>Description</i>
%	percent
mg/kg	milligrams per kilogram
mg/L	milligrams per litre
pH units	pH units

<: less than.

>: greater than.

Surrogate: An analyte that is similar in behavior to target analyte(s), but that does not occur naturally in environmental samples. For applicable tests, surrogates are added to samples prior to analysis as a check on recovery.

Test results reported relate only to the samples as received by the laboratory.

UNLESS OTHERWISE STATED on SRN or QCI Report, ALL SAMPLES WERE RECEIVED IN ACCEPTABLE CONDITION.



Analytical Results

Sub-Matrix: Soil					Client sample ID				
(Matrix: Soil/Solid)					BA2401-A-1	BA2401-A-2	BA2401-A-3	BA2401-A-4	BA2401-A-5
Client sampling date / time					03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24A0540-001	VA24A0540-002	VA24A0540-003	VA24A0540-004	VA24A0540-005
					Result	Result	Result	Result	Result
Physical Tests									
Moisture	----	E144/VA	0.25	%	22.8	21.8	20.9	20.9	20.7
pH (1:2 soil:water)	----	E108/VA	0.10	pH units	11.8	12.0	11.7	12.3	12.3
Metals									
Aluminum	7429-90-5	E440/VA	50	mg/kg	29500	38600	35200	44000	58600
Antimony	7440-36-0	E440/VA	0.10	mg/kg	257	167	189	213	208
Arsenic	7440-38-2	E440/VA	0.10	mg/kg	41.0	20.3	22.7	23.2	22.4
Barium	7440-39-3	E440/VA	0.50	mg/kg	476	516	456	529	552
Beryllium	7440-41-7	E440/VA	0.10	mg/kg	0.40	0.36	0.44	0.35	0.35
Bismuth	7440-69-9	E440/VA	0.20	mg/kg	30.0	22.0	25.1	24.9	24.6
Boron	7440-42-8	E440/VA	5.0	mg/kg	124	194	170	146	187
Cadmium	7440-43-9	E440/VA	0.020	mg/kg	18.6	22.4	19.8	19.6	18.9
Calcium	7440-70-2	E440/VA	50	mg/kg	134000	146000	156000	163000	163000
Chromium	7440-47-3	E440/VA	0.50	mg/kg	139	166	156	176	166
Cobalt	7440-48-4	E440/VA	0.10	mg/kg	678	23.7	422	79.3	44.1
Copper	7440-50-8	E440/VA	0.50	mg/kg	3510	7830	3960	3530	3080
Iron	7439-89-6	E440/VA	50	mg/kg	51500	56600	67900	72400	55500
Lead	7439-92-1	E440/VA	0.50	mg/kg	471	421	375	578	356
Lithium	7439-93-2	E440/VA	2.0	mg/kg	132	39.6	57.9	54.3	25.3
Magnesium	7439-95-4	E440/VA	20	mg/kg	11700	10800	12000	11600	12400
Manganese	7439-96-5	E440/VA	1.0	mg/kg	764	728	830	1030	746
Mercury	7439-97-6	E510/VA	0.0500	mg/kg	0.0890	0.0842	0.0982	0.106	0.0895
Molybdenum	7439-98-7	E440/VA	0.10	mg/kg	28.4	23.3	21.6	29.9	24.4
Nickel	7440-02-0	E440/VA	0.50	mg/kg	1340	154	194	228	119
Phosphorus	7723-14-0	E440/VA	50	mg/kg	8940	10000	11300	11300	11000
Potassium	7440-09-7	E440/VA	100	mg/kg	7500	7160	7750	9000	7500
Selenium	7782-49-2	E440/VA	0.20	mg/kg	0.70	0.61	0.57	0.70	0.63
Silver	7440-22-4	E440/VA	0.10	mg/kg	8.95	7.06	6.21	7.00	6.17
Sodium	7440-23-5	E440/VA	50	mg/kg	18800	17100	19200	20500	18900
Strontium	7440-24-6	E440/VA	0.50	mg/kg	275	316	322	330	315



Analytical Results

Sub-Matrix: Soil					Client sample ID	BA2401-A-1	BA2401-A-2	BA2401-A-3	BA2401-A-4	BA2401-A-5
(Matrix: Soil/Solid)					Client sampling date / time	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24A0540-001	VA24A0540-002	VA24A0540-003	VA24A0540-004	VA24A0540-005	
					Result	Result	Result	Result	Result	
Metals										
Sulfur	7704-34-9	E440/VA	1000	mg/kg	13400	12800	13900	14100	14200	
Thallium	7440-28-0	E440/VA	0.050	mg/kg	0.060	0.054	0.060	0.060	0.063	
Tin	7440-31-5	E440/VA	2.0	mg/kg	236	142	3290	182	169	
Titanium	7440-32-6	E440/VA	1.0	mg/kg	214	248	198	325	458	
Tungsten	7440-33-7	E440/VA	0.50	mg/kg	14.5	6.82	8.36	9.79	9.45	
Uranium	7440-61-1	E440/VA	0.050	mg/kg	4.14	4.06	4.46	5.02	4.65	
Vanadium	7440-62-2	E440/VA	0.20	mg/kg	40.3	41.8	42.1	48.4	52.4	
Zinc	7440-66-6	E440/VA	2.0	mg/kg	4110	4500	4620	8240	4350	
Zirconium	7440-67-7	E440/VA	1.0	mg/kg	1.2	1.9	2.2	2.6	5.1	
TCLP Metals										
pH, TCLP 1st preliminary	----	EPP444/VA	0.010	pH units	11.8	11.7	11.8	11.9	12.0	
pH, TCLP 2nd preliminary	----	EPP444/VA	0.010	pH units	7.72	7.74	8.46	8.96	9.03	
pH, TCLP extraction fluid initial	----	EPP444/VA	0.010	pH units	2.89	2.89	2.89	2.89	2.89	
pH, TCLP final	----	EPP444/VA	0.010	pH units	7.95	7.89	7.93	8.23	8.42	
Antimony, TCLP	7440-36-0	E444/VA	1.00	mg/L	<1.00	<1.00	<1.00	<1.00	<1.00	
Arsenic, TCLP	7440-38-2	E444/VA	1.0	mg/L	<1.0	<1.0	<1.0	<1.0	<1.0	
Barium, TCLP	7440-39-3	E444/VA	2.5	mg/L	<2.5	<2.5	<2.5	<2.5	<2.5	
Beryllium, TCLP	7440-41-7	E444/VA	0.025	mg/L	<0.025	<0.025	<0.025	<0.025	<0.025	
Boron, TCLP	7440-42-8	E444/VA	0.50	mg/L	2.06	1.93	1.99	1.89	1.76	
Cadmium, TCLP	7440-43-9	E444/VA	0.050	mg/L	<0.050	<0.050	<0.050	<0.050	<0.050	
Calcium, TCLP	7440-70-2	E444/VA	10	mg/L	2140	2110	2070	2140	1990	
Chromium, TCLP	7440-47-3	E444/VA	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25	
Cobalt, TCLP	7440-48-4	E444/VA	0.050	mg/L	0.246	0.230	0.187	0.072	<0.050	
Copper, TCLP	7440-50-8	E444/VA	0.050	mg/L	0.639	0.666	0.666	0.692	0.619	
Iron, TCLP	7439-89-6	E444/VA	5.0	mg/L	<5.0	<5.0	<5.0	<5.0	<5.0	
Lead, TCLP	7439-92-1	E444/VA	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25	
Magnesium, TCLP	7439-95-4	E444/VA	2.5	mg/L	103	108	110	101	98.6	
Mercury, TCLP	7439-97-6	E512/VA	0.0010	mg/L	<0.0010	<0.0010	<0.0010	<0.0010	<0.0010	
Nickel, TCLP	7440-02-0	E444/VA	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25	
Selenium, TCLP	7782-49-2	E444/VA	0.10	mg/L	<0.10	<0.10	<0.10	<0.10	<0.10	



Analytical Results

Sub-Matrix: Soil (Matrix: Soil/Solid)					Client sample ID	BA2401-A-1	BA2401-A-2	BA2401-A-3	BA2401-A-4	BA2401-A-5
Client sampling date / time					03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24A0540-001	VA24A0540-002	VA24A0540-003	VA24A0540-004	VA24A0540-005	
					Result	Result	Result	Result	Result	
TCLP Metals										
Silver, TCLP	7440-22-4	E444/VA	0.050	mg/L	<0.050	<0.050	<0.050	<0.050	<0.050	<0.050
Thallium, TCLP	7440-28-0	E444/VA	1.0	mg/L	<1.0	<1.0	<1.0	<1.0	<1.0	<1.0
Uranium, TCLP	7440-61-1	E444/VA	0.20	mg/L	<0.20	<0.20	<0.20	<0.20	<0.20	<0.20
Vanadium, TCLP	7440-62-2	E444/VA	0.15	mg/L	<0.15	<0.15	<0.15	<0.15	<0.15	<0.15
Zinc, TCLP	7440-66-6	E444/VA	0.50	mg/L	<0.50	<0.50	<0.50	<0.50	<0.50	<0.50
Zirconium, TCLP	7440-67-7	E444/VA	10	mg/L	<10	<10	<10	<10	<10	<10

Please refer to the General Comments section for an explanation of any result qualifiers detected.

Please refer to the Accreditation section for an explanation of analyte accreditations.



Analytical Results

Sub-Matrix: Soil (Matrix: Soil/Solid)					Client sample ID	BA2401-A-6	BA2401-A-7	BA2401-A-8	BA2401-A-9	BA2401-A-10
Client sampling date / time					03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24A0540-006	VA24A0540-007	VA24A0540-008	VA24A0540-009	VA24A0540-010	
					Result	Result	Result	Result	Result	
Physical Tests										
Moisture	---	E144/VA	0.25	%	22.0	20.7	21.4	21.2	21.9	
pH (1:2 soil:water)	---	E108/VA	0.10	pH units	12.3	12.3	12.3	12.4	12.4	
Metals										
Aluminum	7429-90-5	E440/VA	50	mg/kg	39700	37100	42700	53800	47300	
Antimony	7440-36-0	E440/VA	0.10	mg/kg	191	205	181	248	196	
Arsenic	7440-38-2	E440/VA	0.10	mg/kg	21.5	21.3	21.0	27.7	24.6	
Barium	7440-39-3	E440/VA	0.50	mg/kg	539	576	576	663	611	
Beryllium	7440-41-7	E440/VA	0.10	mg/kg	1.62	0.43	0.37	0.42	0.37	
Bismuth	7440-69-9	E440/VA	0.20	mg/kg	26.1	30.0	24.6	27.9	35.5	
Boron	7440-42-8	E440/VA	5.0	mg/kg	161	170	141	187	166	
Cadmium	7440-43-9	E440/VA	0.020	mg/kg	19.1	16.8	17.2	21.6	19.9	
Calcium	7440-70-2	E440/VA	50	mg/kg	179000	166000	162000	182000	176000	
Chromium	7440-47-3	E440/VA	0.50	mg/kg	172	164	196	168	174	
Cobalt	7440-48-4	E440/VA	0.10	mg/kg	152	30.3	22.8	247	85.3	
Copper	7440-50-8	E440/VA	0.50	mg/kg	7480	2460	1990	5420	2060	
Iron	7439-89-6	E440/VA	50	mg/kg	49900	45400	46300	51600	66100	
Lead	7439-92-1	E440/VA	0.50	mg/kg	769	402	354	586	349	
Lithium	7439-93-2	E440/VA	2.0	mg/kg	46.6	24.9	36.0	274	38.4	
Magnesium	7439-95-4	E440/VA	20	mg/kg	12200	12000	11000	13000	12300	
Manganese	7439-96-5	E440/VA	1.0	mg/kg	1130	885	864	1260	979	
Mercury	7439-97-6	E510/VA	0.0500	mg/kg	0.0894	0.0913	0.0878	0.110	0.0844	
Molybdenum	7439-98-7	E440/VA	0.10	mg/kg	24.1	32.6	29.5	34.8	26.8	
Nickel	7440-02-0	E440/VA	0.50	mg/kg	314	146	132	735	123	
Phosphorus	7723-14-0	E440/VA	50	mg/kg	15300	11900	11800	12900	10900	
Potassium	7440-09-7	E440/VA	100	mg/kg	8380	7320	7080	8040	7550	
Selenium	7782-49-2	E440/VA	0.20	mg/kg	0.67	0.68	0.61	0.75	0.73	
Silver	7440-22-4	E440/VA	0.10	mg/kg	21.7	6.28	5.57	9.61	6.23	
Sodium	7440-23-5	E440/VA	50	mg/kg	19100	17700	16200	20000	17700	
Strontium	7440-24-6	E440/VA	0.50	mg/kg	337	306	292	534	304	
Sulfur	7704-34-9	E440/VA	1000	mg/kg	13300	13600	13800	15400	14200	



Analytical Results

Sub-Matrix: Soil (Matrix: Soil/Solid)					Client sample ID	BA2401-A-6	BA2401-A-7	BA2401-A-8	BA2401-A-9	BA2401-A-10
Client sampling date / time					03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24A0540-006	VA24A0540-007	VA24A0540-008	VA24A0540-009	VA24A0540-010	
					Result	Result	Result	Result	Result	
Metals										
Thallium	7440-28-0	E440/VA	0.050	mg/kg	0.055	0.055	0.054	0.073	0.059	
Tin	7440-31-5	E440/VA	2.0	mg/kg	3420	178	158	192	171	
Titanium	7440-32-6	E440/VA	1.0	mg/kg	217	250	258	348	297	
Tungsten	7440-33-7	E440/VA	0.50	mg/kg	7.40	11.9	6.34	11.2	8.26	
Uranium	7440-61-1	E440/VA	0.050	mg/kg	4.54	4.72	4.48	4.94	4.86	
Vanadium	7440-62-2	E440/VA	0.20	mg/kg	46.7	44.8	42.1	50.7	48.7	
Zinc	7440-66-6	E440/VA	2.0	mg/kg	4710	6910	3780	5130	4820	
Zirconium	7440-67-7	E440/VA	1.0	mg/kg	3.4	1.5	2.1	2.5	3.0	
TCLP Metals										
pH, TCLP 1st preliminary	----	EPP444/VA	0.010	pH units	11.9	12.0	11.9	12.0	12.0	
pH, TCLP 2nd preliminary	----	EPP444/VA	0.010	pH units	9.06	9.17	8.85	9.33	9.14	
pH, TCLP extraction fluid initial	----	EPP444/VA	0.010	pH units	2.89	2.89	2.89	2.89	2.89	
pH, TCLP final	----	EPP444/VA	0.010	pH units	8.43	8.39	8.14	8.67	8.61	
Antimony, TCLP	7440-36-0	E444/VA	1.00	mg/L	<1.00	<1.00	<1.00	<1.00	<1.00	
Arsenic, TCLP	7440-38-2	E444/VA	1.0	mg/L	<1.0	<1.0	<1.0	<1.0	<1.0	
Barium, TCLP	7440-39-3	E444/VA	2.5	mg/L	<2.5	<2.5	<2.5	<2.5	<2.5	
Beryllium, TCLP	7440-41-7	E444/VA	0.025	mg/L	<0.025	<0.025	<0.025	<0.025	<0.025	
Boron, TCLP	7440-42-8	E444/VA	0.50	mg/L	1.78	1.82	2.22	2.18	2.03	
Cadmium, TCLP	7440-43-9	E444/VA	0.050	mg/L	<0.050	<0.050	<0.050	<0.050	<0.050	
Calcium, TCLP	7440-70-2	E444/VA	10	mg/L	2080	2110	2070	2020	2010	
Chromium, TCLP	7440-47-3	E444/VA	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25	
Cobalt, TCLP	7440-48-4	E444/VA	0.050	mg/L	<0.050	0.064	0.635	<0.050	<0.050	
Copper, TCLP	7440-50-8	E444/VA	0.050	mg/L	0.610	0.600	0.762	0.620	0.615	
Iron, TCLP	7439-89-6	E444/VA	5.0	mg/L	<5.0	<5.0	<5.0	<5.0	<5.0	
Lead, TCLP	7439-92-1	E444/VA	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25	
Magnesium, TCLP	7439-95-4	E444/VA	2.5	mg/L	98.9	102	103	91.8	89.6	
Mercury, TCLP	7439-97-6	E512/VA	0.0010	mg/L	<0.0010	<0.0010	<0.0010	<0.0010	<0.0010	
Nickel, TCLP	7440-02-0	E444/VA	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25	
Selenium, TCLP	7782-49-2	E444/VA	0.10	mg/L	<0.10	<0.10	<0.10	<0.10	<0.10	
Silver, TCLP	7440-22-4	E444/VA	0.050	mg/L	<0.050	<0.050	<0.050	<0.050	<0.050	



Analytical Results

Sub-Matrix: Soil (Matrix: Soil/Solid)					Client sample ID	BA2401-A-6	BA2401-A-7	BA2401-A-8	BA2401-A-9	BA2401-A-10
Client sampling date / time					03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00	03-Jan-2024 09:00
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24A0540-006	VA24A0540-007	VA24A0540-008	VA24A0540-009	VA24A0540-010	
TCLP Metals					Result	Result	Result	Result	Result	
Thallium, TCLP	7440-28-0	E444/VA	1.0	mg/L	<1.0	<1.0	<1.0	<1.0	<1.0	
Uranium, TCLP	7440-61-1	E444/VA	0.20	mg/L	<0.20	<0.20	<0.20	<0.20	<0.20	
Vanadium, TCLP	7440-62-2	E444/VA	0.15	mg/L	<0.15	<0.15	<0.15	<0.15	<0.15	
Zinc, TCLP	7440-66-6	E444/VA	0.50	mg/L	<0.50	<0.50	<0.50	<0.50	<0.50	
Zirconium, TCLP	7440-67-7	E444/VA	10	mg/L	<10	<10	<10	<10	<10	

Please refer to the General Comments section for an explanation of any result qualifiers detected.

Please refer to the Accreditation section for an explanation of analyte accreditations.



Analytical Results

Sub-Matrix: Soil					Client sample ID				
(Matrix: Soil/Solid)					BA2401-A-11	BA2401-A-12	----	----	----
Client sampling date / time					03-Jan-2024 09:00	03-Jan-2024 09:00	----	----	----
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24A0540-011	VA24A0540-012	-----	-----	-----
					Result	Result	----	----	----
Physical Tests									
Moisture	---	E144/VA	0.25	%	21.6	22.3	----	----	----
pH (1:2 soil:water)	---	E108/VA	0.10	pH units	12.4	12.3	----	----	----
Metals									
Aluminum	7429-90-5	E440/VA	50	mg/kg	38000	32800	----	----	----
Antimony	7440-36-0	E440/VA	0.10	mg/kg	181	191	----	----	----
Arsenic	7440-38-2	E440/VA	0.10	mg/kg	22.5	20.1	----	----	----
Barium	7440-39-3	E440/VA	0.50	mg/kg	468	518	----	----	----
Beryllium	7440-41-7	E440/VA	0.10	mg/kg	0.40	0.33	----	----	----
Bismuth	7440-69-9	E440/VA	0.20	mg/kg	24.8	28.0	----	----	----
Boron	7440-42-8	E440/VA	5.0	mg/kg	161	140	----	----	----
Cadmium	7440-43-9	E440/VA	0.020	mg/kg	17.0	17.6	----	----	----
Calcium	7440-70-2	E440/VA	50	mg/kg	161000	161000	----	----	----
Chromium	7440-47-3	E440/VA	0.50	mg/kg	173	166	----	----	----
Cobalt	7440-48-4	E440/VA	0.10	mg/kg	78.4	190	----	----	----
Copper	7440-50-8	E440/VA	0.50	mg/kg	1410	2560	----	----	----
Iron	7439-89-6	E440/VA	50	mg/kg	49200	58600	----	----	----
Lead	7439-92-1	E440/VA	0.50	mg/kg	366	351	----	----	----
Lithium	7439-93-2	E440/VA	2.0	mg/kg	26.8	22.5	----	----	----
Magnesium	7439-95-4	E440/VA	20	mg/kg	11100	11900	----	----	----
Manganese	7439-96-5	E440/VA	1.0	mg/kg	735	712	----	----	----
Mercury	7439-97-6	E510/VA	0.0500	mg/kg	0.0798	0.0887	----	----	----
Molybdenum	7439-98-7	E440/VA	0.10	mg/kg	21.8	22.3	----	----	----
Nickel	7440-02-0	E440/VA	0.50	mg/kg	122	198	----	----	----
Phosphorus	7723-14-0	E440/VA	50	mg/kg	9300	11500	----	----	----
Potassium	7440-09-7	E440/VA	100	mg/kg	7150	7040	----	----	----
Selenium	7782-49-2	E440/VA	0.20	mg/kg	0.72	0.63	----	----	----
Silver	7440-22-4	E440/VA	0.10	mg/kg	7.85	>32.9	----	----	----
Sodium	7440-23-5	E440/VA	50	mg/kg	16600	16100	----	----	----
Strontium	7440-24-6	E440/VA	0.50	mg/kg	297	309	----	----	----
Sulfur	7704-34-9	E440/VA	1000	mg/kg	12600	12400	----	----	----



Analytical Results

Sub-Matrix: Soil					Client sample ID	BA2401-A-11	BA2401-A-12	----	----	----
(Matrix: Soil/Solid)					Client sampling date / time	03-Jan-2024 09:00	03-Jan-2024 09:00	----	----	----
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24A0540-011	VA24A0540-012	-----	-----	-----	
					Result	Result	---	---	---	
Metals										
Thallium	7440-28-0	E440/VA	0.050	mg/kg	0.070	0.052	---	---	---	
Tin	7440-31-5	E440/VA	2.0	mg/kg	153	207	---	---	---	
Titanium	7440-32-6	E440/VA	1.0	mg/kg	245	235	---	---	---	
Tungsten	7440-33-7	E440/VA	0.50	mg/kg	15.2	8.58	---	---	---	
Uranium	7440-61-1	E440/VA	0.050	mg/kg	4.40	4.72	---	---	---	
Vanadium	7440-62-2	E440/VA	0.20	mg/kg	43.9	44.2	---	---	---	
Zinc	7440-66-6	E440/VA	2.0	mg/kg	4290	4750	---	---	---	
Zirconium	7440-67-7	E440/VA	1.0	mg/kg	2.2	2.1	---	---	---	
TCLP Metals										
pH, TCLP 1st preliminary	----	EPP444/VA	0.010	pH units	12.0	11.9	---	---	---	
pH, TCLP 2nd preliminary	----	EPP444/VA	0.010	pH units	9.28	9.13	---	---	---	
pH, TCLP extraction fluid initial	----	EPP444/VA	0.010	pH units	2.89	2.89	---	---	---	
pH, TCLP final	----	EPP444/VA	0.010	pH units	8.46	8.32	---	---	---	
Antimony, TCLP	7440-36-0	E444/VA	1.00	mg/L	<1.00	<1.00	---	---	---	
Arsenic, TCLP	7440-38-2	E444/VA	1.0	mg/L	<1.0	<1.0	---	---	---	
Barium, TCLP	7440-39-3	E444/VA	2.5	mg/L	<2.5	<2.5	---	---	---	
Beryllium, TCLP	7440-41-7	E444/VA	0.025	mg/L	<0.025	<0.025	---	---	---	
Boron, TCLP	7440-42-8	E444/VA	0.50	mg/L	2.08	2.15	---	---	---	
Cadmium, TCLP	7440-43-9	E444/VA	0.050	mg/L	<0.050	<0.050	---	---	---	
Calcium, TCLP	7440-70-2	E444/VA	10	mg/L	2060	2160	---	---	---	
Chromium, TCLP	7440-47-3	E444/VA	0.25	mg/L	<0.25	<0.25	---	---	---	
Cobalt, TCLP	7440-48-4	E444/VA	0.050	mg/L	<0.050	0.056	---	---	---	
Copper, TCLP	7440-50-8	E444/VA	0.050	mg/L	0.649	0.660	---	---	---	
Iron, TCLP	7439-89-6	E444/VA	5.0	mg/L	<5.0	<5.0	---	---	---	
Lead, TCLP	7439-92-1	E444/VA	0.25	mg/L	<0.25	<0.25	---	---	---	
Magnesium, TCLP	7439-95-4	E444/VA	2.5	mg/L	96.7	99.1	---	---	---	
Mercury, TCLP	7439-97-6	E512/VA	0.0010	mg/L	<0.0010	<0.0010	---	---	---	
Nickel, TCLP	7440-02-0	E444/VA	0.25	mg/L	<0.25	<0.25	---	---	---	
Selenium, TCLP	7782-49-2	E444/VA	0.10	mg/L	<0.10	<0.10	---	---	---	
Silver, TCLP	7440-22-4	E444/VA	0.050	mg/L	<0.050	<0.050	---	---	---	



Analytical Results

Sub-Matrix: Soil					Client sample ID		BA2401-A-11	BA2401-A-12	----	----	----
(Matrix: Soil/Solid)					Client sampling date / time		03-Jan-2024 09:00	03-Jan-2024 09:00	----	----	----
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24A0540-011	VA24A0540-012	-----	-----	-----	-----	-----
TCLP Metals					Result	Result	---	---	---	---	---
Thallium, TCLP	7440-28-0	E444/VA	1.0	mg/L	<1.0	<1.0	---	---	---	---	---
Uranium, TCLP	7440-61-1	E444/VA	0.20	mg/L	<0.20	<0.20	---	---	---	---	---
Vanadium, TCLP	7440-62-2	E444/VA	0.15	mg/L	<0.15	<0.15	---	---	---	---	---
Zinc, TCLP	7440-66-6	E444/VA	0.50	mg/L	<0.50	<0.50	---	---	---	---	---
Zirconium, TCLP	7440-67-7	E444/VA	10	mg/L	<10	<10	---	---	---	---	---

Please refer to the General Comments section for an explanation of any result qualifiers detected.

Please refer to the Accreditation section for an explanation of analyte accreditations.



QUALITY CONTROL INTERPRETIVE REPORT

<p>Work Order : VA24A0540</p> <p>Client : Covanta Burnaby Renewable Energy, ULC</p> <p>Contact : Nicole Victor</p> <p>Address : 5150 Riverbend Drive Burnaby BC Canada V3N 4V3</p> <p>Telephone : ----</p> <p>Project : Weekly Bottom Ash - Suite</p> <p>PO : 46693</p> <p>C-O-C number : ----</p> <p>Sampler : ----</p> <p>Site : (includes 2.1 PH)</p> <p>Quote number : Standing Offer (BC work)</p> <p>No. of samples received : 12</p> <p>No. of samples analysed : 12</p>	<p>Page : 1 of 16</p> <p>Laboratory : ALS Environmental - Vancouver</p> <p>Account Manager : Ian Chen</p> <p>Address : 8081 Lougheed Highway Burnaby, British Columbia Canada V5A 1W9</p> <p>Telephone : +1 604 253 4188</p> <p>Date Samples Received : 10-Jan-2024 16:08</p> <p>Issue Date : 17-Jan-2024 10:41</p>
--	--

This report is automatically generated by the ALS LIMS (Laboratory Information Management System) through evaluation of Quality Control (QC) results and other QA parameters associated with this submission, and is intended to facilitate rapid data validation by auditors or reviewers. The report highlights any exceptions and outliers to ALS Data Quality Objectives, provides holding time details and exceptions, summarizes QC sample frequencies, and lists applicable methodology references and summaries.

Key

- Anonymous: Refers to samples which are not part of this work order, but which formed part of the QC process lot.
- CAS Number: Chemical Abstracts Service number is a unique identifier assigned to discrete substances.
- DQO: Data Quality Objective.
- LOR: Limit of Reporting (detection limit).
- RPD: Relative Percent Difference.

Workorder Comments

Holding times are displayed as "----" if no guidance exists from CCME, Canadian provinces, or broadly recognized international references.

Summary of Outliers

Outliers : Quality Control Samples

- No Method Blank value outliers occur.
- No Laboratory Control Sample (LCS) outliers occur
- No Matrix Spike outliers occur.
- Duplicate outliers occur - please see following pages for full details.
- No Test sample Surrogate recovery outliers exist.

Outliers: Reference Material (RM) Samples

- No Reference Material (RM) Sample outliers occur.

Outliers : Analysis Holding Time Compliance (Breaches)

- No Analysis Holding Time Outliers exist.

Outliers : Frequency of Quality Control Samples

- No Quality Control Sample Frequency Outliers occur.



Outliers : Quality Control Samples

Duplicates, Method Blanks, Laboratory Control Samples and Matrix Spikes

Matrix: **Soil/Solid**

Analyte Group	Laboratory sample ID	Client/Ref Sample ID	Analyte	CAS Number	Method	Result	Limits	Comment
Duplicate (DUP) RPDs								
Metals	VA24A0540-001	BA2401-A-1	Antimony	7440-36-0	E440	37.7 % DUP-H	30%	Duplicate RPD does not meet the DQO for this test.
Metals	VA24A0540-001	BA2401-A-1	Arsenic	7440-38-2	E440	69.9 % DUP-H	30%	Duplicate RPD does not meet the DQO for this test.
Metals	VA24A0540-001	BA2401-A-1	Cobalt	7440-48-4	E440	149 % DUP-H	30%	Duplicate RPD does not meet the DQO for this test.
Metals	VA24A0540-001	BA2401-A-1	Copper	7440-50-8	E440	66.4 % DUP-H	30%	Duplicate RPD does not meet the DQO for this test.
Metals	VA24A0540-001	BA2401-A-1	Lithium	7439-93-2	E440	125 % DUP-H	30%	Duplicate RPD does not meet the DQO for this test.
Metals	VA24A0540-001	BA2401-A-1	Nickel	7440-02-0	E440	166 % DUP-H	30%	Duplicate RPD does not meet the DQO for this test.
Metals	VA24A0540-001	BA2401-A-1	Tungsten	7440-33-7	E440	37.5 % DUP-H	30%	Duplicate RPD does not meet the DQO for this test.

Result Qualifiers

Qualifier	Description
DUP-H	Duplicate results outside ALS DQO, due to sample heterogeneity.



Analysis Holding Time Compliance

This report summarizes extraction / preparation and analysis times and compares each with ALS recommended holding times, which are selected to meet known provincial and /or federal requirements. In the absence of regulatory hold times, ALS establishes recommendations based on guidelines published by organizations such as CCME, US EPA, APHA Standard Methods, ASTM, or Environment Canada (where available). Dates and holding times reported below represent the first dates of extraction or analysis. If subsequent tests or dilutions exceeded holding times, qualifiers are added (refer to COA).

If samples are identified below as having been analyzed or extracted outside of recommended holding times, measurement uncertainties may be increased, and this should be taken into consideration when interpreting results.

Where actual sampling date is not provided on the chain of custody, the date of receipt with time at 00:00 is used for calculation purposes.

Where only the sample date without time is provided on the chain of custody, the sampling date at 00:00 is used for calculation purposes.

Matrix: **Soil/Solid**

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2401-A-1	E510	03-Jan-2024	11-Jan-2024	28 days	8 days	✔	11-Jan-2024	28 days	8 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2401-A-10	E510	03-Jan-2024	11-Jan-2024	28 days	8 days	✔	11-Jan-2024	28 days	8 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2401-A-11	E510	03-Jan-2024	11-Jan-2024	28 days	8 days	✔	11-Jan-2024	28 days	8 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2401-A-12	E510	03-Jan-2024	11-Jan-2024	28 days	8 days	✔	11-Jan-2024	28 days	8 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2401-A-2	E510	03-Jan-2024	11-Jan-2024	28 days	8 days	✔	11-Jan-2024	28 days	8 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2401-A-3	E510	03-Jan-2024	11-Jan-2024	28 days	8 days	✔	11-Jan-2024	28 days	8 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2401-A-4	E510	03-Jan-2024	11-Jan-2024	28 days	8 days	✔	11-Jan-2024	28 days	8 days	✔	



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2401-A-5	E510	03-Jan-2024	11-Jan-2024	28 days	8 days	✔	11-Jan-2024	28 days	8 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2401-A-6	E510	03-Jan-2024	11-Jan-2024	28 days	8 days	✔	11-Jan-2024	28 days	8 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2401-A-7	E510	03-Jan-2024	11-Jan-2024	28 days	8 days	✔	11-Jan-2024	28 days	8 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2401-A-8	E510	03-Jan-2024	11-Jan-2024	28 days	8 days	✔	11-Jan-2024	28 days	8 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2401-A-9	E510	03-Jan-2024	11-Jan-2024	28 days	8 days	✔	11-Jan-2024	28 days	8 days	✔	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2401-A-1	E440	03-Jan-2024	11-Jan-2024	180 days	8 days	✔	11-Jan-2024	180 days	8 days	✔	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2401-A-10	E440	03-Jan-2024	11-Jan-2024	180 days	8 days	✔	11-Jan-2024	180 days	8 days	✔	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2401-A-11	E440	03-Jan-2024	11-Jan-2024	180 days	8 days	✔	11-Jan-2024	180 days	8 days	✔	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2401-A-12	E440	03-Jan-2024	11-Jan-2024	180 days	8 days	✔	11-Jan-2024	180 days	8 days	✔	



Matrix: Soil/Solid

Evaluation: * = Holding time exceedance ; ✓ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2401-A-2	E440	03-Jan-2024	11-Jan-2024	180 days	8 days	✓	11-Jan-2024	180 days	8 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2401-A-3	E440	03-Jan-2024	11-Jan-2024	180 days	8 days	✓	11-Jan-2024	180 days	8 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2401-A-4	E440	03-Jan-2024	11-Jan-2024	180 days	8 days	✓	11-Jan-2024	180 days	8 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2401-A-5	E440	03-Jan-2024	11-Jan-2024	180 days	8 days	✓	11-Jan-2024	180 days	8 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2401-A-6	E440	03-Jan-2024	11-Jan-2024	180 days	8 days	✓	11-Jan-2024	180 days	8 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2401-A-7	E440	03-Jan-2024	11-Jan-2024	180 days	8 days	✓	11-Jan-2024	180 days	8 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2401-A-8	E440	03-Jan-2024	11-Jan-2024	180 days	8 days	✓	11-Jan-2024	180 days	8 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2401-A-9	E440	03-Jan-2024	11-Jan-2024	180 days	8 days	✓	11-Jan-2024	180 days	8 days	✓	
Physical Tests : Moisture Content by Gravimetry											
LDPE bag BA2401-A-1	E144	03-Jan-2024	----	----	----		10-Jan-2024	----	8 days		



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2401-A-10	E144	03-Jan-2024	----	----	----		10-Jan-2024	----	8 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2401-A-11	E144	03-Jan-2024	----	----	----		10-Jan-2024	----	8 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2401-A-12	E144	03-Jan-2024	----	----	----		10-Jan-2024	----	8 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2401-A-2	E144	03-Jan-2024	----	----	----		10-Jan-2024	----	8 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2401-A-3	E144	03-Jan-2024	----	----	----		10-Jan-2024	----	8 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2401-A-4	E144	03-Jan-2024	----	----	----		10-Jan-2024	----	8 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2401-A-5	E144	03-Jan-2024	----	----	----		10-Jan-2024	----	8 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2401-A-6	E144	03-Jan-2024	----	----	----		10-Jan-2024	----	8 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2401-A-7	E144	03-Jan-2024	----	----	----		10-Jan-2024	----	8 days	



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2401-A-8	E144	03-Jan-2024	----	----	----		10-Jan-2024	----	8 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2401-A-9	E144	03-Jan-2024	----	----	----		10-Jan-2024	----	8 days	
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2401-A-1	E108	03-Jan-2024	11-Jan-2024	30 days	8 days	✔	11-Jan-2024	30 days	8 days	✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2401-A-10	E108	03-Jan-2024	11-Jan-2024	30 days	8 days	✔	11-Jan-2024	30 days	8 days	✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2401-A-11	E108	03-Jan-2024	11-Jan-2024	30 days	8 days	✔	11-Jan-2024	30 days	8 days	✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2401-A-12	E108	03-Jan-2024	11-Jan-2024	30 days	8 days	✔	11-Jan-2024	30 days	8 days	✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2401-A-2	E108	03-Jan-2024	11-Jan-2024	30 days	8 days	✔	11-Jan-2024	30 days	8 days	✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2401-A-3	E108	03-Jan-2024	11-Jan-2024	30 days	8 days	✔	11-Jan-2024	30 days	8 days	✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2401-A-4	E108	03-Jan-2024	11-Jan-2024	30 days	8 days	✔	11-Jan-2024	30 days	8 days	✔



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2401-A-5	E108	03-Jan-2024	11-Jan-2024	30 days	8 days	✔	11-Jan-2024	30 days	8 days	✔	
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2401-A-6	E108	03-Jan-2024	11-Jan-2024	30 days	8 days	✔	11-Jan-2024	30 days	8 days	✔	
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2401-A-7	E108	03-Jan-2024	11-Jan-2024	30 days	8 days	✔	11-Jan-2024	30 days	8 days	✔	
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2401-A-8	E108	03-Jan-2024	11-Jan-2024	30 days	8 days	✔	11-Jan-2024	30 days	8 days	✔	
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2401-A-9	E108	03-Jan-2024	11-Jan-2024	30 days	8 days	✔	11-Jan-2024	30 days	8 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2401-A-1	E512	10-Jan-2024	17-Jan-2024	36 days	14 days	✔	17-Jan-2024	36 days	14 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2401-A-10	E512	10-Jan-2024	17-Jan-2024	36 days	14 days	✔	17-Jan-2024	36 days	14 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2401-A-11	E512	10-Jan-2024	17-Jan-2024	36 days	14 days	✔	17-Jan-2024	36 days	14 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2401-A-12	E512	10-Jan-2024	17-Jan-2024	36 days	14 days	✔	17-Jan-2024	36 days	14 days	✔	



Matrix: Soil/Solid

Evaluation: * = Holding time exceedance ; ✓ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2401-A-2	E512	10-Jan-2024	17-Jan-2024	36 days	14 days	✓	17-Jan-2024	36 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2401-A-3	E512	10-Jan-2024	17-Jan-2024	36 days	14 days	✓	17-Jan-2024	36 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2401-A-4	E512	10-Jan-2024	17-Jan-2024	36 days	14 days	✓	17-Jan-2024	36 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2401-A-5	E512	10-Jan-2024	17-Jan-2024	36 days	14 days	✓	17-Jan-2024	36 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2401-A-6	E512	10-Jan-2024	17-Jan-2024	36 days	14 days	✓	17-Jan-2024	36 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2401-A-7	E512	10-Jan-2024	17-Jan-2024	36 days	14 days	✓	17-Jan-2024	36 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2401-A-8	E512	10-Jan-2024	17-Jan-2024	36 days	14 days	✓	17-Jan-2024	36 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2401-A-9	E512	10-Jan-2024	17-Jan-2024	36 days	14 days	✓	17-Jan-2024	36 days	14 days	✓
TCLP Metals : Metals by CRC ICPMS (TCLP)										
HDPE - total (lab preserved) BA2401-A-1	E444	10-Jan-2024	17-Jan-2024	188 days	14 days	✓	17-Jan-2024	188 days	14 days	✓



Matrix: Soil/Solid

Evaluation: * = Holding time exceedance ; ✓ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2401-A-10	E444	10-Jan-2024	17-Jan-2024	188 days	14 days	✓	17-Jan-2024	188 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2401-A-11	E444	10-Jan-2024	17-Jan-2024	188 days	14 days	✓	17-Jan-2024	188 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2401-A-12	E444	10-Jan-2024	17-Jan-2024	188 days	14 days	✓	17-Jan-2024	188 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2401-A-2	E444	10-Jan-2024	17-Jan-2024	188 days	14 days	✓	17-Jan-2024	188 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2401-A-3	E444	10-Jan-2024	17-Jan-2024	188 days	14 days	✓	17-Jan-2024	188 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2401-A-4	E444	10-Jan-2024	17-Jan-2024	188 days	14 days	✓	17-Jan-2024	188 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2401-A-5	E444	10-Jan-2024	17-Jan-2024	188 days	14 days	✓	17-Jan-2024	188 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2401-A-6	E444	10-Jan-2024	17-Jan-2024	188 days	14 days	✓	17-Jan-2024	188 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2401-A-7	E444	10-Jan-2024	17-Jan-2024	188 days	14 days	✓	17-Jan-2024	188 days	14 days	✓	



Matrix: Soil/Solid

Evaluation: * = Holding time exceedance ; ✓ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2401-A-8	E444	10-Jan-2024	17-Jan-2024	188 days	14 days	✓	17-Jan-2024	188 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2401-A-9	E444	10-Jan-2024	17-Jan-2024	188 days	14 days	✓	17-Jan-2024	188 days	14 days	✓	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2401-A-1	EPP444	03-Jan-2024	10-Jan-2024	----	----		----	28 days	8 days	✓	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2401-A-10	EPP444	03-Jan-2024	10-Jan-2024	----	----		----	28 days	8 days	✓	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2401-A-11	EPP444	03-Jan-2024	10-Jan-2024	----	----		----	28 days	8 days	✓	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2401-A-12	EPP444	03-Jan-2024	10-Jan-2024	----	----		----	28 days	8 days	✓	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2401-A-2	EPP444	03-Jan-2024	10-Jan-2024	----	----		----	28 days	8 days	✓	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2401-A-3	EPP444	03-Jan-2024	10-Jan-2024	----	----		----	28 days	8 days	✓	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2401-A-4	EPP444	03-Jan-2024	10-Jan-2024	----	----		----	28 days	8 days	✓	



Matrix: **Soil/Solid**

Evaluation: * = Holding time exceedance ; ✓ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2401-A-5	EPP444	03-Jan-2024	10-Jan-2024	----	----		----	28 days	8 days	✓
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2401-A-6	EPP444	03-Jan-2024	10-Jan-2024	----	----		----	28 days	8 days	✓
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2401-A-7	EPP444	03-Jan-2024	10-Jan-2024	----	----		----	28 days	8 days	✓
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2401-A-8	EPP444	03-Jan-2024	10-Jan-2024	----	----		----	28 days	8 days	✓
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2401-A-9	EPP444	03-Jan-2024	10-Jan-2024	----	----		----	28 days	8 days	✓

Legend & Qualifier Definitions

Rec. HT: ALS recommended hold time (see units).



Quality Control Parameter Frequency Compliance

The following report summarizes the frequency of laboratory QC samples analyzed within the analytical batches (QC lots) in which the submitted samples were processed. The actual frequency should be greater than or equal to the expected frequency.

Matrix: **Soil/Solid**

Evaluation: ✖ = QC frequency outside specification; ✔ = QC frequency within specification.

Quality Control Sample Type	Method	QC Lot #	Count		Frequency (%)		
			QC	Regular	Actual	Expected	Evaluation
Analytical Methods							
Laboratory Duplicates (DUP)							
Mercury in Soil/Solid by CVAAS	E510	1299560	1	12	8.3	5.0	✔
Metals in Soil/Solid by CRC ICPMS	E440	1299561	1	12	8.3	5.0	✔
Moisture Content by Gravimetry	E144	1299563	1	12	8.3	5.0	✔
pH by Meter (1:2 Soil:Water Extraction)	E108	1299562	1	12	8.3	5.0	✔
Laboratory Control Samples (LCS)							
Mercury in Soil/Solid by CVAAS	E510	1299560	2	12	16.6	10.0	✔
Metals in Soil/Solid by CRC ICPMS	E440	1299561	2	12	16.6	10.0	✔
Moisture Content by Gravimetry	E144	1299563	1	12	8.3	5.0	✔
pH by Meter (1:2 Soil:Water Extraction)	E108	1299562	1	12	8.3	5.0	✔
Method Blanks (MB)							
Mercury by CVAAS (TCLP)	E512	1304354	1	12	8.3	5.0	✔
Mercury in Soil/Solid by CVAAS	E510	1299560	1	12	8.3	5.0	✔
Metals by CRC ICPMS (TCLP)	E444	1304355	1	12	8.3	5.0	✔
Metals in Soil/Solid by CRC ICPMS	E440	1299561	1	12	8.3	5.0	✔
Moisture Content by Gravimetry	E144	1299563	1	12	8.3	5.0	✔
Matrix Spikes (MS)							
Mercury by CVAAS (TCLP)	E512	1304354	1	12	8.3	5.0	✔
Metals by CRC ICPMS (TCLP)	E444	1304355	1	12	8.3	5.0	✔



Methodology References and Summaries

The analytical methods used by ALS are developed using internationally recognized reference methods (where available), such as those published by US EPA, APHA Standard Methods, ASTM, ISO, Environment Canada, BC MOE, and Ontario MOE. Reference methods may incorporate modifications to improve performance (indicated by "mod").

Analytical Methods	Method / Lab	Matrix	Method Reference	Method Descriptions
pH by Meter (1:2 Soil:Water Extraction)	E108 ALS Environmental - Vancouver	Soil/Solid	BC Lab Manual	pH is determined by potentiometric measurement with a pH electrode at ambient laboratory temperature (normally $20 \pm 5^{\circ}\text{C}$), and is carried out in accordance with procedures described in the BC Lab Manual (prescriptive method). The procedure involves mixing the dried (at $<60^{\circ}\text{C}$) and sieved (10mesh/2mm) sample with ultra pure water at a 1:2 ratio of sediment to water. The pH is then measured by a standard pH probe.
Moisture Content by Gravimetry	E144 ALS Environmental - Vancouver	Soil/Solid	CCME PHC in Soil - Tier 1	Moisture is measured gravimetrically by drying the sample at 105°C . Moisture content is calculated as the weight loss (due to water) divided by the wet weight of the sample, expressed as a percentage.
Metals in Soil/Solid by CRC ICPMS	E440 ALS Environmental - Vancouver	Soil/Solid	EPA 6020B (mod)	This method is intended to liberate metals that may be environmentally available. Samples are dried, then sieved through a 2 mm sieve, and digested with HNO_3 and HCl . Dependent on sample matrix, some metals may be only partially recovered, including Al, Ba, Be, Cr, Sr, Ti, Tl, V, W, and Zr. Silicate minerals are not solubilized. Volatile forms of sulfur (including sulfide) may not be captured, as they may be lost during sampling, storage, or digestion. This method does not adequately recover elemental sulfur, and is unsuitable for assessment of elemental sulfur standards or guidelines. Analysis is by Collision/Reaction Cell ICPMS.
Metals by CRC ICPMS (TCLP)	E444 ALS Environmental - Vancouver	Soil/Solid	EPA 1311/6020B (mod)	An extract produced by the Toxicity Characteristic Leachate Procedure (TCLP) as per EPA 1311 is analyzed by Collision/Reaction Cell ICPMS.
Mercury in Soil/Solid by CVAAS	E510 ALS Environmental - Vancouver	Soil/Solid	EPA 200.2/1631 Appendix (mod)	Samples are dried, then sieved through a 2 mm sieve, and digested with HNO_3 and HCl , followed by CVAAS analysis.
Mercury by CVAAS (TCLP)	E512 ALS Environmental - Vancouver	Soil/Solid	SW 846 -1311/245.1 CVAA ON TCLP LEACHATE	An extract produced by the Toxicity Characteristic Leachate Procedure (TCLP) as per EPA 1311 is analyzed by CVAAS.
Preparation Methods	Method / Lab	Matrix	Method Reference	Method Descriptions
Leach 1:2 Soil:Water for pH/EC	EP108 ALS Environmental - Vancouver	Soil/Solid	BC WLAP METHOD: PH, ELECTROMETRIC, SOIL	The procedure involves mixing the dried (at $<60^{\circ}\text{C}$) and sieved (No. 10 / 2mm) sample with deionized/distilled water at a 1:2 ratio of sediment to water.



<i>Preparation Methods</i>	<i>Method / Lab</i>	<i>Matrix</i>	<i>Method Reference</i>	<i>Method Descriptions</i>
Digestion for Metals and Mercury	EP440 ALS Environmental - Vancouver	Soil/Solid	EPA 200.2 (mod)	Samples are dried, then sieved through a 2 mm sieve, and digested with HNO ₃ and HCl. This method is intended to liberate metals that may be environmentally available.
TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)	EPP444 ALS Environmental - Vancouver	Soil/Solid	EPA 1311	Preparation of a Toxicity Characteristic Leaching Procedure (TCLP) solid sample involves particle size reduction, homogenization, then determination of appropriate extraction fluid. A measured portion of fresh subsample is placed in an extraction bottle with the appropriate extraction fluid then tumbled in a rotary extractor for 18+/- 2 hours at 23 +/- 2 C. The liquid leachate is filtered to separate from solids then bottled and prepared for analytical tests.

QUALITY CONTROL REPORT

Work Order	: VA24A0540	Page	: 1 of 11
Client	: Covanta Burnaby Renewable Energy, ULC	Laboratory	: ALS Environmental - Vancouver
Contact	: Nicole Victor	Account Manager	: Ian Chen
Address	: 5150 Riverbend Drive Burnaby BC Canada V3N 4V3	Address	: 8081 Lougheed Highway Burnaby, British Columbia Canada V5A 1W9
Telephone	:	Telephone	: +1 604 253 4188
Project	: Weekly Bottom Ash - Suite	Date Samples Received	: 10-Jan-2024 16:08
PO	: 46693	Date Analysis Commenced	: 10-Jan-2024
C-O-C number	: ----	Issue Date	: 17-Jan-2024 10:41
Sampler	: ----		
Site	: (includes 2.1 PH)		
Quote number	: Standing Offer (BC work)		
No. of samples received	: 12		
No. of samples analysed	: 12		

This report supersedes any previous report(s) with this reference. Results apply to the sample(s) as submitted. This document shall not be reproduced, except in full.

This Quality Control Report contains the following information:

- Laboratory Duplicate (DUP) Report; Relative Percent Difference (RPD) and Data Quality Objectives
- Matrix Spike (MS) Report; Recovery and Data Quality Objectives
- Reference Material (RM) Report; Recovery and Data Quality Objectives
- Method Blank (MB) Report; Recovery and Data Quality Objectives
- Laboratory Control Sample (LCS) Report; Recovery and Data Quality Objectives

Signatories

This document has been electronically signed by the authorized signatories below. Electronic signing is conducted in accordance with US FDA 21 CFR Part 11.

<i>Signatories</i>	<i>Position</i>	<i>Laboratory Department</i>
Kevin Duarte	Supervisor - Metals ICP Instrumentation	Vancouver Metals, Burnaby, British Columbia
Kim Jensen	Department Manager - Metals	Vancouver Metals, Burnaby, British Columbia
Kim Jensen	Department Manager - Metals	Vancouver Organics, Burnaby, British Columbia
Owen Cheng		Vancouver Metals, Burnaby, British Columbia



General Comments

The ALS Quality Control (QC) report is optionally provided to ALS clients upon request. ALS test methods include comprehensive QC checks with every analysis to ensure our high standards of quality are met. Each QC result has a known or expected target value, which is compared against predetermined Data Quality Objectives (DQOs) to provide confidence in the accuracy of associated test results. This report contains detailed results for all QC results applicable to this sample submission. Please refer to the ALS Quality Control Interpretation report (QCI) for applicable method references and methodology summaries.

Key :

Anonymous = Refers to samples which are not part of this work order, but which formed part of the QC process lot.

CAS Number = Chemical Abstracts Service number is a unique identifier assigned to discrete substances.

DQO = Data Quality Objective.

LOR = Limit of Reporting (detection limit).

RPD = Relative Percent Difference

= Indicates a QC result that did not meet the ALS DQO.

Workorder Comments

Holding times are displayed as "---" if no guidance exists from CCME, Canadian provinces, or broadly recognized international references.



Laboratory Duplicate (DUP) Report

A Laboratory Duplicate (DUP) is a randomly selected intralaboratory replicate sample. Laboratory Duplicates provide information regarding method precision and sample heterogeneity. ALS DQOs for Laboratory Duplicates are expressed as test-specific limits for Relative Percent Difference (RPD), or as an absolute difference limit of 2 times the LOR for low concentration duplicates within ~ 4-10 times the LOR (cut-off is test-specific).

Sub-Matrix: Soil/Solid

					Laboratory Duplicate (DUP) Report						
Laboratory sample ID	Client sample ID	Analyte	CAS Number	Method	LOR	Unit	Original Result	Duplicate Result	RPD(%) or Difference	Duplicate Limits	Qualifier
Physical Tests (QC Lot: 1299562)											
VA24A0540-001	BA2401-A-1	pH (1:2 soil:water)	----	E108	0.10	pH units	11.8	11.7	1.5%	5%	----
Physical Tests (QC Lot: 1299563)											
VA24A0540-001	BA2401-A-1	Moisture	----	E144	0.25	%	22.8	21.9	4.03%	20%	----
Metals (QC Lot: 1299560)											
VA24A0540-001	BA2401-A-1	Mercury	7439-97-6	E510	0.0500	mg/kg	0.0890	0.104	0.0153	Diff <2x LOR	----
Metals (QC Lot: 1299561)											
VA24A0540-001	BA2401-A-1	Aluminum	7429-90-5	E440	50	mg/kg	29500	40100	30.5%	40%	----
		Antimony	7440-36-0	E440	0.10	mg/kg	257	175	37.7%	30%	DUP-H
		Arsenic	7440-38-2	E440	0.10	mg/kg	41.0	19.8	69.9%	30%	DUP-H
		Barium	7440-39-3	E440	0.50	mg/kg	476	479	0.564%	40%	----
		Beryllium	7440-41-7	E440	0.10	mg/kg	0.40	0.39	0.010	Diff <2x LOR	----
		Bismuth	7440-69-9	E440	0.20	mg/kg	30.0	25.3	16.8%	30%	----
		Boron	7440-42-8	E440	5.0	mg/kg	124	147	16.5%	30%	----
		Cadmium	7440-43-9	E440	0.020	mg/kg	18.6	19.5	4.40%	30%	----
		Calcium	7440-70-2	E440	50	mg/kg	134000	152000	12.4%	30%	----
		Chromium	7440-47-3	E440	0.50	mg/kg	139	148	6.27%	30%	----
		Cobalt	7440-48-4	E440	0.10	mg/kg	678	97.9	149%	30%	DUP-H
		Copper	7440-50-8	E440	0.50	mg/kg	3510	1760	66.4%	30%	DUP-H
		Iron	7439-89-6	E440	50	mg/kg	51500	64700	22.7%	30%	----
		Lead	7439-92-1	E440	0.50	mg/kg	471	365	25.3%	40%	----
		Lithium	7439-93-2	E440	2.0	mg/kg	132	30.3	125%	30%	DUP-H
		Magnesium	7439-95-4	E440	20	mg/kg	11700	11600	0.714%	30%	----
		Manganese	7439-96-5	E440	1.0	mg/kg	764	753	1.37%	30%	----
		Molybdenum	7439-98-7	E440	0.10	mg/kg	28.4	30.8	8.06%	40%	----
		Nickel	7440-02-0	E440	0.50	mg/kg	1340	124	166%	30%	DUP-H
		Phosphorus	7723-14-0	E440	50	mg/kg	8940	10800	19.1%	30%	----
		Potassium	7440-09-7	E440	100	mg/kg	7500	8100	7.77%	40%	----
		Selenium	7782-49-2	E440	0.20	mg/kg	0.70	0.61	0.08	Diff <2x LOR	----
		Silver	7440-22-4	E440	0.10	mg/kg	8.95	7.97	11.6%	40%	----
		Sodium	7440-23-5	E440	50	mg/kg	18800	19100	1.68%	40%	----



Sub-Matrix: Soil/Solid					Laboratory Duplicate (DUP) Report						
Laboratory sample ID	Client sample ID	Analyte	CAS Number	Method	LOR	Unit	Original Result	Duplicate Result	RPD(%) or Difference	Duplicate Limits	Qualifier
Metals (QC Lot: 1299561) - continued											
VA24A0540-001	BA2401-A-1	Strontium	7440-24-6	E440	0.50	mg/kg	275	296	7.26%	40%	----
		Sulfur	7704-34-9	E440	1000	mg/kg	13400	13600	2.02%	30%	----
		Thallium	7440-28-0	E440	0.050	mg/kg	0.060	0.060	0.0004	Diff <2x LOR	----
		Tin	7440-31-5	E440	2.0	mg/kg	236	178	27.7%	40%	----
		Titanium	7440-32-6	E440	1.0	mg/kg	214	247	14.3%	40%	----
		Tungsten	7440-33-7	E440	0.50	mg/kg	14.5	21.2	37.5%	30%	DUP-H
		Uranium	7440-61-1	E440	0.050	mg/kg	4.14	4.74	13.7%	30%	----
		Vanadium	7440-62-2	E440	0.20	mg/kg	40.3	46.8	14.8%	30%	----
		Zinc	7440-66-6	E440	2.0	mg/kg	4110	4470	8.29%	30%	----
		Zirconium	7440-67-7	E440	1.0	mg/kg	1.2	2.6	1.4	Diff <2x LOR	----

Qualifiers

Qualifier	Description
DUP-H	Duplicate results outside ALS DQO, due to sample heterogeneity.



Method Blank (MB) Report

A Method Blank is an analyte-free matrix that undergoes sample processing identical to that carried out for test samples. Method Blank results are used to monitor and control for potential contamination from the laboratory environment and reagents. For most tests, the DQO for Method Blanks is for the result to be < LOR.

Sub-Matrix: Soil/Solid

Analyte	CAS Number	Method	LOR	Unit	Result	Qualifier
Physical Tests (QCLot: 1299563)						
Moisture	---	E144	0.25	%	<0.25	---
Metals (QCLot: 1299560)						
Mercury	7439-97-6	E510	0.005	mg/kg	<0.0050	---
Metals (QCLot: 1299561)						
Aluminum	7429-90-5	E440	50	mg/kg	<50	---
Antimony	7440-36-0	E440	0.1	mg/kg	<0.10	---
Arsenic	7440-38-2	E440	0.1	mg/kg	<0.10	---
Barium	7440-39-3	E440	0.5	mg/kg	<0.50	---
Beryllium	7440-41-7	E440	0.1	mg/kg	<0.10	---
Bismuth	7440-69-9	E440	0.2	mg/kg	<0.20	---
Boron	7440-42-8	E440	5	mg/kg	<5.0	---
Cadmium	7440-43-9	E440	0.02	mg/kg	<0.020	---
Calcium	7440-70-2	E440	50	mg/kg	<50	---
Chromium	7440-47-3	E440	0.5	mg/kg	<0.50	---
Cobalt	7440-48-4	E440	0.1	mg/kg	<0.10	---
Copper	7440-50-8	E440	0.5	mg/kg	<0.50	---
Iron	7439-89-6	E440	50	mg/kg	<50	---
Lead	7439-92-1	E440	0.5	mg/kg	<0.50	---
Lithium	7439-93-2	E440	2	mg/kg	<2.0	---
Magnesium	7439-95-4	E440	20	mg/kg	<20	---
Manganese	7439-96-5	E440	1	mg/kg	<1.0	---
Molybdenum	7439-98-7	E440	0.1	mg/kg	<0.10	---
Nickel	7440-02-0	E440	0.5	mg/kg	<0.50	---
Phosphorus	7723-14-0	E440	50	mg/kg	<50	---
Potassium	7440-09-7	E440	100	mg/kg	<100	---
Selenium	7782-49-2	E440	0.2	mg/kg	<0.20	---
Silver	7440-22-4	E440	0.1	mg/kg	<0.10	---
Sodium	7440-23-5	E440	50	mg/kg	<50	---
Strontium	7440-24-6	E440	0.5	mg/kg	<0.50	---
Sulfur	7704-34-9	E440	1000	mg/kg	<1000	---
Thallium	7440-28-0	E440	0.05	mg/kg	<0.050	---
Tin	7440-31-5	E440	2	mg/kg	<2.0	---



Sub-Matrix: **Soil/Solid**

Analyte	CAS Number	Method	LOR	Unit	Result	Qualifier
Metals (QCLot: 1299561) - continued						
Titanium	7440-32-6	E440	1	mg/kg	<1.0	----
Tungsten	7440-33-7	E440	0.5	mg/kg	<0.50	----
Uranium	7440-61-1	E440	0.05	mg/kg	<0.050	----
Vanadium	7440-62-2	E440	0.2	mg/kg	<0.20	----
Zinc	7440-66-6	E440	2	mg/kg	<2.0	----
Zirconium	7440-67-7	E440	1	mg/kg	<1.0	----
TCLP Metals (QCLot: 1304354)						
Mercury, TCLP	7439-97-6	E512	0.001	mg/L	<0.0010	----
TCLP Metals (QCLot: 1304355)						
Antimony, TCLP	7440-36-0	E444	0.1	mg/L	<0.10	----
Arsenic, TCLP	7440-38-2	E444	1	mg/L	<1.0	----
Barium, TCLP	7440-39-3	E444	2.5	mg/L	<2.5	----
Beryllium, TCLP	7440-41-7	E444	0.025	mg/L	<0.025	----
Boron, TCLP	7440-42-8	E444	0.5	mg/L	<0.50	----
Cadmium, TCLP	7440-43-9	E444	0.05	mg/L	<0.050	----
Calcium, TCLP	7440-70-2	E444	10	mg/L	<10	----
Chromium, TCLP	7440-47-3	E444	0.25	mg/L	<0.25	----
Cobalt, TCLP	7440-48-4	E444	0.05	mg/L	<0.050	----
Copper, TCLP	7440-50-8	E444	0.05	mg/L	<0.050	----
Iron, TCLP	7439-89-6	E444	5	mg/L	<5.0	----
Lead, TCLP	7439-92-1	E444	0.25	mg/L	<0.25	----
Magnesium, TCLP	7439-95-4	E444	2.5	mg/L	<2.5	----
Nickel, TCLP	7440-02-0	E444	0.25	mg/L	<0.25	----
Selenium, TCLP	7782-49-2	E444	0.1	mg/L	<0.10	----
Silver, TCLP	7440-22-4	E444	0.05	mg/L	<0.050	----
Thallium, TCLP	7440-28-0	E444	1	mg/L	<1.0	----
Uranium, TCLP	7440-61-1	E444	0.2	mg/L	<0.20	----
Vanadium, TCLP	7440-62-2	E444	0.15	mg/L	<0.15	----
Zinc, TCLP	7440-66-6	E444	0.5	mg/L	<0.50	----
Zirconium, TCLP	7440-67-7	E444	10	mg/L	<10	----



Laboratory Control Sample (LCS) Report

A Laboratory Control Sample (LCS) is an analyte-free matrix that has been fortified (spiked) with test analytes at known concentration and processed in an identical manner to test samples. LCS results are expressed as percent recovery, and are used to monitor and control test method accuracy and precision, independent of test sample matrix.

Sub-Matrix: Soil/Solid

					Laboratory Control Sample (LCS) Report				
					Spike	Recovery (%)	Recovery Limits (%)		
Analyte	CAS Number	Method	LOR	Unit	Concentration	LCS	Low	High	Qualifier
Physical Tests (QCLot: 1299562)									
pH (1:2 soil:water)	----	E108	----	pH units	6 pH units	99.8	95.0	105	----
Physical Tests (QCLot: 1299563)									
Moisture	----	E144	0.25	%	50 %	99.6	90.0	110	----
Metals (QCLot: 1299560)									
Mercury	7439-97-6	E510	0.005	mg/kg	0.1 mg/kg	96.1	80.0	120	----
Metals (QCLot: 1299561)									
Aluminum	7429-90-5	E440	50	mg/kg	200 mg/kg	97.9	80.0	120	----
Antimony	7440-36-0	E440	0.1	mg/kg	100 mg/kg	102	80.0	120	----
Arsenic	7440-38-2	E440	0.1	mg/kg	100 mg/kg	110	80.0	120	----
Barium	7440-39-3	E440	0.5	mg/kg	25 mg/kg	104	80.0	120	----
Beryllium	7440-41-7	E440	0.1	mg/kg	10 mg/kg	91.6	80.0	120	----
Bismuth	7440-69-9	E440	0.2	mg/kg	100 mg/kg	94.7	80.0	120	----
Boron	7440-42-8	E440	5	mg/kg	100 mg/kg	87.7	80.0	120	----
Cadmium	7440-43-9	E440	0.02	mg/kg	10 mg/kg	99.6	80.0	120	----
Calcium	7440-70-2	E440	50	mg/kg	5000 mg/kg	96.4	80.0	120	----
Chromium	7440-47-3	E440	0.5	mg/kg	25 mg/kg	102	80.0	120	----
Cobalt	7440-48-4	E440	0.1	mg/kg	25 mg/kg	101	80.0	120	----
Copper	7440-50-8	E440	0.5	mg/kg	25 mg/kg	97.3	80.0	120	----
Iron	7439-89-6	E440	50	mg/kg	100 mg/kg	102	80.0	120	----
Lead	7439-92-1	E440	0.5	mg/kg	50 mg/kg	96.7	80.0	120	----
Lithium	7439-93-2	E440	2	mg/kg	25 mg/kg	88.3	80.0	120	----
Magnesium	7439-95-4	E440	20	mg/kg	5000 mg/kg	102	80.0	120	----
Manganese	7439-96-5	E440	1	mg/kg	25 mg/kg	96.6	80.0	120	----
Molybdenum	7439-98-7	E440	0.1	mg/kg	25 mg/kg	101	80.0	120	----
Nickel	7440-02-0	E440	0.5	mg/kg	50 mg/kg	102	80.0	120	----
Phosphorus	7723-14-0	E440	50	mg/kg	1000 mg/kg	107	80.0	120	----
Potassium	7440-09-7	E440	100	mg/kg	5000 mg/kg	103	80.0	120	----
Selenium	7782-49-2	E440	0.2	mg/kg	100 mg/kg	106	80.0	120	----
Silver	7440-22-4	E440	0.1	mg/kg	10 mg/kg	88.5	80.0	120	----
Sodium	7440-23-5	E440	50	mg/kg	5000 mg/kg	101	80.0	120	----
Strontium	7440-24-6	E440	0.5	mg/kg	25 mg/kg	98.8	80.0	120	----
Sulfur	7704-34-9	E440	1000	mg/kg	5000 mg/kg	101	80.0	120	----



Sub-Matrix: Soil/Solid

					Laboratory Control Sample (LCS) Report				
					Spike	Recovery (%)	Recovery Limits (%)		
Analyte	CAS Number	Method	LOR	Unit	Concentration	LCS	Low	High	Qualifier
Metals (QCLot: 1299561) - continued									
Thallium	7440-28-0	E440	0.05	mg/kg	100 mg/kg	95.0	80.0	120	----
Tin	7440-31-5	E440	2	mg/kg	50 mg/kg	97.6	80.0	120	----
Titanium	7440-32-6	E440	1	mg/kg	25 mg/kg	101	80.0	120	----
Tungsten	7440-33-7	E440	0.5	mg/kg	10 mg/kg	98.0	80.0	120	----
Uranium	7440-61-1	E440	0.05	mg/kg	0.5 mg/kg	99.7	80.0	120	----
Vanadium	7440-62-2	E440	0.2	mg/kg	50 mg/kg	105	80.0	120	----
Zinc	7440-66-6	E440	2	mg/kg	50 mg/kg	97.4	80.0	120	----
Zirconium	7440-67-7	E440	1	mg/kg	10 mg/kg	102	80.0	120	----



Matrix Spike (MS) Report

A Matrix Spike (MS) is a randomly selected intra-laboratory replicate sample that has been fortified (spiked) with test analytes at known concentration, and processed in an identical manner to test samples. Matrix Spikes provide information regarding analyte recovery and potential matrix effects. MS DQO exceedances due to sample matrix may sometimes be unavoidable; in such cases, test results for the associated sample (or similar samples) may be subject to bias. ND – Recovery not determined, background level >= 1x spike level.

Sub-Matrix: Soil/Solid

					Matrix Spike (MS) Report					
					Spike		Recovery (%)	Recovery Limits (%)		
Laboratory sample ID	Client sample ID	Analyte	CAS Number	Method	Concentration	Target	MS	Low	High	Qualifier
TCLP Metals (QCLot: 1304354)										
VA24A0540-001	BA2401-A-1	Mercury, TCLP	7439-97-6	E512	0.0010 mg/L	0.001 mg/L	97.6	50.0	140	----
TCLP Metals (QCLot: 1304355)										
VA24A0540-001	BA2401-A-1	Antimony, TCLP	7440-36-0	E444	4.60 mg/L	5 mg/L	92.0	50.0	140	----
		Arsenic, TCLP	7440-38-2	E444	4.6 mg/L	5 mg/L	92.0	50.0	140	----
		Barium, TCLP	7440-39-3	E444	11.4 mg/L	12.5 mg/L	91.0	50.0	140	----
		Beryllium, TCLP	7440-41-7	E444	0.212 mg/L	0.25 mg/L	85.0	50.0	140	----
		Boron, TCLP	7440-42-8	E444	9.05 mg/L	10 mg/L	90.5	50.0	140	----
		Cadmium, TCLP	7440-43-9	E444	0.208 mg/L	0.25 mg/L	83.4	50.0	140	----
		Calcium, TCLP	7440-70-2	E444	ND mg/L	250 mg/L	ND	50.0	140	----
		Chromium, TCLP	7440-47-3	E444	1.06 mg/L	1.25 mg/L	84.7	50.0	140	----
		Cobalt, TCLP	7440-48-4	E444	0.205 mg/L	0.25 mg/L	82.1	50.0	140	----
		Copper, TCLP	7440-50-8	E444	1.98 mg/L	2.5 mg/L	79.1	50.0	140	----
		Iron, TCLP	7439-89-6	E444	216 mg/L	250 mg/L	86.3	50.0	140	----
		Lead, TCLP	7439-92-1	E444	8.35 mg/L	10 mg/L	83.5	50.0	140	----
		Magnesium, TCLP	7439-95-4	E444	215 mg/L	250 mg/L	85.9	50.0	140	----
		Nickel, TCLP	7440-02-0	E444	2.13 mg/L	2.5 mg/L	85.2	50.0	140	----
		Selenium, TCLP	7782-49-2	E444	4.40 mg/L	5 mg/L	88.0	50.0	140	----
		Silver, TCLP	7440-22-4	E444	0.072 mg/L	0.1 mg/L	71.6	50.0	140	----
		Thallium, TCLP	7440-28-0	E444	4.2 mg/L	5 mg/L	83.8	50.0	140	----
		Uranium, TCLP	7440-61-1	E444	4.41 mg/L	5 mg/L	88.2	50.0	150	----
		Vanadium, TCLP	7440-62-2	E444	0.65 mg/L	0.75 mg/L	86.5	50.0	140	----
		Zinc, TCLP	7440-66-6	E444	8.06 mg/L	10 mg/L	80.6	50.0	140	----
		Zirconium, TCLP	7440-67-7	E444	0.7 mg/L	1 mg/L	73.9	50.0	150	----



Reference Material (RM) Report

A Reference Material (RM) is a homogenous material with known and well-established analyte concentrations. RMs are processed in an identical manner to test samples, and are used to monitor and control the accuracy and precision of a test method for a typical sample matrix. RM results are expressed as percent recovery of the target analyte concentration. RM targets may be certified target concentrations provided by the RM supplier, or may be ALS long-term mean values (for empirical test methods).

Sub-Matrix:

Laboratory sample ID	Reference Material ID	Analyte	CAS Number	Method	Reference Material (RM) Report				
					RM Target Concentration	Recovery (%) RM	Recovery Limits (%)		Qualifier
							Low	High	
Metals (QCLot: 1299560)									
	SCP SS-2	Mercury	7439-97-6	E510	0.059 mg/kg	103	70.0	130	----
Metals (QCLot: 1299561)									
	SCP SS-2	Aluminum	7429-90-5	E440	9817 mg/kg	105	70.0	130	----
	SCP SS-2	Antimony	7440-36-0	E440	3.99 mg/kg	111	70.0	130	----
	SCP SS-2	Arsenic	7440-38-2	E440	3.73 mg/kg	105	70.0	130	----
	SCP SS-2	Barium	7440-39-3	E440	105 mg/kg	105	70.0	130	----
	SCP SS-2	Beryllium	7440-41-7	E440	0.349 mg/kg	107	70.0	130	----
	SCP SS-2	Boron	7440-42-8	E440	8.5 mg/kg	120	40.0	160	----
	SCP SS-2	Cadmium	7440-43-9	E440	0.91 mg/kg	116	70.0	130	----
	SCP SS-2	Calcium	7440-70-2	E440	31082 mg/kg	105	70.0	130	----
	SCP SS-2	Chromium	7440-47-3	E440	101 mg/kg	120	70.0	130	----
	SCP SS-2	Cobalt	7440-48-4	E440	6.9 mg/kg	103	70.0	130	----
	SCP SS-2	Copper	7440-50-8	E440	123 mg/kg	99.0	70.0	130	----
	SCP SS-2	Iron	7439-89-6	E440	23558 mg/kg	103	70.0	130	----
	SCP SS-2	Lead	7439-92-1	E440	267 mg/kg	103	70.0	130	----
	SCP SS-2	Lithium	7439-93-2	E440	9.5 mg/kg	99.3	70.0	130	----
	SCP SS-2	Magnesium	7439-95-4	E440	5509 mg/kg	105	70.0	130	----
	SCP SS-2	Manganese	7439-96-5	E440	269 mg/kg	106	70.0	130	----
	SCP SS-2	Molybdenum	7439-98-7	E440	1.03 mg/kg	106	70.0	130	----
	SCP SS-2	Nickel	7440-02-0	E440	26.7 mg/kg	107	70.0	130	----
	SCP SS-2	Phosphorus	7723-14-0	E440	752 mg/kg	103	70.0	130	----
	SCP SS-2	Potassium	7440-09-7	E440	1587 mg/kg	121	70.0	130	----
	SCP SS-2	Sodium	7440-23-5	E440	797 mg/kg	107	70.0	130	----
	SCP SS-2	Strontium	7440-24-6	E440	86.1 mg/kg	103	70.0	130	----
	SCP SS-2	Thallium	7440-28-0	E440	0.0786 mg/kg	108	40.0	160	----
	SCP SS-2	Tin	7440-31-5	E440	10.6 mg/kg	99.5	70.0	130	----
	SCP SS-2	Titanium	7440-32-6	E440	839 mg/kg	116	70.0	130	----

Page : 11 of 11
 Work Order : VA24A0540
 Client : Covanta Burnaby Renewable Energy, ULC
 Project : Weekly Bottom Ash - Suite



Sub-Matrix:

Laboratory sample ID	Reference Material ID	Analyte	CAS Number	Method	Reference Material (RM) Report				
					RM Target Concentration	Recovery (%) RM	Recovery Limits (%)		Qualifier
							Low	High	
Metals (QCLot: 1299561) - continued									
	SCP SS-2	Uranium	7440-61-1	E440	0.52 mg/kg	115	70.0	130	----
	SCP SS-2	Vanadium	7440-62-2	E440	32.7 mg/kg	111	70.0	130	----
	SCP SS-2	Zinc	7440-66-6	E440	297 mg/kg	98.5	70.0	130	----
	SCP SS-2	Zirconium	7440-67-7	E440	5.73 mg/kg	107	70.0	130	----



Report To		Report Format / Distribution		Service Requested (Rush for routine analysis subject to availability)					
Company: Covanta Energy		<input type="checkbox"/> Standard <input type="checkbox"/> Other		<input checked="" type="radio"/> Regular (Standard Turnaround Times - Business Days)					
Contact: Nicole Victor / Dan Skrypnik		<input checked="" type="checkbox"/> PDF <input type="checkbox"/> Excel <input type="checkbox"/> Digital <input type="checkbox"/> Fax		<input type="radio"/> Priority (2-4 Business Days) - 50% Surcharge - Contact ALS to Confirm TAT					
Address: 5150 Riverbend Drive		Email 1: nvictor@covanta.com		<input type="radio"/> Emergency (1-2 Bus. Days) - 100% Surcharge - Contact ALS to Confirm TAT					
Burnaby BC		Email 2: ofetherstonhaugh@covanta.com		<input type="radio"/> Same Day or Weekend Emergency - Contact ALS to Confirm TAT					
Phone: 804-521-1025		Email 3: dskrypnik@covanta.com		Analysis Request					
Fax: <input type="checkbox"/> Yes <input type="checkbox"/> No		brent.kirkpatrick@metrovancover.org							
		Sarah.Wellman@metrovancover.org							

Invoice To Same as Report? <input type="checkbox"/> Yes <input type="checkbox"/> No		Client / Project Information		Please indicate below Filtered, Preserved or both (F, P, F/P)																																		
Hardcopy of Invoice with Report? <input type="checkbox"/> Yes <input type="checkbox"/> No		Job #:		<table border="1" style="width:100%; border-collapse: collapse;"> <tr> <td rowspan="4" style="writing-mode: vertical-rl; transform: rotate(180deg);">MET-TCLP-VA (all metals, Hg)</td> <td rowspan="4" style="writing-mode: vertical-rl; transform: rotate(180deg);">MOISTURE</td> <td rowspan="4" style="writing-mode: vertical-rl; transform: rotate(180deg);">Chrome 6</td> <td rowspan="4" style="writing-mode: vertical-rl; transform: rotate(180deg);">MET-CSR+FULL-VA (all metals)</td> <td colspan="6"></td> <td rowspan="4" style="writing-mode: vertical-rl; transform: rotate(180deg);">Number of Containers</td> </tr> <tr><td colspan="6"></td></tr> <tr><td colspan="6"></td></tr> <tr><td colspan="6"></td></tr> </table>						MET-TCLP-VA (all metals, Hg)	MOISTURE	Chrome 6	MET-CSR+FULL-VA (all metals)							Number of Containers																		
MET-TCLP-VA (all metals, Hg)	MOISTURE	Chrome 6	MET-CSR+FULL-VA (all metals)																		Number of Containers																	
Company:		PO / AFE: PO# 46693 Weekly Bottom Ash - Suite																																				
Contact:		LSD: (includes 2:1 pH)																																				
Address:		Quote #:																																				
Phone:																																						

Lab Work Order # (lab use only)		ALS Contact:		Sampler:							
A0540											
Sample #	Sample Identification (This description will appear on the report)	Date (dd-mmm-yy)	Time (hh:mm)	Sample Type	MET-TCLP-VA (all metals, Hg)		MOISTURE	Chrome 6	MET-CSR+FULL-VA (all metals)		Number of Containers
1	BA2401-A-1	03-Jan-24	9:00	Soil	X	X			X		1
2	BA2401-A-2	03-Jan-24	9:00	Soil	X	X			X		1
3	BA2401-A-3	03-Jan-24	9:00	Soil	X	X			X		1
4	BA2401-A-4	03-Jan-24	9:00	Soil	X	X			X		1
5	BA2401-A-5	03-Jan-24	9:00	Soil	X	X			X		1
6	BA2401-A-6	03-Jan-24	9:00	Soil	X	X			X		1
7	BA2401-A-7	03-Jan-24	9:00	Soil	X	X			X		1
8	BA2401-A-8	03-Jan-24	9:00	Soil	X	X			X		1
9	BA2401-A-9	03-Jan-24	9:00	Soil	X	X			X		1
10	BA2401-A-10	03-Jan-24	9:00	Soil	X	X			X		1
11	BA2401-A-11	03-Jan-24	9:00	Soil	X	X			X		1
12	BA2401-A-12	03-Jan-24	9:00	Soil	X	X			X		1

**Environmental Division
 Vancouver**
 Work Order Reference
VA24A0540

Telephone : +1 604 253 4188

Special Instructions / Regulations with water or land use (CCME-Freshwater Aquatic Life/BC CSR - Commercial/AB Tier 1 - Natural, etc) / Hazardous Details

Failure to complete all portions of this form may delay analysis. Please fill in this form LEGIBLY.
 By the use of this form the user acknowledges and agrees with the Terms and Conditions as provided on a separate Excel tab.
 Also provided on another Excel tab are the ALS location addresses, phone numbers and sample container / preservation / holding time table for common analyses.

SHIPMENT RELEASE (client use)			SHIPMENT RECEPTION (lab use only)				SHIPMENT VERIFICATION (lab use only)			
Released by:	Date (dd-mmm-yy)	Time (hh-mm)	Received by:	Date:	Time:	Temperature:	Verified by:	Date:	Time:	Observations: Yes / No ? If Yes add SIF
<i>[Signature]</i>	9-Jan-24	8:00	<i>[Signature]</i>	10 JAN 2024	1350	17, 15°C				