

Bottom Ash Data

2024 Week 25

The following analytical report represents bottom ash composite results for week 25 of 2024 (June 16, 2024 to June 22, 2024).

The bottom ash meets the conditions of Metro Vancouver's 2020 Bottom Ash Management Plan and is suitable for disposal.



CERTIFICATE OF ANALYSIS

Work Order : **VA24B5000**
Client : **Reworld Renewable Burnaby, ULC**
Contact : Nicole Victor
Address : 5150 Riverbend Drive
 Burnaby BC Canada V3N 4V3
Telephone : ----
Project : Weekly Bottom Ash - Suite
PO : 46693
C-O-C number : ----
Sampler : ----
Site : ----
Quote number : Covanta Burnaby Standing Offer 2024
No. of samples received : 12
No. of samples analysed : 12

Page : 1 of 11
Laboratory : ALS Environmental - Vancouver
Account Manager : Ian Chen
Address : 8081 Lougheed Highway
 Burnaby BC Canada V5A 1W9
Telephone : +1 604 253 4188
Date Samples Received : 25-Jun-2024 12:25
Date Analysis Commenced : 26-Jun-2024
Issue Date : 04-Jul-2024 12:31

This report supersedes any previous report(s) with this reference. Results apply to the sample(s) as submitted. This document shall not be reproduced, except in full.

This Certificate of Analysis contains the following information:

- General Comments
- Analytical Results

Additional information pertinent to this report will be found in the following separate attachments: Quality Control Report, QC Interpretive report to assist with Quality Review and Sample Receipt Notification (SRN).

Signatories

This document has been electronically signed by the authorized signatories below. Electronic signing is conducted in accordance with US FDA 21 CFR Part 11.

<i>Signatories</i>	<i>Position</i>	<i>Laboratory Department</i>
Ghazaleh Khanmirzaei	Analyst	Metals, Burnaby, British Columbia
Janice Leung	Supervisor - Organics Instrumentation	Organics, Burnaby, British Columbia
Robin Weeks	Team Leader - Metals	Metals, Burnaby, British Columbia



General Comments

The analytical methods used by ALS are developed using internationally recognized reference methods (where available), such as those published by US EPA, APHA Standard Methods, ASTM, ISO, Environment Canada, BC MOE, and Ontario MOE. Refer to the ALS Quality Control Interpretive report (QCI) for applicable references and methodology summaries. Reference methods may incorporate modifications to improve performance.

Where a reported less than (<) result is higher than the LOR, this may be due to primary sample extract/digestate dilution and/or insufficient sample for analysis.

Where the LOR of a reported result differs from standard LOR, this may be due to high moisture content, insufficient sample (reduced weight employed) or matrix interference.

Please refer to Quality Control Interpretive report (QCI) for information regarding Holding Time compliance.

Key : CAS Number: Chemical Abstracts Services number is a unique identifier assigned to discrete substances
LOR: Limit of Reporting (detection limit).

<i>Unit</i>	<i>Description</i>
%	percent
mg/kg	milligrams per kilogram
mg/L	milligrams per litre
pH units	pH units

<: less than.

>: greater than.

Surrogate: An analyte that is similar in behavior to target analyte(s), but that does not occur naturally in environmental samples. For applicable tests, surrogates are added to samples prior to analysis as a check on recovery.

Test results reported relate only to the samples as received by the laboratory.

UNLESS OTHERWISE STATED on SRN or QCI Report, ALL SAMPLES WERE RECEIVED IN ACCEPTABLE CONDITION.



Analytical Results

Sub-Matrix: Soil/Solid					Client sample ID				
(Matrix: Soil/Solid)					BA2425-A-1	BA2425-A-2	BA2425-A-3	BA2425-A-4	BA2425-A-5
Client sampling date / time					19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24B5000-001	VA24B5000-002	VA24B5000-003	VA24B5000-004	VA24B5000-005
					Result	Result	Result	Result	Result
Physical Tests									
Moisture	----	E144/VA	0.25	%	24.0	23.8	23.3	22.4	23.0
pH (1:2 soil:water)	----	E108/VA	0.10	pH units	11.2	11.1	11.1	11.1	11.3
Metals									
Aluminum	7429-90-5	E440/VA	50	mg/kg	30700	31500	39200	26600	30700
Antimony	7440-36-0	E440/VA	0.10	mg/kg	117	100	109	87.2	108
Arsenic	7440-38-2	E440/VA	0.10	mg/kg	21.3	24.0	23.3	18.2	24.1
Barium	7440-39-3	E440/VA	0.50	mg/kg	569	526	524	444	466
Beryllium	7440-41-7	E440/VA	0.10	mg/kg	0.35	0.32	0.33	0.33	0.30
Bismuth	7440-69-9	E440/VA	0.20	mg/kg	10.4	8.24	10.9	5.96	37.1
Boron	7440-42-8	E440/VA	5.0	mg/kg	247	156	224	155	211
Cadmium	7440-43-9	E440/VA	0.020	mg/kg	7.89	7.40	7.24	6.15	9.19
Calcium	7440-70-2	E440/VA	50	mg/kg	129000	131000	133000	114000	118000
Chromium	7440-47-3	E440/VA	0.50	mg/kg	156	373	149	186	211
Cobalt	7440-48-4	E440/VA	0.10	mg/kg	48.7	98.8	110	69.0	81.4
Copper	7440-50-8	E440/VA	0.50	mg/kg	1610	5340	6700	3420	5520
Iron	7439-89-6	E440/VA	50	mg/kg	46700	51300	56300	45000	54100
Lead	7439-92-1	E440/VA	0.50	mg/kg	760	362	1200	310	420
Lithium	7439-93-2	E440/VA	2.0	mg/kg	24.5	23.8	28.8	29.8	28.4
Magnesium	7439-95-4	E440/VA	20	mg/kg	10400	11100	11600	9090	9400
Manganese	7439-96-5	E440/VA	1.0	mg/kg	4170	721	650	660	780
Mercury	7439-97-6	E510/VA	0.0500	mg/kg	0.0652	0.0574	0.0537	0.0688	0.0540
Molybdenum	7439-98-7	E440/VA	0.10	mg/kg	27.7	68.7	20.4	20.2	22.7
Nickel	7440-02-0	E440/VA	0.50	mg/kg	144	548	122	133	157
Phosphorus	7723-14-0	E440/VA	50	mg/kg	8620	8860	8570	8060	7880
Potassium	7440-09-7	E440/VA	100	mg/kg	5500	5370	5460	4960	4960
Selenium	7782-49-2	E440/VA	0.20	mg/kg	0.30	0.32	0.29	0.26	0.35
Silver	7440-22-4	E440/VA	0.10	mg/kg	4.97	5.54	4.08	7.12	4.08
Sodium	7440-23-5	E440/VA	50	mg/kg	14900	15200	16000	14300	14100
Strontium	7440-24-6	E440/VA	0.50	mg/kg	281	304	298	257	252



Analytical Results

Sub-Matrix: Soil/Solid					Client sample ID				
(Matrix: Soil/Solid)					BA2425-A-1	BA2425-A-2	BA2425-A-3	BA2425-A-4	BA2425-A-5
Client sampling date / time					19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24B5000-001	VA24B5000-002	VA24B5000-003	VA24B5000-004	VA24B5000-005
					Result	Result	Result	Result	Result
Metals									
Sulfur	7704-34-9	E440/VA	1000	mg/kg	11400	11800	11300	9100	11400
Thallium	7440-28-0	E440/VA	0.050	mg/kg	<0.050	<0.050	<0.050	<0.050	<0.050
Tin	7440-31-5	E440/VA	2.0	mg/kg	243	105	458	93.2	168
Titanium	7440-32-6	E440/VA	1.0	mg/kg	258	225	334	198	318
Tungsten	7440-33-7	E440/VA	0.50	mg/kg	7.11	7.47	7.21	5.19	8.27
Uranium	7440-61-1	E440/VA	0.050	mg/kg	1.58	1.53	1.59	1.48	1.55
Vanadium	7440-62-2	E440/VA	0.20	mg/kg	30.6	32.7	32.9	30.6	34.7
Zinc	7440-66-6	E440/VA	2.0	mg/kg	6610	3230	3700	3020	4210
Zirconium	7440-67-7	E440/VA	1.0	mg/kg	2.1	2.4	2.4	2.3	1.6
TCLP Metals									
pH, TCLP 1st preliminary	----	EPP444/VA	0.010	pH units	11.7	11.9	11.9	11.8	11.9
pH, TCLP 2nd preliminary	----	EPP444/VA	0.010	pH units	6.56	7.19	7.18	6.98	7.41
pH, TCLP extraction fluid initial	----	EPP444/VA	0.010	pH units	2.88	2.88	2.88	2.88	2.88
pH, TCLP final	----	EPP444/VA	0.010	pH units	7.89	7.91	7.95	7.86	7.91
Antimony, TCLP	7440-36-0	E444/VA	1.00	mg/L	<1.00	<1.00	<1.00	<1.00	<1.00
Arsenic, TCLP	7440-38-2	E444/VA	1.0	mg/L	<1.0	<1.0	<1.0	<1.0	<1.0
Barium, TCLP	7440-39-3	E444/VA	2.5	mg/L	<2.5	<2.5	<2.5	<2.5	<2.5
Beryllium, TCLP	7440-41-7	E444/VA	0.025	mg/L	<0.025	<0.025	<0.025	<0.025	<0.025
Boron, TCLP	7440-42-8	E444/VA	0.50	mg/L	1.77	1.90	1.98	2.00	1.86
Cadmium, TCLP	7440-43-9	E444/VA	0.050	mg/L	<0.050	<0.050	<0.050	<0.050	<0.050
Calcium, TCLP	7440-70-2	E444/VA	10	mg/L	1570	1580	1650	1660	1660
Chromium, TCLP	7440-47-3	E444/VA	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25
Cobalt, TCLP	7440-48-4	E444/VA	0.050	mg/L	0.120	0.100	0.103	0.179	0.127
Copper, TCLP	7440-50-8	E444/VA	0.050	mg/L	0.921	0.938	0.960	0.951	1.04
Iron, TCLP	7439-89-6	E444/VA	5.0	mg/L	<5.0	<5.0	<5.0	<5.0	<5.0
Lead, TCLP	7439-92-1	E444/VA	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25
Magnesium, TCLP	7439-95-4	E444/VA	2.5	mg/L	81.1	81.6	80.3	84.4	79.5
Mercury, TCLP	7439-97-6	E512/VA	0.0010	mg/L	<0.0010	<0.0010	<0.0010	<0.0010	<0.0010
Nickel, TCLP	7440-02-0	E444/VA	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25
Selenium, TCLP	7782-49-2	E444/VA	0.10	mg/L	<0.10	<0.10	<0.10	<0.10	<0.10



Analytical Results

Sub-Matrix: Soil/Solid

(Matrix: Soil/Solid)

					Client sample ID	BA2425-A-1	BA2425-A-2	BA2425-A-3	BA2425-A-4	BA2425-A-5
					Client sampling date / time	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24B5000-001	VA24B5000-002	VA24B5000-003	VA24B5000-004	VA24B5000-005	
					Result	Result	Result	Result	Result	
TCLP Metals										
Silver, TCLP	7440-22-4	E444/VA	0.050	mg/L	<0.050	<0.050	<0.050	<0.050	<0.050	<0.050
Thallium, TCLP	7440-28-0	E444/VA	1.0	mg/L	<1.0	<1.0	<1.0	<1.0	<1.0	<1.0
Uranium, TCLP	7440-61-1	E444/VA	0.20	mg/L	<0.20	<0.20	<0.20	<0.20	<0.20	<0.20
Vanadium, TCLP	7440-62-2	E444/VA	0.15	mg/L	<0.15	<0.15	<0.15	<0.15	<0.15	<0.15
Zinc, TCLP	7440-66-6	E444/VA	0.50	mg/L	<0.50	<0.50	<0.50	<0.50	<0.50	<0.50
Zirconium, TCLP	7440-67-7	E444/VA	10	mg/L	<10	<10	<10	<10	<10	<10

Please refer to the General Comments section for an explanation of any result qualifiers detected.

Please refer to the Accreditation section for an explanation of analyte accreditations.



Analytical Results

Sub-Matrix: Soil/Solid

Client sample ID

(Matrix: Soil/Solid)

					BA2425-A-6	BA2425-A-7	BA2425-A-8	BA2425-A-9	BA2425-A-10
Client sampling date / time					19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24B5000-006	VA24B5000-007	VA24B5000-008	VA24B5000-009	VA24B5000-010
					Result	Result	Result	Result	Result
Physical Tests									
Moisture	---	E144/VA	0.25	%	21.9	22.1	23.7	24.2	23.8
pH (1:2 soil:water)	---	E108/VA	0.10	pH units	10.9	10.9	11.3	10.9	11.2
Metals									
Aluminum	7429-90-5	E440/VA	50	mg/kg	26000	26200	23100	33700	29400
Antimony	7440-36-0	E440/VA	0.10	mg/kg	93.0	91.0	95.7	84.6	95.1
Arsenic	7440-38-2	E440/VA	0.10	mg/kg	19.5	16.2	21.5	19.5	20.2
Barium	7440-39-3	E440/VA	0.50	mg/kg	380	416	441	466	481
Beryllium	7440-41-7	E440/VA	0.10	mg/kg	0.28	0.33	0.29	0.32	0.29
Bismuth	7440-69-9	E440/VA	0.20	mg/kg	7.21	7.05	10.1	489	7.09
Boron	7440-42-8	E440/VA	5.0	mg/kg	159	140	156	154	177
Cadmium	7440-43-9	E440/VA	0.020	mg/kg	6.70	7.79	7.52	81.2	7.93
Calcium	7440-70-2	E440/VA	50	mg/kg	112000	111000	115000	110000	111000
Chromium	7440-47-3	E440/VA	0.50	mg/kg	140	190	132	112	143
Cobalt	7440-48-4	E440/VA	0.10	mg/kg	116	69.1	78.7	45.4	347
Copper	7440-50-8	E440/VA	0.50	mg/kg	1110	2760	1310	1700	9190
Iron	7439-89-6	E440/VA	50	mg/kg	41500	50300	45300	36200	47700
Lead	7439-92-1	E440/VA	0.50	mg/kg	387	283	364	869	370
Lithium	7439-93-2	E440/VA	2.0	mg/kg	29.3	25.4	21.0	22.8	35.0
Magnesium	7439-95-4	E440/VA	20	mg/kg	9490	9900	9090	9270	8970
Manganese	7439-96-5	E440/VA	1.0	mg/kg	690	643	735	683	601
Mercury	7439-97-6	E510/VA	0.0500	mg/kg	0.0541	<0.0500	0.0537	0.0945	<0.0500
Molybdenum	7439-98-7	E440/VA	0.10	mg/kg	20.8	18.0	19.1	21.1	23.3
Nickel	7440-02-0	E440/VA	0.50	mg/kg	206	153	146	115	110
Phosphorus	7723-14-0	E440/VA	50	mg/kg	7900	6270	7680	6900	7220
Potassium	7440-09-7	E440/VA	100	mg/kg	4650	4870	4610	4590	4610
Selenium	7782-49-2	E440/VA	0.20	mg/kg	0.26	0.32	0.34	0.23	0.26
Silver	7440-22-4	E440/VA	0.10	mg/kg	4.28	3.81	3.20	6.54	5.66
Sodium	7440-23-5	E440/VA	50	mg/kg	13000	13400	13300	13100	13600
Strontium	7440-24-6	E440/VA	0.50	mg/kg	234	312	260	238	311
Sulfur	7704-34-9	E440/VA	1000	mg/kg	9800	9900	10400	9200	10300



Analytical Results

Sub-Matrix: Soil/Solid

Client sample ID

(Matrix: Soil/Solid)

					BA2425-A-6	BA2425-A-7	BA2425-A-8	BA2425-A-9	BA2425-A-10
Client sampling date / time					19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24B5000-006	VA24B5000-007	VA24B5000-008	VA24B5000-009	VA24B5000-010
					Result	Result	Result	Result	Result
Metals									
Thallium	7440-28-0	E440/VA	0.050	mg/kg	<0.050	<0.050	<0.050	<0.050	<0.050
Tin	7440-31-5	E440/VA	2.0	mg/kg	166	118	90.6	449	117
Titanium	7440-32-6	E440/VA	1.0	mg/kg	150	166	164	228	221
Tungsten	7440-33-7	E440/VA	0.50	mg/kg	6.36	6.65	7.04	6.30	6.32
Uranium	7440-61-1	E440/VA	0.050	mg/kg	1.36	1.42	1.38	1.41	1.34
Vanadium	7440-62-2	E440/VA	0.20	mg/kg	25.7	29.4	29.1	27.8	30.8
Zinc	7440-66-6	E440/VA	2.0	mg/kg	2830	3120	4200	3180	17000
Zirconium	7440-67-7	E440/VA	1.0	mg/kg	2.5	2.2	1.8	2.6	1.9
TCLP Metals									
pH, TCLP 1st preliminary	----	EPP444/VA	0.010	pH units	11.8	11.9	11.8	11.8	11.8
pH, TCLP 2nd preliminary	----	EPP444/VA	0.010	pH units	7.32	7.60	7.15	7.68	6.81
pH, TCLP extraction fluid initial	----	EPP444/VA	0.010	pH units	2.88	2.88	2.88	2.88	2.88
pH, TCLP final	----	EPP444/VA	0.010	pH units	8.05	8.04	7.82	7.99	8.08
Antimony, TCLP	7440-36-0	E444/VA	1.00	mg/L	<1.00	<1.00	<1.00	<1.00	<1.00
Arsenic, TCLP	7440-38-2	E444/VA	1.0	mg/L	<1.0	<1.0	<1.0	<1.0	<1.0
Barium, TCLP	7440-39-3	E444/VA	2.5	mg/L	<2.5	<2.5	<2.5	<2.5	<2.5
Beryllium, TCLP	7440-41-7	E444/VA	0.025	mg/L	<0.025	<0.025	<0.025	<0.025	<0.025
Boron, TCLP	7440-42-8	E444/VA	0.50	mg/L	1.93	1.74	1.95	1.94	2.04
Cadmium, TCLP	7440-43-9	E444/VA	0.050	mg/L	<0.050	<0.050	<0.050	<0.050	<0.050
Calcium, TCLP	7440-70-2	E444/VA	10	mg/L	1640	1510	1720	1660	1600
Chromium, TCLP	7440-47-3	E444/VA	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25
Cobalt, TCLP	7440-48-4	E444/VA	0.050	mg/L	0.087	0.073	0.152	0.073	0.073
Copper, TCLP	7440-50-8	E444/VA	0.050	mg/L	0.969	0.989	0.997	0.967	1.03
Iron, TCLP	7439-89-6	E444/VA	5.0	mg/L	<5.0	<5.0	<5.0	<5.0	<5.0
Lead, TCLP	7439-92-1	E444/VA	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25
Magnesium, TCLP	7439-95-4	E444/VA	2.5	mg/L	77.2	75.4	84.0	78.4	77.6
Mercury, TCLP	7439-97-6	E512/VA	0.0010	mg/L	<0.0010	<0.0010	<0.0010	<0.0010	<0.0010
Nickel, TCLP	7440-02-0	E444/VA	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25
Selenium, TCLP	7782-49-2	E444/VA	0.10	mg/L	<0.10	<0.10	<0.10	<0.10	<0.10
Silver, TCLP	7440-22-4	E444/VA	0.050	mg/L	<0.050	<0.050	<0.050	<0.050	<0.050



Analytical Results

Sub-Matrix: Soil/Solid

(Matrix: Soil/Solid)

					Client sample ID	BA2425-A-6	BA2425-A-7	BA2425-A-8	BA2425-A-9	BA2425-A-10
					Client sampling date / time	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00	19-Jun-2024 09:00
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24B5000-006	VA24B5000-007	VA24B5000-008	VA24B5000-009	VA24B5000-010	
					Result	Result	Result	Result	Result	
TCLP Metals										
Thallium, TCLP	7440-28-0	E444/VA	1.0	mg/L	<1.0	<1.0	<1.0	<1.0	<1.0	
Uranium, TCLP	7440-61-1	E444/VA	0.20	mg/L	<0.20	<0.20	<0.20	<0.20	<0.20	
Vanadium, TCLP	7440-62-2	E444/VA	0.15	mg/L	<0.15	<0.15	<0.15	<0.15	<0.15	
Zinc, TCLP	7440-66-6	E444/VA	0.50	mg/L	<0.50	<0.50	<0.50	<0.50	<0.50	
Zirconium, TCLP	7440-67-7	E444/VA	10	mg/L	<10	<10	<10	<10	<10	

Please refer to the General Comments section for an explanation of any result qualifiers detected.

Please refer to the Accreditation section for an explanation of analyte accreditations.



Analytical Results

Sub-Matrix: Soil/Solid

Client sample ID

(Matrix: Soil/Solid)

					BA2425-A-11	BA2425-A-12	----	----	----
					19-Jun-2024 09:00	19-Jun-2024 09:00	----	----	----
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24B5000-011	VA24B5000-012	-----	-----	-----
					Result	Result	----	----	----
Physical Tests									
Moisture	---	E144/VA	0.25	%	22.8	21.8	----	----	----
pH (1:2 soil:water)	---	E108/VA	0.10	pH units	11.1	11.3	----	----	----
Metals									
Aluminum	7429-90-5	E440/VA	50	mg/kg	41200	30300	----	----	----
Antimony	7440-36-0	E440/VA	0.10	mg/kg	101	101	----	----	----
Arsenic	7440-38-2	E440/VA	0.10	mg/kg	16.8	24.7	----	----	----
Barium	7440-39-3	E440/VA	0.50	mg/kg	599	480	----	----	----
Beryllium	7440-41-7	E440/VA	0.10	mg/kg	0.34	0.35	----	----	----
Bismuth	7440-69-9	E440/VA	0.20	mg/kg	10.6	8.37	----	----	----
Boron	7440-42-8	E440/VA	5.0	mg/kg	199	176	----	----	----
Cadmium	7440-43-9	E440/VA	0.020	mg/kg	6.56	39.6	----	----	----
Calcium	7440-70-2	E440/VA	50	mg/kg	128000	138000	----	----	----
Chromium	7440-47-3	E440/VA	0.50	mg/kg	204	232	----	----	----
Cobalt	7440-48-4	E440/VA	0.10	mg/kg	40.9	33.7	----	----	----
Copper	7440-50-8	E440/VA	0.50	mg/kg	5900	2010	----	----	----
Iron	7439-89-6	E440/VA	50	mg/kg	53600	59200	----	----	----
Lead	7439-92-1	E440/VA	0.50	mg/kg	309	366	----	----	----
Lithium	7439-93-2	E440/VA	2.0	mg/kg	22.4	23.8	----	----	----
Magnesium	7439-95-4	E440/VA	20	mg/kg	10800	10500	----	----	----
Manganese	7439-96-5	E440/VA	1.0	mg/kg	771	821	----	----	----
Mercury	7439-97-6	E510/VA	0.0500	mg/kg	<0.0500	0.0535	----	----	----
Molybdenum	7439-98-7	E440/VA	0.10	mg/kg	20.8	23.5	----	----	----
Nickel	7440-02-0	E440/VA	0.50	mg/kg	164	183	----	----	----
Phosphorus	7723-14-0	E440/VA	50	mg/kg	9270	9060	----	----	----
Potassium	7440-09-7	E440/VA	100	mg/kg	5770	5600	----	----	----
Selenium	7782-49-2	E440/VA	0.20	mg/kg	0.32	0.28	----	----	----
Silver	7440-22-4	E440/VA	0.10	mg/kg	5.67	3.79	----	----	----
Sodium	7440-23-5	E440/VA	50	mg/kg	15700	14900	----	----	----
Strontium	7440-24-6	E440/VA	0.50	mg/kg	271	289	----	----	----
Sulfur	7704-34-9	E440/VA	1000	mg/kg	10400	11000	----	----	----



Analytical Results

Sub-Matrix: Soil/Solid					Client sample ID		BA2425-A-11	BA2425-A-12	----	----	----
(Matrix: Soil/Solid)					Client sampling date / time		19-Jun-2024 09:00	19-Jun-2024 09:00	----	----	----
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24B5000-011	VA24B5000-012	-----	-----	-----	-----	-----
					Result	Result	----	----	----	----	----
Metals											
Thallium	7440-28-0	E440/VA	0.050	mg/kg	<0.050	<0.050	----	----	----	----	----
Tin	7440-31-5	E440/VA	2.0	mg/kg	172	204	----	----	----	----	----
Titanium	7440-32-6	E440/VA	1.0	mg/kg	330	204	----	----	----	----	----
Tungsten	7440-33-7	E440/VA	0.50	mg/kg	8.39	6.58	----	----	----	----	----
Uranium	7440-61-1	E440/VA	0.050	mg/kg	1.64	1.62	----	----	----	----	----
Vanadium	7440-62-2	E440/VA	0.20	mg/kg	35.0	33.6	----	----	----	----	----
Zinc	7440-66-6	E440/VA	2.0	mg/kg	3070	2980	----	----	----	----	----
Zirconium	7440-67-7	E440/VA	1.0	mg/kg	2.5	3.4	----	----	----	----	----
TCLP Metals											
pH, TCLP 1st preliminary	----	EPP444/VA	0.010	pH units	11.9	11.9	----	----	----	----	----
pH, TCLP 2nd preliminary	----	EPP444/VA	0.010	pH units	7.06	8.32	----	----	----	----	----
pH, TCLP extraction fluid initial	----	EPP444/VA	0.010	pH units	2.88	2.88	----	----	----	----	----
pH, TCLP final	----	EPP444/VA	0.010	pH units	8.02	7.81	----	----	----	----	----
Antimony, TCLP	7440-36-0	E444/VA	1.00	mg/L	<1.00	<1.00	----	----	----	----	----
Arsenic, TCLP	7440-38-2	E444/VA	1.0	mg/L	<1.0	<1.0	----	----	----	----	----
Barium, TCLP	7440-39-3	E444/VA	2.5	mg/L	<2.5	<2.5	----	----	----	----	----
Beryllium, TCLP	7440-41-7	E444/VA	0.025	mg/L	<0.025	<0.025	----	----	----	----	----
Boron, TCLP	7440-42-8	E444/VA	0.50	mg/L	1.92	1.88	----	----	----	----	----
Cadmium, TCLP	7440-43-9	E444/VA	0.050	mg/L	<0.050	<0.050	----	----	----	----	----
Calcium, TCLP	7440-70-2	E444/VA	10	mg/L	1620	1660	----	----	----	----	----
Chromium, TCLP	7440-47-3	E444/VA	0.25	mg/L	<0.25	<0.25	----	----	----	----	----
Cobalt, TCLP	7440-48-4	E444/VA	0.050	mg/L	0.080	0.146	----	----	----	----	----
Copper, TCLP	7440-50-8	E444/VA	0.050	mg/L	1.04	0.955	----	----	----	----	----
Iron, TCLP	7439-89-6	E444/VA	5.0	mg/L	<5.0	<5.0	----	----	----	----	----
Lead, TCLP	7439-92-1	E444/VA	0.25	mg/L	<0.25	<0.25	----	----	----	----	----
Magnesium, TCLP	7439-95-4	E444/VA	2.5	mg/L	75.7	82.3	----	----	----	----	----
Mercury, TCLP	7439-97-6	E512/VA	0.0010	mg/L	<0.0010	<0.0010	----	----	----	----	----
Nickel, TCLP	7440-02-0	E444/VA	0.25	mg/L	<0.25	<0.25	----	----	----	----	----
Selenium, TCLP	7782-49-2	E444/VA	0.10	mg/L	<0.10	<0.10	----	----	----	----	----
Silver, TCLP	7440-22-4	E444/VA	0.050	mg/L	<0.050	<0.050	----	----	----	----	----



Analytical Results

Sub-Matrix: Soil/Solid					Client sample ID		BA2425-A-11	BA2425-A-12	----	----	----
(Matrix: Soil/Solid)					Client sampling date / time		19-Jun-2024 09:00	19-Jun-2024 09:00	----	----	----
Analyte	CAS Number	Method/Lab	LOR	Unit	VA24B5000-011	VA24B5000-012	-----	-----	-----	-----	-----
TCLP Metals					Result	Result	---	---	---	---	---
Thallium, TCLP	7440-28-0	E444/VA	1.0	mg/L	<1.0	<1.0	---	---	---	---	---
Uranium, TCLP	7440-61-1	E444/VA	0.20	mg/L	<0.20	<0.20	---	---	---	---	---
Vanadium, TCLP	7440-62-2	E444/VA	0.15	mg/L	<0.15	<0.15	---	---	---	---	---
Zinc, TCLP	7440-66-6	E444/VA	0.50	mg/L	<0.50	<0.50	---	---	---	---	---
Zirconium, TCLP	7440-67-7	E444/VA	10	mg/L	<10	<10	---	---	---	---	---

Please refer to the General Comments section for an explanation of any result qualifiers detected.

Please refer to the Accreditation section for an explanation of analyte accreditations.



QUALITY CONTROL INTERPRETIVE REPORT

<p>Work Order : VA24B5000</p> <p>Client : Reworld Renewable Burnaby, ULC</p> <p>Contact : Nicole Victor</p> <p>Address : 5150 Riverbend Drive Burnaby BC Canada V3N 4V3</p> <p>Telephone : ----</p> <p>Project : Weekly Bottom Ash - Suite</p> <p>PO : 46693</p> <p>C-O-C number : ----</p> <p>Sampler : ----</p> <p>Site : ----</p> <p>Quote number : Covanta Burnaby Standing Offer 2024</p> <p>No. of samples received : 12</p> <p>No. of samples analysed : 12</p>	<p>Page : 1 of 16</p> <p>Laboratory : ALS Environmental - Vancouver</p> <p>Account Manager : Ian Chen</p> <p>Address : 8081 Lougheed Highway Burnaby, British Columbia Canada V5A 1W9</p> <p>Telephone : +1 604 253 4188</p> <p>Date Samples Received : 25-Jun-2024 12:25</p> <p>Issue Date : 04-Jul-2024 12:32</p>
---	--

This report is automatically generated by the ALS LIMS (Laboratory Information Management System) through evaluation of Quality Control (QC) results and other QA parameters associated with this submission, and is intended to facilitate rapid data validation by auditors or reviewers. The report highlights any exceptions and outliers to ALS Data Quality Objectives, provides holding time details and exceptions, summarizes QC sample frequencies, and lists applicable methodology references and summaries.

Key

- Anonymous: Refers to samples which are not part of this work order, but which formed part of the QC process lot.
- CAS Number: Chemical Abstracts Service number is a unique identifier assigned to discrete substances.
- DQO: Data Quality Objective.
- LOR: Limit of Reporting (detection limit).
- RPD: Relative Percent Difference.

Workorder Comments

Holding times are displayed as "----" if no guidance exists from CCME, Canadian provinces, or broadly recognized international references.

Summary of Outliers

Outliers : Quality Control Samples

- No Method Blank value outliers occur.
- No Laboratory Control Sample (LCS) outliers occur
- No Matrix Spike outliers occur.
- Duplicate outliers occur - please see following pages for full details.
- No Test sample Surrogate recovery outliers exist.

Outliers: Reference Material (RM) Samples

- No Reference Material (RM) Sample outliers occur.

Outliers : Analysis Holding Time Compliance (Breaches)

- No Analysis Holding Time Outliers exist.

Outliers : Frequency of Quality Control Samples

- No Quality Control Sample Frequency Outliers occur.



Outliers : Quality Control Samples

Duplicates, Method Blanks, Laboratory Control Samples and Matrix Spikes

Matrix: **Soil/Solid**

Analyte Group	Laboratory sample ID	Client/Ref Sample ID	Analyte	CAS Number	Method	Result	Limits	Comment
Duplicate (DUP) RPDs								
Metals	Anonymous	Anonymous	Chromium	7440-47-3	E440	35.4 % DUP-H	30%	Duplicate RPD does not meet the DQO for this test.
Metals	Anonymous	Anonymous	Uranium	7440-61-1	E440	0.103 % DUP-H	Diff <2x LOR	Low Level DUP DQO exceeded (difference > 2 LOR).

Result Qualifiers

Qualifier	Description
DUP-H	Duplicate results outside ALS DQO, due to sample heterogeneity.



Analysis Holding Time Compliance

This report summarizes extraction / preparation and analysis times and compares each with ALS recommended holding times, which are selected to meet known provincial and /or federal requirements. In the absence of regulatory hold times, ALS establishes recommendations based on guidelines published by organizations such as CCME, US EPA, APHA Standard Methods, ASTM, or Environment Canada (where available). Dates and holding times reported below represent the first dates of extraction or analysis. If subsequent tests or dilutions exceeded holding times, qualifiers are added (refer to COA).

If samples are identified below as having been analyzed or extracted outside of recommended holding times, measurement uncertainties may be increased, and this should be taken into consideration when interpreting results.

Where actual sampling date is not provided on the chain of custody, the date of receipt with time at 00:00 is used for calculation purposes.

Where only the sample date without time is provided on the chain of custody, the sampling date at 00:00 is used for calculation purposes.

Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2425-A-1	E510	19-Jun-2024	27-Jun-2024	28 days	8 days	✔	29-Jun-2024	28 days	10 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2425-A-10	E510	19-Jun-2024	27-Jun-2024	28 days	8 days	✔	29-Jun-2024	28 days	10 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2425-A-11	E510	19-Jun-2024	27-Jun-2024	28 days	8 days	✔	29-Jun-2024	28 days	10 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2425-A-12	E510	19-Jun-2024	27-Jun-2024	28 days	8 days	✔	29-Jun-2024	28 days	10 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2425-A-2	E510	19-Jun-2024	27-Jun-2024	28 days	8 days	✔	29-Jun-2024	28 days	10 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2425-A-3	E510	19-Jun-2024	27-Jun-2024	28 days	8 days	✔	29-Jun-2024	28 days	10 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2425-A-4	E510	19-Jun-2024	27-Jun-2024	28 days	8 days	✔	29-Jun-2024	28 days	10 days	✔	



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
Metals : Mercury in Soil/Solid by CVAAS										
LDPE bag BA2425-A-5	E510	19-Jun-2024	27-Jun-2024	28 days	8 days	✔	29-Jun-2024	28 days	10 days	✔
Metals : Mercury in Soil/Solid by CVAAS										
LDPE bag BA2425-A-6	E510	19-Jun-2024	27-Jun-2024	28 days	8 days	✔	29-Jun-2024	28 days	10 days	✔
Metals : Mercury in Soil/Solid by CVAAS										
LDPE bag BA2425-A-7	E510	19-Jun-2024	27-Jun-2024	28 days	8 days	✔	29-Jun-2024	28 days	10 days	✔
Metals : Mercury in Soil/Solid by CVAAS										
LDPE bag BA2425-A-8	E510	19-Jun-2024	27-Jun-2024	28 days	8 days	✔	29-Jun-2024	28 days	10 days	✔
Metals : Mercury in Soil/Solid by CVAAS										
LDPE bag BA2425-A-9	E510	19-Jun-2024	27-Jun-2024	28 days	8 days	✔	29-Jun-2024	28 days	10 days	✔
Metals : Metals in Soil/Solid by CRC ICPMS										
LDPE bag BA2425-A-1	E440	19-Jun-2024	27-Jun-2024	180 days	8 days	✔	29-Jun-2024	180 days	10 days	✔
Metals : Metals in Soil/Solid by CRC ICPMS										
LDPE bag BA2425-A-10	E440	19-Jun-2024	27-Jun-2024	180 days	8 days	✔	29-Jun-2024	180 days	10 days	✔
Metals : Metals in Soil/Solid by CRC ICPMS										
LDPE bag BA2425-A-11	E440	19-Jun-2024	27-Jun-2024	180 days	8 days	✔	29-Jun-2024	180 days	10 days	✔
Metals : Metals in Soil/Solid by CRC ICPMS										
LDPE bag BA2425-A-12	E440	19-Jun-2024	27-Jun-2024	180 days	8 days	✔	29-Jun-2024	180 days	10 days	✔



Matrix: Soil/Solid

Evaluation: * = Holding time exceedance ; ✓ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2425-A-2	E440	19-Jun-2024	27-Jun-2024	180 days	8 days	✓	29-Jun-2024	180 days	10 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2425-A-3	E440	19-Jun-2024	27-Jun-2024	180 days	8 days	✓	29-Jun-2024	180 days	10 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2425-A-4	E440	19-Jun-2024	27-Jun-2024	180 days	8 days	✓	29-Jun-2024	180 days	10 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2425-A-5	E440	19-Jun-2024	27-Jun-2024	180 days	8 days	✓	29-Jun-2024	180 days	10 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2425-A-6	E440	19-Jun-2024	27-Jun-2024	180 days	8 days	✓	29-Jun-2024	180 days	10 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2425-A-7	E440	19-Jun-2024	27-Jun-2024	180 days	8 days	✓	29-Jun-2024	180 days	10 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2425-A-8	E440	19-Jun-2024	27-Jun-2024	180 days	8 days	✓	29-Jun-2024	180 days	10 days	✓	
Metals : Metals in Soil/Solid by CRC ICPMS											
LDPE bag BA2425-A-9	E440	19-Jun-2024	27-Jun-2024	180 days	8 days	✓	29-Jun-2024	180 days	10 days	✓	
Physical Tests : Moisture Content by Gravimetry											
LDPE bag BA2425-A-1	E144	19-Jun-2024	----	----	----		26-Jun-2024	----	7 days		



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2425-A-10	E144	19-Jun-2024	----	----	----		26-Jun-2024	----	7 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2425-A-11	E144	19-Jun-2024	----	----	----		26-Jun-2024	----	7 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2425-A-12	E144	19-Jun-2024	----	----	----		26-Jun-2024	----	7 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2425-A-2	E144	19-Jun-2024	----	----	----		26-Jun-2024	----	7 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2425-A-3	E144	19-Jun-2024	----	----	----		26-Jun-2024	----	7 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2425-A-4	E144	19-Jun-2024	----	----	----		26-Jun-2024	----	7 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2425-A-5	E144	19-Jun-2024	----	----	----		26-Jun-2024	----	7 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2425-A-6	E144	19-Jun-2024	----	----	----		26-Jun-2024	----	7 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2425-A-7	E144	19-Jun-2024	----	----	----		26-Jun-2024	----	7 days	



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2425-A-8	E144	19-Jun-2024	----	----	----		26-Jun-2024	----	7 days	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2425-A-9	E144	19-Jun-2024	----	----	----		26-Jun-2024	----	7 days	
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2425-A-1	E108	19-Jun-2024	27-Jun-2024	30 days	8 days	✔	27-Jun-2024	30 days	8 days	✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2425-A-10	E108	19-Jun-2024	27-Jun-2024	30 days	8 days	✔	27-Jun-2024	30 days	8 days	✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2425-A-11	E108	19-Jun-2024	27-Jun-2024	30 days	8 days	✔	27-Jun-2024	30 days	8 days	✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2425-A-12	E108	19-Jun-2024	27-Jun-2024	30 days	8 days	✔	27-Jun-2024	30 days	8 days	✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2425-A-2	E108	19-Jun-2024	27-Jun-2024	30 days	8 days	✔	27-Jun-2024	30 days	8 days	✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2425-A-3	E108	19-Jun-2024	27-Jun-2024	30 days	8 days	✔	27-Jun-2024	30 days	8 days	✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2425-A-4	E108	19-Jun-2024	27-Jun-2024	30 days	8 days	✔	27-Jun-2024	30 days	8 days	✔



Matrix: Soil/Solid

Evaluation: * = Holding time exceedance ; ✓ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2425-A-5	E108	19-Jun-2024	27-Jun-2024	30 days	8 days	✓	27-Jun-2024	30 days	8 days	✓
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2425-A-6	E108	19-Jun-2024	27-Jun-2024	30 days	8 days	✓	27-Jun-2024	30 days	8 days	✓
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2425-A-7	E108	19-Jun-2024	27-Jun-2024	30 days	8 days	✓	27-Jun-2024	30 days	8 days	✓
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2425-A-8	E108	19-Jun-2024	27-Jun-2024	30 days	8 days	✓	27-Jun-2024	30 days	8 days	✓
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)										
LDPE bag BA2425-A-9	E108	19-Jun-2024	27-Jun-2024	30 days	8 days	✓	27-Jun-2024	30 days	8 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2425-A-1	E512	28-Jun-2024	03-Jul-2024	37 days	14 days	✓	03-Jul-2024	37 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2425-A-10	E512	28-Jun-2024	03-Jul-2024	37 days	14 days	✓	03-Jul-2024	37 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2425-A-11	E512	28-Jun-2024	03-Jul-2024	37 days	14 days	✓	03-Jul-2024	37 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2425-A-12	E512	28-Jun-2024	03-Jul-2024	37 days	14 days	✓	03-Jul-2024	37 days	14 days	✓



Matrix: Soil/Solid

Evaluation: * = Holding time exceedance ; ✓ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2425-A-2	E512	28-Jun-2024	03-Jul-2024	37 days	14 days	✓	03-Jul-2024	37 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2425-A-3	E512	28-Jun-2024	03-Jul-2024	37 days	14 days	✓	03-Jul-2024	37 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2425-A-4	E512	28-Jun-2024	03-Jul-2024	37 days	14 days	✓	03-Jul-2024	37 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2425-A-5	E512	28-Jun-2024	03-Jul-2024	37 days	14 days	✓	03-Jul-2024	37 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2425-A-6	E512	28-Jun-2024	03-Jul-2024	37 days	14 days	✓	03-Jul-2024	37 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2425-A-7	E512	28-Jun-2024	03-Jul-2024	37 days	14 days	✓	03-Jul-2024	37 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2425-A-8	E512	28-Jun-2024	03-Jul-2024	37 days	14 days	✓	03-Jul-2024	37 days	14 days	✓
TCLP Metals : Mercury by CVAAS (TCLP)										
Glass vial - total (lab preserved) BA2425-A-9	E512	28-Jun-2024	03-Jul-2024	37 days	14 days	✓	03-Jul-2024	37 days	14 days	✓
TCLP Metals : Metals by CRC ICPMS (TCLP)										
HDPE - total (lab preserved) BA2425-A-1	E444	28-Jun-2024	03-Jul-2024	189 days	14 days	✓	03-Jul-2024	189 days	14 days	✓



Matrix: Soil/Solid

Evaluation: * = Holding time exceedance ; ✓ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2425-A-10	E444	28-Jun-2024	03-Jul-2024	189 days	14 days	✓	03-Jul-2024	189 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2425-A-11	E444	28-Jun-2024	03-Jul-2024	189 days	14 days	✓	03-Jul-2024	189 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2425-A-12	E444	28-Jun-2024	03-Jul-2024	189 days	14 days	✓	03-Jul-2024	189 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2425-A-2	E444	28-Jun-2024	03-Jul-2024	189 days	14 days	✓	03-Jul-2024	189 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2425-A-3	E444	28-Jun-2024	03-Jul-2024	189 days	14 days	✓	03-Jul-2024	189 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2425-A-4	E444	28-Jun-2024	03-Jul-2024	189 days	14 days	✓	03-Jul-2024	189 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2425-A-5	E444	28-Jun-2024	03-Jul-2024	189 days	14 days	✓	03-Jul-2024	189 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2425-A-6	E444	28-Jun-2024	03-Jul-2024	189 days	14 days	✓	03-Jul-2024	189 days	14 days	✓	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2425-A-7	E444	28-Jun-2024	03-Jul-2024	189 days	14 days	✓	03-Jul-2024	189 days	14 days	✓	



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2425-A-8	E444	28-Jun-2024	03-Jul-2024	189 days	14 days	✔	03-Jul-2024	189 days	14 days	✔	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2425-A-9	E444	28-Jun-2024	03-Jul-2024	189 days	14 days	✔	03-Jul-2024	189 days	14 days	✔	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2425-A-1	EPP444	19-Jun-2024	28-Jun-2024	----	----		----	28 days	9 days	✔	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2425-A-10	EPP444	19-Jun-2024	28-Jun-2024	----	----		----	28 days	9 days	✔	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2425-A-11	EPP444	19-Jun-2024	28-Jun-2024	----	----		----	28 days	9 days	✔	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2425-A-12	EPP444	19-Jun-2024	28-Jun-2024	----	----		----	28 days	9 days	✔	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2425-A-2	EPP444	19-Jun-2024	28-Jun-2024	----	----		----	28 days	9 days	✔	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2425-A-3	EPP444	19-Jun-2024	28-Jun-2024	----	----		----	28 days	9 days	✔	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)											
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2425-A-4	EPP444	19-Jun-2024	28-Jun-2024	----	----		----	28 days	9 days	✔	



Matrix: **Soil/Solid**

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group : Analytical Method Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2425-A-5	EPP444	19-Jun-2024	28-Jun-2024	----	----		----	28 days	9 days	✔
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2425-A-6	EPP444	19-Jun-2024	28-Jun-2024	----	----		----	28 days	9 days	✔
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2425-A-7	EPP444	19-Jun-2024	28-Jun-2024	----	----		----	28 days	9 days	✔
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2425-A-8	EPP444	19-Jun-2024	28-Jun-2024	----	----		----	28 days	9 days	✔
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2425-A-9	EPP444	19-Jun-2024	28-Jun-2024	----	----		----	28 days	9 days	✔

Legend & Qualifier Definitions

Rec. HT: ALS recommended hold time (see units).



Quality Control Parameter Frequency Compliance

The following report summarizes the frequency of laboratory QC samples analyzed within the analytical batches (QC lots) in which the submitted samples were processed. The actual frequency should be greater than or equal to the expected frequency.

Matrix: **Soil/Solid**

Evaluation: ✖ = QC frequency outside specification; ✔ = QC frequency within specification.

Quality Control Sample Type	Method	QC Lot #	Count		Frequency (%)		
			QC	Regular	Actual	Expected	Evaluation
Analytical Methods							
Laboratory Duplicates (DUP)							
Mercury by CVAAS (TCLP)	E512	1525424	1	12	8.3	5.0	✔
Mercury in Soil/Solid by CVAAS	E510	1515508	1	20	5.0	5.0	✔
Metals by CRC ICPMS (TCLP)	E444	1525425	1	12	8.3	5.0	✔
Metals in Soil/Solid by CRC ICPMS	E440	1515509	1	20	5.0	5.0	✔
Moisture Content by Gravimetry	E144	1515511	1	16	6.2	5.0	✔
pH by Meter (1:2 Soil:Water Extraction)	E108	1515510	1	20	5.0	5.0	✔
Laboratory Control Samples (LCS)							
Mercury in Soil/Solid by CVAAS	E510	1515508	2	20	10.0	10.0	✔
Metals in Soil/Solid by CRC ICPMS	E440	1515509	2	20	10.0	10.0	✔
Moisture Content by Gravimetry	E144	1515511	1	16	6.2	5.0	✔
pH by Meter (1:2 Soil:Water Extraction)	E108	1515510	1	20	5.0	5.0	✔
Method Blanks (MB)							
Mercury by CVAAS (TCLP)	E512	1525424	1	12	8.3	5.0	✔
Mercury in Soil/Solid by CVAAS	E510	1515508	1	20	5.0	5.0	✔
Metals by CRC ICPMS (TCLP)	E444	1525425	1	12	8.3	5.0	✔
Metals in Soil/Solid by CRC ICPMS	E440	1515509	1	20	5.0	5.0	✔
Moisture Content by Gravimetry	E144	1515511	1	16	6.2	5.0	✔
Matrix Spikes (MS)							
Mercury by CVAAS (TCLP)	E512	1525424	1	12	8.3	5.0	✔
Metals by CRC ICPMS (TCLP)	E444	1525425	1	12	8.3	5.0	✔



Methodology References and Summaries

The analytical methods used by ALS are developed using internationally recognized reference methods (where available), such as those published by US EPA, APHA Standard Methods, ASTM, ISO, Environment Canada, BC MOE, and Ontario MOE. Reference methods may incorporate modifications to improve performance (indicated by "mod").

Analytical Methods	Method / Lab	Matrix	Method Reference	Method Descriptions
pH by Meter (1:2 Soil:Water Extraction)	E108 ALS Environmental - Vancouver	Soil/Solid	BC Lab Manual	pH is determined by potentiometric measurement with a pH electrode at ambient laboratory temperature (normally $20 \pm 5^{\circ}\text{C}$), and is carried out in accordance with procedures described in the BC Lab Manual (prescriptive method). The procedure involves mixing the dried (at $<60^{\circ}\text{C}$) and sieved (10mesh/2mm) sample with ultra pure water at a 1:2 ratio of sediment to water. The pH is then measured by a standard pH probe.
Moisture Content by Gravimetry	E144 ALS Environmental - Vancouver	Soil/Solid	CCME PHC in Soil - Tier 1	Moisture is measured gravimetrically by drying the sample at 105°C . Moisture content is calculated as the weight loss (due to water) divided by the wet weight of the sample, expressed as a percentage.
Metals in Soil/Solid by CRC ICPMS	E440 ALS Environmental - Vancouver	Soil/Solid	EPA 6020B (mod)	This method is intended to liberate metals that may be environmentally available. Samples are dried, then sieved through a 2 mm sieve, and digested with HNO_3 and HCl . Dependent on sample matrix, some metals may be only partially recovered, including Al, Ba, Be, Cr, Sr, Ti, Tl, V, W, and Zr. Silicate minerals are not solubilized. Volatile forms of sulfur (including sulfide) may not be captured, as they may be lost during sampling, storage, or digestion. This method does not adequately recover elemental sulfur, and is unsuitable for assessment of elemental sulfur standards or guidelines. Analysis is by Collision/Reaction Cell ICPMS.
Metals by CRC ICPMS (TCLP)	E444 ALS Environmental - Vancouver	Soil/Solid	EPA 1311/6020B (mod)	An extract produced by the Toxicity Characteristic Leachate Procedure (TCLP) as per EPA 1311 is analyzed by Collision/Reaction Cell ICPMS.
Mercury in Soil/Solid by CVAAS	E510 ALS Environmental - Vancouver	Soil/Solid	EPA 200.2/1631 Appendix (mod)	Samples are dried, then sieved through a 2 mm sieve, and digested with HNO_3 and HCl , followed by CVAAS analysis.
Mercury by CVAAS (TCLP)	E512 ALS Environmental - Vancouver	Soil/Solid	SW 846 -1311/245.1 CVAA ON TCLP LEACHATE	An extract produced by the Toxicity Characteristic Leachate Procedure (TCLP) as per EPA 1311 is analyzed by CVAAS.
Preparation Methods	Method / Lab	Matrix	Method Reference	Method Descriptions
Leach 1:2 Soil:Water for pH/EC	EP108 ALS Environmental - Vancouver	Soil/Solid	BC WLAP METHOD: PH, ELECTROMETRIC, SOIL	The procedure involves mixing the dried (at $<60^{\circ}\text{C}$) and sieved (No. 10 / 2mm) sample with deionized/distilled water at a 1:2 ratio of sediment to water.

Page : 16 of 16
 Work Order : VA24B5000
 Client : Reworld Renewable Burnaby, ULC
 Project : Weekly Bottom Ash - Suite



<i>Preparation Methods</i>	<i>Method / Lab</i>	<i>Matrix</i>	<i>Method Reference</i>	<i>Method Descriptions</i>
Digestion for Metals and Mercury	EP440 ALS Environmental - Vancouver	Soil/Solid	EPA 200.2 (mod)	Samples are dried, then sieved through a 2 mm sieve, and digested with HNO ₃ and HCl. This method is intended to liberate metals that may be environmentally available.
TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)	EPP444 ALS Environmental - Vancouver	Soil/Solid	EPA 1311	Preparation of a Toxicity Characteristic Leaching Procedure (TCLP) solid sample involves particle size reduction, homogenization, then determination of appropriate extraction fluid. A measured portion of fresh subsample is placed in an extraction bottle with the appropriate extraction fluid then tumbled in a rotary extractor for 18+/- 2 hours at 23 +/- 2 C. The liquid leachate is filtered to separate from solids then bottled and prepared for analytical tests.

QUALITY CONTROL REPORT

Work Order	: VA24B5000	Page	: 1 of 12
Client	: Reworld Renewable Burnaby, ULC	Laboratory	: ALS Environmental - Vancouver
Contact	: Nicole Victor	Account Manager	: Ian Chen
Address	: 5150 Riverbend Drive Burnaby BC Canada V3N 4V3	Address	: 8081 Lougheed Highway Burnaby, British Columbia Canada V5A 1W9
Telephone	: ----	Telephone	: +1 604 253 4188
Project	: Weekly Bottom Ash - Suite	Date Samples Received	: 25-Jun-2024 12:25
PO	: 46693	Date Analysis Commenced	: 26-Jun-2024
C-O-C number	: ----	Issue Date	: 04-Jul-2024 12:32
Sampler	: ----		
Site	: ----		
Quote number	: Covanta Burnaby Standing Offer 2024		
No. of samples received	: 12		
No. of samples analysed	: 12		

This report supersedes any previous report(s) with this reference. Results apply to the sample(s) as submitted. This document shall not be reproduced, except in full.

This Quality Control Report contains the following information:

- Laboratory Duplicate (DUP) Report; Relative Percent Difference (RPD) and Data Quality Objectives
- Matrix Spike (MS) Report; Recovery and Data Quality Objectives
- Reference Material (RM) Report; Recovery and Data Quality Objectives
- Method Blank (MB) Report; Recovery and Data Quality Objectives
- Laboratory Control Sample (LCS) Report; Recovery and Data Quality Objectives

Signatories

This document has been electronically signed by the authorized signatories below. Electronic signing is conducted in accordance with US FDA 21 CFR Part 11.

<i>Signatories</i>	<i>Position</i>	<i>Laboratory Department</i>
Ghazaleh Khanmirzaei	Analyst	Vancouver Metals, Burnaby, British Columbia
Janice Leung	Supervisor - Organics Instrumentation	Vancouver Organics, Burnaby, British Columbia
Robin Weeks	Team Leader - Metals	Vancouver Metals, Burnaby, British Columbia

Page : 2 of 12
Work Order : VA24B5000
Client : Reworld Renewable Burnaby, ULC
Project : Weekly Bottom Ash - Suite



General Comments

The ALS Quality Control (QC) report is optionally provided to ALS clients upon request. ALS test methods include comprehensive QC checks with every analysis to ensure our high standards of quality are met. Each QC result has a known or expected target value, which is compared against predetermined Data Quality Objectives (DQOs) to provide confidence in the accuracy of associated test results. This report contains detailed results for all QC results applicable to this sample submission. Please refer to the ALS Quality Control Interpretation report (QCI) for applicable method references and methodology summaries.

Key :

Anonymous = Refers to samples which are not part of this work order, but which formed part of the QC process lot.

CAS Number = Chemical Abstracts Service number is a unique identifier assigned to discrete substances.

DQO = Data Quality Objective.

LOR = Limit of Reporting (detection limit).

RPD = Relative Percent Difference

= Indicates a QC result that did not meet the ALS DQO.

Workorder Comments

Holding times are displayed as "---" if no guidance exists from CCME, Canadian provinces, or broadly recognized international references.



Laboratory Duplicate (DUP) Report

A Laboratory Duplicate (DUP) is a randomly selected intralaboratory replicate sample. Laboratory Duplicates provide information regarding method precision and sample heterogeneity. ALS DQOs for Laboratory Duplicates are expressed as test-specific limits for Relative Percent Difference (RPD), or as an absolute difference limit of 2 times the LOR for low concentration duplicates within ~ 4-10 times the LOR (cut-off is test-specific).

Sub-Matrix: Soil/Solid

					Laboratory Duplicate (DUP) Report						
Laboratory sample ID	Client sample ID	Analyte	CAS Number	Method	LOR	Unit	Original Result	Duplicate Result	RPD(%) or Difference	Duplicate Limits	Qualifier
Physical Tests (QC Lot: 1515510)											
VA24B4821-008	Anonymous	pH (1:2 soil:water)	----	E108	0.10	pH units	6.34	6.41	1.1%	5%	----
Physical Tests (QC Lot: 1515511)											
VA24B4821-016	Anonymous	Moisture	----	E144	0.25	%	36.3	37.9	4.27%	20%	----
Metals (QC Lot: 1515508)											
VA24B4821-008	Anonymous	Mercury	7439-97-6	E510	0.0050	mg/kg	0.0226 µg/g	0.0192	0.0034	Diff <2x LOR	----
Metals (QC Lot: 1515509)											
VA24B4821-008	Anonymous	Aluminum	7429-90-5	E440	50	mg/kg	11200 µg/g	11300	0.978%	40%	----
		Antimony	7440-36-0	E440	0.10	mg/kg	0.23 µg/g	0.24	0.007	Diff <2x LOR	----
		Arsenic	7440-38-2	E440	0.10	mg/kg	3.08 µg/g	3.40	10.0%	30%	----
		Barium	7440-39-3	E440	0.50	mg/kg	67.6 µg/g	60.0	11.9%	40%	----
		Beryllium	7440-41-7	E440	0.10	mg/kg	0.21 µg/g	0.21	0.004	Diff <2x LOR	----
		Bismuth	7440-69-9	E440	0.20	mg/kg	<0.20	<0.20	0	Diff <2x LOR	----
		Boron	7440-42-8	E440	5.0	mg/kg	<5.0 µg/g	<5.0	0	Diff <2x LOR	----
		Cadmium	7440-43-9	E440	0.020	mg/kg	0.116 µg/g	0.112	0.005	Diff <2x LOR	----
		Calcium	7440-70-2	E440	50	mg/kg	5770	5960	3.32%	30%	----
		Chromium	7440-47-3	E440	0.50	mg/kg	24.3 µg/g	34.8	35.4%	30%	DUP-H
		Cobalt	7440-48-4	E440	0.10	mg/kg	7.00 µg/g	7.26	3.68%	30%	----
		Copper	7440-50-8	E440	0.50	mg/kg	14.0 µg/g	14.2	1.32%	30%	----
		Iron	7439-89-6	E440	50	mg/kg	17000 µg/g	17400	1.86%	30%	----
		Lead	7439-92-1	E440	0.50	mg/kg	3.39 µg/g	3.35	1.07%	40%	----
		Lithium	7439-93-2	E440	2.0	mg/kg	7.9 µg/g	8.5	0.6	Diff <2x LOR	----
		Magnesium	7439-95-4	E440	20	mg/kg	6180	7280	16.4%	30%	----
		Manganese	7439-96-5	E440	1.0	mg/kg	264 µg/g	263	0.129%	30%	----
		Molybdenum	7439-98-7	E440	0.10	mg/kg	0.58 µg/g	0.53	9.26%	40%	----
		Nickel	7440-02-0	E440	0.50	mg/kg	24.8 µg/g	30.3	20.1%	30%	----
		Phosphorus	7723-14-0	E440	50	mg/kg	440	406	8.17%	30%	----
		Potassium	7440-09-7	E440	100	mg/kg	620	570	8.53%	40%	----
		Selenium	7782-49-2	E440	0.20	mg/kg	<0.20 µg/g	<0.20	0	Diff <2x LOR	----
		Silver	7440-22-4	E440	0.10	mg/kg	<0.10 µg/g	<0.10	0	Diff <2x LOR	----
		Sodium	7440-23-5	E440	50	mg/kg	290	282	2.79%	40%	----



Sub-Matrix: Soil/Solid					Laboratory Duplicate (DUP) Report						
Laboratory sample ID	Client sample ID	Analyte	CAS Number	Method	LOR	Unit	Original Result	Duplicate Result	RPD(%) or Difference	Duplicate Limits	Qualifier
Metals (QC Lot: 1515509) - continued											
VA24B4821-008	Anonymous	Strontium	7440-24-6	E440	0.50	mg/kg	23.4 µg/g	22.2	5.41%	40%	----
		Sulfur	7704-34-9	E440	1000	mg/kg	<1000	<1000	0	Diff <2x LOR	----
		Thallium	7440-28-0	E440	0.050	mg/kg	0.054 µg/g	0.052	0.002	Diff <2x LOR	----
		Tin	7440-31-5	E440	2.0	mg/kg	<2.0 µg/g	<2.0	0	Diff <2x LOR	----
		Titanium	7440-32-6	E440	1.0	mg/kg	969 µg/g	948	2.24%	40%	----
		Tungsten	7440-33-7	E440	0.50	mg/kg	<0.50 µg/g	<0.50	0	Diff <2x LOR	----
		Uranium	7440-61-1	E440	0.050	mg/kg	0.250	# 0.353	0.103	Diff <2x LOR	DUP-H
		Vanadium	7440-62-2	E440	0.20	mg/kg	47.7 µg/g	49.4	3.51%	30%	----
		Zinc	7440-66-6	E440	2.0	mg/kg	81.8 µg/g	81.9	0.0398%	30%	----
Zirconium	7440-67-7	E440	1.0	mg/kg	5.0	4.9	0.08	Diff <2x LOR	----		
TCLP Metals (QC Lot: 1525424)											
VA24B5000-001	BA2425-A-1	Mercury, TCLP	7439-97-6	E512	0.0010	mg/L	<0.0010	<0.0010	0	Diff <2x LOR	----
TCLP Metals (QC Lot: 1525425)											
VA24B5000-001	BA2425-A-1	Antimony, TCLP	7440-36-0	E444	1.00	mg/L	<1.00	<1.00	0	Diff <2x LOR	----
		Arsenic, TCLP	7440-38-2	E444	1.0	mg/L	<1.0	<1.0	0	Diff <2x LOR	----
		Barium, TCLP	7440-39-3	E444	2.5	mg/L	<2.5	<2.5	0	Diff <2x LOR	----
		Beryllium, TCLP	7440-41-7	E444	0.025	mg/L	<0.025	<0.025	0	Diff <2x LOR	----
		Boron, TCLP	7440-42-8	E444	0.50	mg/L	1.77	1.84	0.07	Diff <2x LOR	----
		Cadmium, TCLP	7440-43-9	E444	0.050	mg/L	<0.050	<0.050	0	Diff <2x LOR	----
		Calcium, TCLP	7440-70-2	E444	10	mg/L	1570	1620	3.11%	30%	----
		Chromium, TCLP	7440-47-3	E444	0.25	mg/L	<0.25	<0.25	0	Diff <2x LOR	----
		Cobalt, TCLP	7440-48-4	E444	0.050	mg/L	0.120	0.120	0.0003	Diff <2x LOR	----
		Copper, TCLP	7440-50-8	E444	0.050	mg/L	0.921	0.938	1.88%	30%	----
		Iron, TCLP	7439-89-6	E444	5.0	mg/L	<5.0	<5.0	0	Diff <2x LOR	----
		Lead, TCLP	7439-92-1	E444	0.25	mg/L	<0.25	<0.25	0	Diff <2x LOR	----
		Magnesium, TCLP	7439-95-4	E444	2.5	mg/L	81.1	82.8	2.11%	30%	----
		Nickel, TCLP	7440-02-0	E444	0.25	mg/L	<0.25	<0.25	0	Diff <2x LOR	----
		Selenium, TCLP	7782-49-2	E444	0.10	mg/L	<0.10	<0.10	0	Diff <2x LOR	----
		Silver, TCLP	7440-22-4	E444	0.050	mg/L	<0.050	<0.050	0	Diff <2x LOR	----
		Thallium, TCLP	7440-28-0	E444	1.0	mg/L	<1.0	<1.0	0	Diff <2x LOR	----
		Uranium, TCLP	7440-61-1	E444	0.20	mg/L	<0.20	<0.20	0	Diff <2x LOR	----
		Vanadium, TCLP	7440-62-2	E444	0.15	mg/L	<0.15	<0.15	0	Diff <2x LOR	----
		Zinc, TCLP	7440-66-6	E444	0.50	mg/L	<0.50	<0.50	0	Diff <2x LOR	----
Zirconium, TCLP	7440-67-7	E444	10	mg/L	<10	<10	0	Diff <2x LOR	----		



Qualifiers

<i>Qualifier</i>	<i>Description</i>
DUP-H	<i>Duplicate results outside ALS DQO, due to sample heterogeneity.</i>



Method Blank (MB) Report

A Method Blank is an analyte-free matrix that undergoes sample processing identical to that carried out for test samples. Method Blank results are used to monitor and control for potential contamination from the laboratory environment and reagents. For most tests, the DQO for Method Blanks is for the result to be < LOR.

Sub-Matrix: Soil/Solid

Analyte	CAS Number	Method	LOR	Unit	Result	Qualifier
Physical Tests (QCLot: 1515511)						
Moisture	---	E144	0.25	%	<0.25	---
Metals (QCLot: 1515508)						
Mercury	7439-97-6	E510	0.005	mg/kg	<0.0050	---
Metals (QCLot: 1515509)						
Aluminum	7429-90-5	E440	50	mg/kg	<50	---
Antimony	7440-36-0	E440	0.1	mg/kg	<0.10	---
Arsenic	7440-38-2	E440	0.1	mg/kg	<0.10	---
Barium	7440-39-3	E440	0.5	mg/kg	<0.50	---
Beryllium	7440-41-7	E440	0.1	mg/kg	<0.10	---
Bismuth	7440-69-9	E440	0.2	mg/kg	<0.20	---
Boron	7440-42-8	E440	5	mg/kg	<5.0	---
Cadmium	7440-43-9	E440	0.02	mg/kg	<0.020	---
Calcium	7440-70-2	E440	50	mg/kg	<50	---
Chromium	7440-47-3	E440	0.5	mg/kg	<0.50	---
Cobalt	7440-48-4	E440	0.1	mg/kg	<0.10	---
Copper	7440-50-8	E440	0.5	mg/kg	<0.50	---
Iron	7439-89-6	E440	50	mg/kg	<50	---
Lead	7439-92-1	E440	0.5	mg/kg	<0.50	---
Lithium	7439-93-2	E440	2	mg/kg	<2.0	---
Magnesium	7439-95-4	E440	20	mg/kg	<20	---
Manganese	7439-96-5	E440	1	mg/kg	<1.0	---
Molybdenum	7439-98-7	E440	0.1	mg/kg	<0.10	---
Nickel	7440-02-0	E440	0.5	mg/kg	<0.50	---
Phosphorus	7723-14-0	E440	50	mg/kg	<50	---
Potassium	7440-09-7	E440	100	mg/kg	<100	---
Selenium	7782-49-2	E440	0.2	mg/kg	<0.20	---
Silver	7440-22-4	E440	0.1	mg/kg	<0.10	---
Sodium	7440-23-5	E440	50	mg/kg	<50	---
Strontium	7440-24-6	E440	0.5	mg/kg	<0.50	---
Sulfur	7704-34-9	E440	1000	mg/kg	<1000	---
Thallium	7440-28-0	E440	0.05	mg/kg	<0.050	---
Tin	7440-31-5	E440	2	mg/kg	<2.0	---



Sub-Matrix: **Soil/Solid**

Analyte	CAS Number	Method	LOR	Unit	Result	Qualifier
Metals (QCLot: 1515509) - continued						
Titanium	7440-32-6	E440	1	mg/kg	<1.0	----
Tungsten	7440-33-7	E440	0.5	mg/kg	<0.50	----
Uranium	7440-61-1	E440	0.05	mg/kg	<0.050	----
Vanadium	7440-62-2	E440	0.2	mg/kg	<0.20	----
Zinc	7440-66-6	E440	2	mg/kg	<2.0	----
Zirconium	7440-67-7	E440	1	mg/kg	<1.0	----
TCLP Metals (QCLot: 1525424)						
Mercury, TCLP	7439-97-6	E512	0.001	mg/L	<0.0010	----
TCLP Metals (QCLot: 1525425)						
Antimony, TCLP	7440-36-0	E444	0.1	mg/L	<0.10	----
Arsenic, TCLP	7440-38-2	E444	1	mg/L	<1.0	----
Barium, TCLP	7440-39-3	E444	2.5	mg/L	<2.5	----
Beryllium, TCLP	7440-41-7	E444	0.025	mg/L	<0.025	----
Boron, TCLP	7440-42-8	E444	0.5	mg/L	<0.50	----
Cadmium, TCLP	7440-43-9	E444	0.05	mg/L	<0.050	----
Calcium, TCLP	7440-70-2	E444	10	mg/L	<10	----
Chromium, TCLP	7440-47-3	E444	0.25	mg/L	<0.25	----
Cobalt, TCLP	7440-48-4	E444	0.05	mg/L	<0.050	----
Copper, TCLP	7440-50-8	E444	0.05	mg/L	<0.050	----
Iron, TCLP	7439-89-6	E444	5	mg/L	<5.0	----
Lead, TCLP	7439-92-1	E444	0.25	mg/L	<0.25	----
Magnesium, TCLP	7439-95-4	E444	2.5	mg/L	<2.5	----
Nickel, TCLP	7440-02-0	E444	0.25	mg/L	<0.25	----
Selenium, TCLP	7782-49-2	E444	0.1	mg/L	<0.10	----
Silver, TCLP	7440-22-4	E444	0.05	mg/L	<0.050	----
Thallium, TCLP	7440-28-0	E444	1	mg/L	<1.0	----
Uranium, TCLP	7440-61-1	E444	0.2	mg/L	<0.20	----
Vanadium, TCLP	7440-62-2	E444	0.15	mg/L	<0.15	----
Zinc, TCLP	7440-66-6	E444	0.5	mg/L	<0.50	----
Zirconium, TCLP	7440-67-7	E444	10	mg/L	<10	----



Laboratory Control Sample (LCS) Report

A Laboratory Control Sample (LCS) is an analyte-free matrix that has been fortified (spiked) with test analytes at known concentration and processed in an identical manner to test samples. LCS results are expressed as percent recovery, and are used to monitor and control test method accuracy and precision, independent of test sample matrix.

Sub-Matrix: Soil/Solid

					Laboratory Control Sample (LCS) Report				
					Spike	Recovery (%)	Recovery Limits (%)		
Analyte	CAS Number	Method	LOR	Unit	Target Concentration	LCS	Low	High	Qualifier
Physical Tests (QCLot: 1515510)									
pH (1:2 soil:water)	---	E108	---	pH units	6 pH units	99.8	95.0	105	---
Physical Tests (QCLot: 1515511)									
Moisture	---	E144	0.25	%	50 %	100	90.0	110	---
Metals (QCLot: 1515508)									
Mercury	7439-97-6	E510	0.005	mg/kg	0.1 mg/kg	105	80.0	120	---
Metals (QCLot: 1515509)									
Aluminum	7429-90-5	E440	50	mg/kg	200 mg/kg	103	80.0	120	---
Antimony	7440-36-0	E440	0.1	mg/kg	100 mg/kg	97.6	80.0	120	---
Arsenic	7440-38-2	E440	0.1	mg/kg	100 mg/kg	105	80.0	120	---
Barium	7440-39-3	E440	0.5	mg/kg	25 mg/kg	101	80.0	120	---
Beryllium	7440-41-7	E440	0.1	mg/kg	10 mg/kg	102	80.0	120	---
Bismuth	7440-69-9	E440	0.2	mg/kg	100 mg/kg	93.7	80.0	120	---
Boron	7440-42-8	E440	5	mg/kg	100 mg/kg	99.0	80.0	120	---
Cadmium	7440-43-9	E440	0.02	mg/kg	10 mg/kg	100.0	80.0	120	---
Calcium	7440-70-2	E440	50	mg/kg	5000 mg/kg	102	80.0	120	---
Chromium	7440-47-3	E440	0.5	mg/kg	25 mg/kg	98.8	80.0	120	---
Cobalt	7440-48-4	E440	0.1	mg/kg	25 mg/kg	98.3	80.0	120	---
Copper	7440-50-8	E440	0.5	mg/kg	25 mg/kg	98.0	80.0	120	---
Iron	7439-89-6	E440	50	mg/kg	100 mg/kg	98.9	80.0	120	---
Lead	7439-92-1	E440	0.5	mg/kg	50 mg/kg	100	80.0	120	---
Lithium	7439-93-2	E440	2	mg/kg	25 mg/kg	108	80.0	120	---
Magnesium	7439-95-4	E440	20	mg/kg	5000 mg/kg	101	80.0	120	---
Manganese	7439-96-5	E440	1	mg/kg	25 mg/kg	98.3	80.0	120	---
Molybdenum	7439-98-7	E440	0.1	mg/kg	25 mg/kg	102	80.0	120	---
Nickel	7440-02-0	E440	0.5	mg/kg	50 mg/kg	97.2	80.0	120	---
Phosphorus	7723-14-0	E440	50	mg/kg	1000 mg/kg	105	80.0	120	---
Potassium	7440-09-7	E440	100	mg/kg	5000 mg/kg	99.7	80.0	120	---
Selenium	7782-49-2	E440	0.2	mg/kg	100 mg/kg	99.3	80.0	120	---
Silver	7440-22-4	E440	0.1	mg/kg	10 mg/kg	88.9	80.0	120	---
Sodium	7440-23-5	E440	50	mg/kg	5000 mg/kg	104	80.0	120	---
Strontium	7440-24-6	E440	0.5	mg/kg	25 mg/kg	99.7	80.0	120	---
Sulfur	7704-34-9	E440	1000	mg/kg	5000 mg/kg	98.8	80.0	120	---



Sub-Matrix: Soil/Solid

					Laboratory Control Sample (LCS) Report				
					Spike	Recovery (%)	Recovery Limits (%)		
Analyte	CAS Number	Method	LOR	Unit	Target Concentration	LCS	Low	High	Qualifier
Metals (QCLot: 1515509) - continued									
Thallium	7440-28-0	E440	0.05	mg/kg	100 mg/kg	97.1	80.0	120	----
Tin	7440-31-5	E440	2	mg/kg	50 mg/kg	98.1	80.0	120	----
Titanium	7440-32-6	E440	1	mg/kg	25 mg/kg	98.7	80.0	120	----
Tungsten	7440-33-7	E440	0.5	mg/kg	10 mg/kg	100	80.0	120	----
Uranium	7440-61-1	E440	0.05	mg/kg	0.5 mg/kg	99.4	80.0	120	----
Vanadium	7440-62-2	E440	0.2	mg/kg	50 mg/kg	100.0	80.0	120	----
Zinc	7440-66-6	E440	2	mg/kg	50 mg/kg	99.7	80.0	120	----
Zirconium	7440-67-7	E440	1	mg/kg	10 mg/kg	96.0	80.0	120	----



Matrix Spike (MS) Report

A Matrix Spike (MS) is a randomly selected intra-laboratory replicate sample that has been fortified (spiked) with test analytes at known concentration, and processed in an identical manner to test samples. Matrix Spikes provide information regarding analyte recovery and potential matrix effects. MS DQO exceedances due to sample matrix may sometimes be unavoidable; in such cases, test results for the associated sample (or similar samples) may be subject to bias. ND – Recovery not determined, background level >= 1x spike level.

Sub-Matrix: **Soil/Solid**

					Matrix Spike (MS) Report					
					Spike		Recovery (%)	Recovery Limits (%)		
Laboratory sample ID	Client sample ID	Analyte	CAS Number	Method	Concentration	Target	MS	Low	High	Qualifier
TCLP Metals (QCLot: 1525424)										
VA24B5000-001	BA2425-A-1	Mercury, TCLP	7439-97-6	E512	0.0010 mg/L	0.001 mg/L	95.0	50.0	140	----
TCLP Metals (QCLot: 1525425)										
VA24B5000-001	BA2425-A-1	Antimony, TCLP	7440-36-0	E444	5.43 mg/L	5 mg/L	109	50.0	140	----
		Arsenic, TCLP	7440-38-2	E444	5.1 mg/L	5 mg/L	101	50.0	140	----
		Barium, TCLP	7440-39-3	E444	12.4 mg/L	12.5 mg/L	99.1	50.0	140	----
		Beryllium, TCLP	7440-41-7	E444	0.262 mg/L	0.25 mg/L	105	50.0	140	----
		Boron, TCLP	7440-42-8	E444	9.59 mg/L	10 mg/L	95.9	50.0	140	----
		Cadmium, TCLP	7440-43-9	E444	0.243 mg/L	0.25 mg/L	97.1	50.0	140	----
		Calcium, TCLP	7440-70-2	E444	ND mg/L	----	ND	50.0	140	----
		Chromium, TCLP	7440-47-3	E444	1.20 mg/L	1.25 mg/L	96.0	50.0	140	----
		Cobalt, TCLP	7440-48-4	E444	0.231 mg/L	0.25 mg/L	92.6	50.0	140	----
		Copper, TCLP	7440-50-8	E444	2.26 mg/L	2.5 mg/L	90.5	50.0	140	----
		Iron, TCLP	7439-89-6	E444	236 mg/L	250 mg/L	94.5	50.0	140	----
		Lead, TCLP	7439-92-1	E444	9.91 mg/L	10 mg/L	99.1	50.0	140	----
		Magnesium, TCLP	7439-95-4	E444	246 mg/L	250 mg/L	98.3	50.0	140	----
		Nickel, TCLP	7440-02-0	E444	2.34 mg/L	2.5 mg/L	93.5	50.0	140	----
		Selenium, TCLP	7782-49-2	E444	4.86 mg/L	5 mg/L	97.2	50.0	140	----
		Silver, TCLP	7440-22-4	E444	0.097 mg/L	0.1 mg/L	97.1	50.0	140	----
		Thallium, TCLP	7440-28-0	E444	5.1 mg/L	5 mg/L	103	50.0	140	----
		Uranium, TCLP	7440-61-1	E444	4.87 mg/L	5 mg/L	97.4	50.0	150	----
		Vanadium, TCLP	7440-62-2	E444	0.72 mg/L	0.75 mg/L	96.7	50.0	140	----
		Zinc, TCLP	7440-66-6	E444	9.90 mg/L	10 mg/L	99.0	50.0	140	----
		Zirconium, TCLP	7440-67-7	E444	0.8 mg/L	1 mg/L	84.1	50.0	150	----



Reference Material (RM) Report

A Reference Material (RM) is a homogenous material with known and well-established analyte concentrations. RMs are processed in an identical manner to test samples, and are used to monitor and control the accuracy and precision of a test method for a typical sample matrix. RM results are expressed as percent recovery of the target analyte concentration. RM targets may be certified target concentrations provided by the RM supplier, or may be ALS long-term mean values (for empirical test methods).

Sub-Matrix:

Laboratory sample ID	Reference Material ID	Analyte	CAS Number	Method	Reference Material (RM) Report				
					RM Target Concentration	Recovery (%) RM	Recovery Limits (%)		Qualifier
							Low	High	
Metals (QCLot: 1515508)									
QC-1515508-003	MRCA-21	Mercury	7439-97-6	E510	0.068 mg/kg	101	70.0	130	----
Metals (QCLot: 1515509)									
QC-1515509-003	MRCA-21	Aluminum	7429-90-5	E440	22500 mg/kg	111	70.0	130	----
QC-1515509-003	MRCA-21	Antimony	7440-36-0	E440	24.8 mg/kg	97.8	70.0	130	----
QC-1515509-003	MRCA-21	Arsenic	7440-38-2	E440	21.2 mg/kg	102	70.0	130	----
QC-1515509-003	MRCA-21	Barium	7440-39-3	E440	788 mg/kg	101	70.0	130	----
QC-1515509-003	MRCA-21	Beryllium	7440-41-7	E440	1.82 mg/kg	112	70.0	130	----
QC-1515509-003	MRCA-21	Bismuth	7440-69-9	E440	1.78 mg/kg	95.2	70.0	130	----
QC-1515509-003	MRCA-21	Cadmium	7440-43-9	E440	2.15 mg/kg	103	70.0	130	----
QC-1515509-003	MRCA-21	Calcium	7440-70-2	E440	4900 mg/kg	107	70.0	130	----
QC-1515509-003	MRCA-21	Chromium	7440-47-3	E440	56.9 mg/kg	101	70.0	130	----
QC-1515509-003	MRCA-21	Cobalt	7440-48-4	E440	32 mg/kg	100	70.0	130	----
QC-1515509-003	MRCA-21	Copper	7440-50-8	E440	969 mg/kg	101	70.0	130	----
QC-1515509-003	MRCA-21	Iron	7439-89-6	E440	32700 mg/kg	102	70.0	130	----
QC-1515509-003	MRCA-21	Lead	7439-92-1	E440	919 mg/kg	100	70.0	130	----
QC-1515509-003	MRCA-21	Lithium	7439-93-2	E440	47.3 mg/kg	114	70.0	130	----
QC-1515509-003	MRCA-21	Magnesium	7439-95-4	E440	7780 mg/kg	103	70.0	130	----
QC-1515509-003	MRCA-21	Manganese	7439-96-5	E440	8640 mg/kg	98.6	70.0	130	----
QC-1515509-003	MRCA-21	Molybdenum	7439-98-7	E440	25.1 mg/kg	95.6	70.0	130	----
QC-1515509-003	MRCA-21	Nickel	7440-02-0	E440	1000 mg/kg	102	70.0	130	----
QC-1515509-003	MRCA-21	Phosphorus	7723-14-0	E440	660 mg/kg	100	70.0	130	----
QC-1515509-003	MRCA-21	Potassium	7440-09-7	E440	10800 mg/kg	99.2	70.0	130	----
QC-1515509-003	MRCA-21	Selenium	7782-49-2	E440	1.04 mg/kg	112	60.0	140	----
QC-1515509-003	MRCA-21	Silver	7440-22-4	E440	8.98 mg/kg	95.5	70.0	130	----
QC-1515509-003	MRCA-21	Sodium	7440-23-5	E440	1770 mg/kg	120	70.0	130	----
QC-1515509-003	MRCA-21	Strontium	7440-24-6	E440	41 mg/kg	96.3	70.0	130	----
QC-1515509-003	MRCA-21	Sulfur	7704-34-9	E440	3940 mg/kg	94.8	50.0	150	----
QC-1515509-003	MRCA-21	Thallium	7440-28-0	E440	0.907 mg/kg	102	70.0	130	----
QC-1515509-003	MRCA-21	Tin	7440-31-5	E440	3.79 mg/kg	94.1	40.0	160	----
QC-1515509-003	MRCA-21	Titanium	7440-32-6	E440	2790 mg/kg	104	70.0	130	----
QC-1515509-003	MRCA-21	Tungsten	7440-33-7	E440	6.99 mg/kg	122	70.0	130	----
QC-1515509-003	MRCA-21	Uranium	7440-61-1	E440	3.97 mg/kg	94.8	70.0	130	----
QC-1515509-003	MRCA-21	Vanadium	7440-62-2	E440	66.2 mg/kg	99.4	70.0	130	----

Page : 12 of 12
 Work Order : VA24B5000
 Client : Reworld Renewable Burnaby, ULC
 Project : Weekly Bottom Ash - Suite



Sub-Matrix:

Laboratory sample ID	Reference Material ID	Analyte	CAS Number	Method	Reference Material (RM) Report				
					RM Target Concentration	Recovery (%) RM	Recovery Limits (%)		Qualifier
							Low	High	
Metals (QCLot: 1515509) - continued									
QC-1515509-003	MRCA-21	Zinc	7440-66-6	E440	828 mg/kg	102	70.0	130	----
QC-1515509-003	MRCA-21	Zirconium	7440-67-7	E440	6.91 mg/kg	112	70.0	130	----

