

Bottom Ash Data

2023 Week 6

The following analytical report represents bottom ash composite results for week 6 of 2023 (February 5, 2023 to February 11, 2023).

The bottom ash meets the conditions of Metro Vancouver's 2020 Bottom Ash Management Plan and is suitable for disposal.



CERTIFICATE OF ANALYSIS

Work Order	: VA23A3361	Page	: 1 of 11
Client	: Covanta Burnaby Renewable Energy, ULC	Laboratory	: Vancouver - Environmental
Contact	: Nicole Victor	Account Manager	: Brent Mack
Address	: 5150 Riverbend Drive Burnaby BC Canada V3N 4V3	Address	: 8081 Lougheed Highway Burnaby BC Canada V5A 1W9
Telephone	: ----	Telephone	: 778-370-3279
Project	: Weekly Bottom Ash - Suite	Date Samples Received	: 14-Feb-2023 14:00
PO	: VANCO0000051998	Date Analysis Commenced	: 17-Feb-2023
C-O-C number	: ----	Issue Date	: 23-Feb-2023 13:37
Sampler	: ----		
Site	: ----		
Quote number	: Standing Offer (BC work)		
No. of samples received	: 12		
No. of samples analysed	: 12		

This report supersedes any previous report(s) with this reference. Results apply to the sample(s) as submitted. This document shall not be reproduced, except in full.

This Certificate of Analysis contains the following information:

- General Comments
- Analytical Results

Additional information pertinent to this report will be found in the following separate attachments: Quality Control Report, QC Interpretive report to assist with Quality Review and Sample Receipt Notification (SRN).

Signatories

This document has been electronically signed by the authorized signatories below. Electronic signing is conducted in accordance with US FDA 21 CFR Part 11.

<i>Signatories</i>	<i>Position</i>	<i>Laboratory Department</i>
Alex Thornton	Analyst	Metals, Burnaby, British Columbia
Brianna Allen	Production/Validation Manager	Organics, Burnaby, British Columbia
Kevin Duarte	Supervisor - Metals ICP Instrumentation	Metals, Burnaby, British Columbia



General Comments

The analytical methods used by ALS are developed using internationally recognized reference methods (where available), such as those published by US EPA, APHA Standard Methods, ASTM, ISO, Environment Canada, BC MOE, and Ontario MOE. Refer to the ALS Quality Control Interpretive report (QCI) for applicable references and methodology summaries. Reference methods may incorporate modifications to improve performance.

Where a reported less than (<) result is higher than the LOR, this may be due to primary sample extract/digestate dilution and/or insufficient sample for analysis.

Where the LOR of a reported result differs from standard LOR, this may be due to high moisture content, insufficient sample (reduced weight employed) or matrix interference.

Please refer to Quality Control Interpretive report (QCI) for information regarding Holding Time compliance.

Key : CAS Number: Chemical Abstracts Services number is a unique identifier assigned to discrete substances
LOR: Limit of Reporting (detection limit).

<i>Unit</i>	<i>Description</i>
%	percent
mg/kg	milligrams per kilogram
mg/L	milligrams per litre
pH units	pH units

<: less than.

>: greater than.

Surrogate: An analyte that is similar in behavior to target analyte(s), but that does not occur naturally in environmental samples. For applicable tests, surrogates are added to samples prior to analysis as a check on recovery.

Test results reported relate only to the samples as received by the laboratory.

UNLESS OTHERWISE STATED on SRN or QCI Report, ALL SAMPLES WERE RECEIVED IN ACCEPTABLE CONDITION.



Analytical Results

Sub-Matrix: Soil					Client sample ID	BA2306-A-1	BA2306-A-2	BA2306-A-3	BA2306-A-4	BA2306-A-5
(Matrix: Soil/Solid)					Client sampling date / time	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00
Analyte	CAS Number	Method	LOR	Unit	VA23A3361-001	VA23A3361-002	VA23A3361-003	VA23A3361-004	VA23A3361-005	
					Result	Result	Result	Result	Result	
Physical Tests										
Moisture	----	E144	0.25	%	20.1	20.6	20.9	22.9	23.5	
pH (1:2 soil:water)	----	E108	0.10	pH units	12.0	11.8	12.0	12.0	11.8	
Metals										
Aluminum	7429-90-5	E440	50	mg/kg	58600	52400	48100	48000	43300	
Antimony	7440-36-0	E440	0.10	mg/kg	128	116	145	126	129	
Arsenic	7440-38-2	E440	0.10	mg/kg	19.7	18.5	19.4	19.2	20.6	
Barium	7440-39-3	E440	0.50	mg/kg	644	690	620	779	727	
Beryllium	7440-41-7	E440	0.10	mg/kg	0.45	0.57	0.42	0.44	0.44	
Bismuth	7440-69-9	E440	0.20	mg/kg	9.57	16.2	11.7	10.9	14.3	
Boron	7440-42-8	E440	5.0	mg/kg	390	222	228	404	384	
Cadmium	7440-43-9	E440	0.020	mg/kg	12.3	8.48	7.45	7.61	8.16	
Calcium	7440-70-2	E440	50	mg/kg	185000	175000	175000	165000	180000	
Chromium	7440-47-3	E440	0.50	mg/kg	160	117	145	180	123	
Cobalt	7440-48-4	E440	0.10	mg/kg	58.1	30.5	63.0	33.0	35.7	
Copper	7440-50-8	E440	0.50	mg/kg	1290	1730	1840	1450	2730	
Iron	7439-89-6	E440	50	mg/kg	45800	38200	58700	44700	33300	
Lead	7439-92-1	E440	0.50	mg/kg	470	432	484	719	380	
Lithium	7439-93-2	E440	2.0	mg/kg	22.8	29.3	23.3	25.9	20.4	
Magnesium	7439-95-4	E440	20	mg/kg	11000	10800	10400	11400	11900	
Manganese	7439-96-5	E440	1.0	mg/kg	841	797	717	984	705	
Mercury	7439-97-6	E510	0.0500	mg/kg	<0.0500	<0.0500	<0.0500	<0.0500	<0.0500	
Molybdenum	7439-98-7	E440	0.10	mg/kg	196	14.2	18.2	17.0	14.1	
Nickel	7440-02-0	E440	0.50	mg/kg	107	176	77.4	558	156	
Phosphorus	7723-14-0	E440	50	mg/kg	13900	11600	8600	12900	14000	
Potassium	7440-09-7	E440	100	mg/kg	4890	4500	4860	5490	5300	
Selenium	7782-49-2	E440	0.20	mg/kg	0.37	0.67	0.44	0.41	0.43	
Silver	7440-22-4	E440	0.10	mg/kg	3.91	3.60	16.1	12.9	4.32	
Sodium	7440-23-5	E440	50	mg/kg	15000	14600	15300	17600	16100	
Strontium	7440-24-6	E440	0.50	mg/kg	298	286	294	324	317	



Analytical Results

Sub-Matrix: Soil					Client sample ID	BA2306-A-1	BA2306-A-2	BA2306-A-3	BA2306-A-4	BA2306-A-5
(Matrix: Soil/Solid)					Client sampling date / time	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00
Analyte	CAS Number	Method	LOR	Unit	VA23A3361-001	VA23A3361-002	VA23A3361-003	VA23A3361-004	VA23A3361-005	
					Result	Result	Result	Result	Result	
Metals										
Sulfur	7704-34-9	E440	1000	mg/kg	8900	7400	8400	8300	9400	
Thallium	7440-28-0	E440	0.050	mg/kg	<0.050	<0.050	<0.050	<0.050	<0.050	
Tin	7440-31-5	E440	2.0	mg/kg	120	132	239	197	148	
Titanium	7440-32-6	E440	1.0	mg/kg	572	348	424	259	269	
Tungsten	7440-33-7	E440	0.50	mg/kg	4.84	6.84	5.48	8.74	5.52	
Uranium	7440-61-1	E440	0.050	mg/kg	4.02	4.13	4.10	4.21	3.98	
Vanadium	7440-62-2	E440	0.20	mg/kg	40.6	44.2	48.1	43.0	41.0	
Zinc	7440-66-6	E440	2.0	mg/kg	2760	3260	3150	2960	3050	
Zirconium	7440-67-7	E440	1.0	mg/kg	4.5	3.6	2.7	3.1	2.5	
TCLP Metals										
pH, TCLP 1st preliminary	----	EPP444	0.010	pH units	11.9	11.9	12.0	11.8	11.9	
pH, TCLP 2nd preliminary	----	EPP444	0.010	pH units	8.51	8.45	8.61	6.57	8.55	
pH, TCLP extraction fluid initial	----	EPP444	0.010	pH units	2.87	2.87	2.87	2.87	2.87	
pH, TCLP final	----	EPP444	0.010	pH units	7.01	7.25	7.40	7.18	7.18	
Antimony, TCLP	7440-36-0	E444	1.00	mg/L	<1.00	<1.00	<1.00	<1.00	<1.00	
Arsenic, TCLP	7440-38-2	E444	1.0	mg/L	<1.0	<1.0	<1.0	<1.0	<1.0	
Barium, TCLP	7440-39-3	E444	2.5	mg/L	<2.5	<2.5	<2.5	<2.5	<2.5	
Beryllium, TCLP	7440-41-7	E444	0.025	mg/L	<0.025	<0.025	<0.025	<0.025	<0.025	
Boron, TCLP	7440-42-8	E444	0.50	mg/L	2.20	2.49	2.33	2.20	2.14	
Cadmium, TCLP	7440-43-9	E444	0.050	mg/L	0.058	0.052	0.054	0.054	<0.050	
Calcium, TCLP	7440-70-2	E444	10	mg/L	2040	2280	2070	2120	2120	
Chromium, TCLP	7440-47-3	E444	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25	
Cobalt, TCLP	7440-48-4	E444	0.050	mg/L	0.605	1.03	0.920	0.853	0.740	
Copper, TCLP	7440-50-8	E444	0.050	mg/L	0.394	0.502	0.340	0.444	0.492	
Iron, TCLP	7439-89-6	E444	5.0	mg/L	<5.0	<5.0	<5.0	<5.0	<5.0	
Lead, TCLP	7439-92-1	E444	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25	
Magnesium, TCLP	7439-95-4	E444	2.5	mg/L	112	124	118	119	116	
Mercury, TCLP	7439-97-6	E512	0.0010	mg/L	<0.0010	<0.0010	<0.0010	<0.0010	<0.0010	
Nickel, TCLP	7440-02-0	E444	0.25	mg/L	0.42	0.35	0.32	0.33	0.39	
Selenium, TCLP	7782-49-2	E444	0.10	mg/L	<0.10	<0.10	<0.10	<0.10	<0.10	



Analytical Results

Sub-Matrix: Soil (Matrix: Soil/Solid)					Client sample ID	BA2306-A-1	BA2306-A-2	BA2306-A-3	BA2306-A-4	BA2306-A-5
Client sampling date / time					08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00
Analyte	CAS Number	Method	LOR	Unit	VA23A3361-001	VA23A3361-002	VA23A3361-003	VA23A3361-004	VA23A3361-005	
					Result	Result	Result	Result	Result	
TCLP Metals										
Silver, TCLP	7440-22-4	E444	0.050	mg/L	<0.050	<0.050	<0.050	<0.050	<0.050	<0.050
Thallium, TCLP	7440-28-0	E444	1.0	mg/L	<1.0	<1.0	<1.0	<1.0	<1.0	<1.0
Uranium, TCLP	7440-61-1	E444	0.20	mg/L	<0.20	<0.20	<0.20	<0.20	<0.20	<0.20
Vanadium, TCLP	7440-62-2	E444	0.15	mg/L	<0.15	<0.15	<0.15	<0.15	<0.15	<0.15
Zinc, TCLP	7440-66-6	E444	0.50	mg/L	7.17	2.44	1.37	3.33	3.31	3.31
Zirconium, TCLP	7440-67-7	E444	10	mg/L	<10	<10	<10	<10	<10	<10

Please refer to the General Comments section for an explanation of any qualifiers detected.



Analytical Results

Sub-Matrix: Soil					Client sample ID	BA2306-A-6	BA2306-A-7	BA2306-A-8	BA2306-A-9	BA2306-A-10
(Matrix: Soil/Solid)					Client sampling date / time	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00
Analyte	CAS Number	Method	LOR	Unit	VA23A3361-006	VA23A3361-007	VA23A3361-008	VA23A3361-009	VA23A3361-010	
					Result	Result	Result	Result	Result	
Physical Tests										
Moisture	----	E144	0.25	%	23.0	21.3	19.8	21.4	23.4	
pH (1:2 soil:water)	----	E108	0.10	pH units	12.0	11.9	11.9	12.0	11.9	
Metals										
Aluminum	7429-90-5	E440	50	mg/kg	45800	38100	51400	42300	42800	
Antimony	7440-36-0	E440	0.10	mg/kg	142	148	123	136	126	
Arsenic	7440-38-2	E440	0.10	mg/kg	44.8	20.6	19.0	21.5	24.3	
Barium	7440-39-3	E440	0.50	mg/kg	871	864	780	601	704	
Beryllium	7440-41-7	E440	0.10	mg/kg	0.46	0.42	0.47	0.43	0.39	
Bismuth	7440-69-9	E440	0.20	mg/kg	11.2	12.5	12.7	9.94	9.23	
Boron	7440-42-8	E440	5.0	mg/kg	334	289	241	260	294	
Cadmium	7440-43-9	E440	0.020	mg/kg	8.10	9.50	8.42	7.41	7.03	
Calcium	7440-70-2	E440	50	mg/kg	183000	166000	168000	166000	176000	
Chromium	7440-47-3	E440	0.50	mg/kg	145	113	152	134	270	
Cobalt	7440-48-4	E440	0.10	mg/kg	83.7	60.6	275	57.7	77.7	
Copper	7440-50-8	E440	0.50	mg/kg	1700	1300	1180	1220	1510	
Iron	7439-89-6	E440	50	mg/kg	48400	32400	28300	47600	43400	
Lead	7439-92-1	E440	0.50	mg/kg	484	1260	1180	436	674	
Lithium	7439-93-2	E440	2.0	mg/kg	22.8	27.7	38.6	31.7	20.9	
Magnesium	7439-95-4	E440	20	mg/kg	13000	11100	11000	12700	11600	
Manganese	7439-96-5	E440	1.0	mg/kg	1020	727	927	831	1070	
Mercury	7439-97-6	E510	0.0500	mg/kg	<0.0500	0.0647	<0.0500	<0.0500	<0.0500	
Molybdenum	7439-98-7	E440	0.10	mg/kg	18.9	14.0	15.3	15.1	33.5	
Nickel	7440-02-0	E440	0.50	mg/kg	146	102	91.3	120	131	
Phosphorus	7723-14-0	E440	50	mg/kg	15800	10800	9280	12300	12200	
Potassium	7440-09-7	E440	100	mg/kg	5000	4600	4810	4860	4730	
Selenium	7782-49-2	E440	0.20	mg/kg	0.44	0.38	0.42	0.40	0.34	
Silver	7440-22-4	E440	0.10	mg/kg	3.78	3.08	3.85	3.72	3.58	
Sodium	7440-23-5	E440	50	mg/kg	17400	15100	16500	15200	15400	
Strontium	7440-24-6	E440	0.50	mg/kg	357	295	315	314	284	
Sulfur	7704-34-9	E440	1000	mg/kg	9000	8800	9000	9700	7400	



Analytical Results

Sub-Matrix: Soil					Client sample ID	BA2306-A-6	BA2306-A-7	BA2306-A-8	BA2306-A-9	BA2306-A-10
(Matrix: Soil/Solid)					Client sampling date / time	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00
Analyte	CAS Number	Method	LOR	Unit	VA23A3361-006	VA23A3361-007	VA23A3361-008	VA23A3361-009	VA23A3361-010	
					Result	Result	Result	Result	Result	
Metals										
Thallium	7440-28-0	E440	0.050	mg/kg	<0.050	<0.050	0.094	<0.050	<0.050	
Tin	7440-31-5	E440	2.0	mg/kg	150	202	190	125	415	
Titanium	7440-32-6	E440	1.0	mg/kg	279	371	682	227	297	
Tungsten	7440-33-7	E440	0.50	mg/kg	5.49	6.72	7.62	4.82	4.13	
Uranium	7440-61-1	E440	0.050	mg/kg	4.71	4.42	4.17	4.35	4.31	
Vanadium	7440-62-2	E440	0.20	mg/kg	47.2	40.7	47.9	40.9	42.9	
Zinc	7440-66-6	E440	2.0	mg/kg	5240	4490	5770	8140	3210	
Zirconium	7440-67-7	E440	1.0	mg/kg	5.9	1.8	2.2	3.6	4.2	
TCLP Metals										
pH, TCLP 1st preliminary	----	EPP444	0.010	pH units	12.0	12.0	12.0	12.0	12.0	
pH, TCLP 2nd preliminary	----	EPP444	0.010	pH units	9.03	8.74	8.31	10.5	8.68	
pH, TCLP extraction fluid initial	----	EPP444	0.010	pH units	2.87	2.87	2.87	2.87	2.87	
pH, TCLP final	----	EPP444	0.010	pH units	7.11	7.43	7.24	7.26	7.24	
Antimony, TCLP	7440-36-0	E444	1.00	mg/L	<1.00	<1.00	<1.00	<1.00	<1.00	
Arsenic, TCLP	7440-38-2	E444	1.0	mg/L	<1.0	<1.0	<1.0	<1.0	<1.0	
Barium, TCLP	7440-39-3	E444	2.5	mg/L	<2.5	<2.5	<2.5	<2.5	<2.5	
Beryllium, TCLP	7440-41-7	E444	0.025	mg/L	<0.025	<0.025	<0.025	<0.025	<0.025	
Boron, TCLP	7440-42-8	E444	0.50	mg/L	2.08	2.17	2.20	2.58	2.10	
Cadmium, TCLP	7440-43-9	E444	0.050	mg/L	0.060	<0.050	0.066	0.051	<0.050	
Calcium, TCLP	7440-70-2	E444	10	mg/L	2040	2050	2160	2250	2040	
Chromium, TCLP	7440-47-3	E444	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25	
Cobalt, TCLP	7440-48-4	E444	0.050	mg/L	0.718	0.526	0.558	0.540	0.449	
Copper, TCLP	7440-50-8	E444	0.050	mg/L	0.489	0.470	0.522	0.500	0.353	
Iron, TCLP	7439-89-6	E444	5.0	mg/L	<5.0	<5.0	<5.0	<5.0	<5.0	
Lead, TCLP	7439-92-1	E444	0.25	mg/L	<0.25	<0.25	<0.25	<0.25	<0.25	
Magnesium, TCLP	7439-95-4	E444	2.5	mg/L	113	118	117	125	114	
Mercury, TCLP	7439-97-6	E512	0.0010	mg/L	<0.0010	<0.0010	<0.0010	<0.0010	<0.0010	
Nickel, TCLP	7440-02-0	E444	0.25	mg/L	0.34	0.30	0.39	0.36	0.37	
Selenium, TCLP	7782-49-2	E444	0.10	mg/L	<0.10	<0.10	<0.10	<0.10	<0.10	
Silver, TCLP	7440-22-4	E444	0.050	mg/L	<0.050	<0.050	<0.050	<0.050	<0.050	



Analytical Results

Sub-Matrix: Soil					Client sample ID	BA2306-A-6	BA2306-A-7	BA2306-A-8	BA2306-A-9	BA2306-A-10
(Matrix: Soil/Solid)					Client sampling date / time	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00	08-Feb-2023 09:00
Analyte	CAS Number	Method	LOR	Unit	VA23A3361-006	VA23A3361-007	VA23A3361-008	VA23A3361-009	VA23A3361-010	
TCLP Metals					Result	Result	Result	Result	Result	
Thallium, TCLP	7440-28-0	E444	1.0	mg/L	<1.0	<1.0	<1.0	<1.0	<1.0	
Uranium, TCLP	7440-61-1	E444	0.20	mg/L	<0.20	<0.20	<0.20	<0.20	<0.20	
Vanadium, TCLP	7440-62-2	E444	0.15	mg/L	<0.15	<0.15	<0.15	<0.15	<0.15	
Zinc, TCLP	7440-66-6	E444	0.50	mg/L	8.18	1.05	3.32	3.65	3.38	
Zirconium, TCLP	7440-67-7	E444	10	mg/L	<10	<10	<10	<10	<10	

Please refer to the General Comments section for an explanation of any qualifiers detected.



Analytical Results

Sub-Matrix: Soil					Client sample ID	BA2306-A-11	BA2306-A-12	----	----	----
(Matrix: Soil/Solid)					Client sampling date / time	08-Feb-2023 09:00	08-Feb-2023 09:00	----	----	----
Analyte	CAS Number	Method	LOR	Unit	VA23A3361-011	VA23A3361-012	-----	-----	-----	
					Result	Result	----	----	----	
Physical Tests										
Moisture	----	E144	0.25	%	21.0	21.9	----	----	----	
pH (1:2 soil:water)	----	E108	0.10	pH units	12.0	12.0	----	----	----	
Metals										
Aluminum	7429-90-5	E440	50	mg/kg	49800	39300	----	----	----	
Antimony	7440-36-0	E440	0.10	mg/kg	110	142	----	----	----	
Arsenic	7440-38-2	E440	0.10	mg/kg	17.2	23.8	----	----	----	
Barium	7440-39-3	E440	0.50	mg/kg	706	608	----	----	----	
Beryllium	7440-41-7	E440	0.10	mg/kg	0.40	0.41	----	----	----	
Bismuth	7440-69-9	E440	0.20	mg/kg	9.23	14.0	----	----	----	
Boron	7440-42-8	E440	5.0	mg/kg	418	218	----	----	----	
Cadmium	7440-43-9	E440	0.020	mg/kg	7.15	9.48	----	----	----	
Calcium	7440-70-2	E440	50	mg/kg	159000	177000	----	----	----	
Chromium	7440-47-3	E440	0.50	mg/kg	180	149	----	----	----	
Cobalt	7440-48-4	E440	0.10	mg/kg	35.2	336	----	----	----	
Copper	7440-50-8	E440	0.50	mg/kg	3120	1690	----	----	----	
Iron	7439-89-6	E440	50	mg/kg	59700	43000	----	----	----	
Lead	7439-92-1	E440	0.50	mg/kg	446	426	----	----	----	
Lithium	7439-93-2	E440	2.0	mg/kg	68.4	80.3	----	----	----	
Magnesium	7439-95-4	E440	20	mg/kg	10400	10400	----	----	----	
Manganese	7439-96-5	E440	1.0	mg/kg	849	1790	----	----	----	
Mercury	7439-97-6	E510	0.0500	mg/kg	<0.0500	<0.0500	----	----	----	
Molybdenum	7439-98-7	E440	0.10	mg/kg	20.8	16.3	----	----	----	
Nickel	7440-02-0	E440	0.50	mg/kg	94.5	311	----	----	----	
Phosphorus	7723-14-0	E440	50	mg/kg	10600	12000	----	----	----	
Potassium	7440-09-7	E440	100	mg/kg	4440	5240	----	----	----	
Selenium	7782-49-2	E440	0.20	mg/kg	0.39	0.44	----	----	----	
Silver	7440-22-4	E440	0.10	mg/kg	4.53	5.47	----	----	----	
Sodium	7440-23-5	E440	50	mg/kg	15800	14700	----	----	----	
Strontium	7440-24-6	E440	0.50	mg/kg	303	291	----	----	----	
Sulfur	7704-34-9	E440	1000	mg/kg	8300	8800	----	----	----	



Analytical Results

Sub-Matrix: Soil					Client sample ID	BA2306-A-11	BA2306-A-12	----	----	----
(Matrix: Soil/Solid)					Client sampling date / time	08-Feb-2023 09:00	08-Feb-2023 09:00	----	----	----
Analyte	CAS Number	Method	LOR	Unit	VA23A3361-011	VA23A3361-012	-----	-----	-----	
					Result	Result	----	----	----	
Metals										
Thallium	7440-28-0	E440	0.050	mg/kg	<0.050	<0.050	----	----	----	
Tin	7440-31-5	E440	2.0	mg/kg	236	153	----	----	----	
Titanium	7440-32-6	E440	1.0	mg/kg	396	269	----	----	----	
Tungsten	7440-33-7	E440	0.50	mg/kg	5.97	6.03	----	----	----	
Uranium	7440-61-1	E440	0.050	mg/kg	4.07	4.33	----	----	----	
Vanadium	7440-62-2	E440	0.20	mg/kg	39.3	43.6	----	----	----	
Zinc	7440-66-6	E440	2.0	mg/kg	4140	3610	----	----	----	
Zirconium	7440-67-7	E440	1.0	mg/kg	3.9	3.2	----	----	----	
TCLP Metals										
pH, TCLP 1st preliminary	----	EPP444	0.010	pH units	12.0	12.0	----	----	----	
pH, TCLP 2nd preliminary	----	EPP444	0.010	pH units	8.76	8.90	----	----	----	
pH, TCLP extraction fluid initial	----	EPP444	0.010	pH units	2.87	2.87	----	----	----	
pH, TCLP final	----	EPP444	0.010	pH units	7.32	7.41	----	----	----	
Antimony, TCLP	7440-36-0	E444	1.00	mg/L	<1.00	<1.00	----	----	----	
Arsenic, TCLP	7440-38-2	E444	1.0	mg/L	<1.0	<1.0	----	----	----	
Barium, TCLP	7440-39-3	E444	2.5	mg/L	<2.5	<2.5	----	----	----	
Beryllium, TCLP	7440-41-7	E444	0.025	mg/L	<0.025	<0.025	----	----	----	
Boron, TCLP	7440-42-8	E444	0.50	mg/L	2.21	2.34	----	----	----	
Cadmium, TCLP	7440-43-9	E444	0.050	mg/L	<0.050	0.052	----	----	----	
Calcium, TCLP	7440-70-2	E444	10	mg/L	2080	2230	----	----	----	
Chromium, TCLP	7440-47-3	E444	0.25	mg/L	<0.25	<0.25	----	----	----	
Cobalt, TCLP	7440-48-4	E444	0.050	mg/L	0.443	0.545	----	----	----	
Copper, TCLP	7440-50-8	E444	0.050	mg/L	0.401	0.442	----	----	----	
Iron, TCLP	7439-89-6	E444	5.0	mg/L	<5.0	<5.0	----	----	----	
Lead, TCLP	7439-92-1	E444	0.25	mg/L	<0.25	<0.25	----	----	----	
Magnesium, TCLP	7439-95-4	E444	2.5	mg/L	115	122	----	----	----	
Mercury, TCLP	7439-97-6	E512	0.0010	mg/L	<0.0010	<0.0010	----	----	----	
Nickel, TCLP	7440-02-0	E444	0.25	mg/L	0.36	0.31	----	----	----	
Selenium, TCLP	7782-49-2	E444	0.10	mg/L	<0.10	<0.10	----	----	----	
Silver, TCLP	7440-22-4	E444	0.050	mg/L	<0.050	<0.050	----	----	----	



Analytical Results

Sub-Matrix: Soil					Client sample ID		BA2306-A-11	BA2306-A-12	----	----	----
(Matrix: Soil/Solid)					Client sampling date / time		08-Feb-2023 09:00	08-Feb-2023 09:00	----	----	----
Analyte	CAS Number	Method	LOR	Unit	VA23A3361-011	VA23A3361-012	-----	-----	-----	-----	-----
TCLP Metals					Result	Result	---	---	---	---	---
Thallium, TCLP	7440-28-0	E444	1.0	mg/L	<1.0	<1.0	----	----	----	----	----
Uranium, TCLP	7440-61-1	E444	0.20	mg/L	<0.20	<0.20	----	----	----	----	----
Vanadium, TCLP	7440-62-2	E444	0.15	mg/L	<0.15	<0.15	----	----	----	----	----
Zinc, TCLP	7440-66-6	E444	0.50	mg/L	1.56	1.48	----	----	----	----	----
Zirconium, TCLP	7440-67-7	E444	10	mg/L	<10	<10	----	----	----	----	----

Please refer to the General Comments section for an explanation of any qualifiers detected.



QUALITY CONTROL INTERPRETIVE REPORT

<p>Work Order : VA23A3361</p> <p>Client : Covanta Burnaby Renewable Energy, ULC</p> <p>Contact : Nicole Victor</p> <p>Address : 5150 Riverbend Drive Burnaby BC Canada V3N 4V3</p> <p>Telephone : ----</p> <p>Project : Weekly Bottom Ash - Suite</p> <p>PO : VANCO0000051998</p> <p>C-O-C number : ----</p> <p>Sampler : ----</p> <p>Site : ----</p> <p>Quote number : Standing Offer (BC work)</p> <p>No. of samples received : 12</p> <p>No. of samples analysed : 12</p>	<p>Page : 1 of 16</p> <p>Laboratory : Vancouver - Environmental</p> <p>Account Manager : Brent Mack</p> <p>Address : 8081 Lougheed Highway Burnaby, British Columbia Canada V5A 1W9</p> <p>Telephone : 778-370-3279</p> <p>Date Samples Received : 14-Feb-2023 14:00</p> <p>Issue Date : 23-Feb-2023 13:37</p>
---	---

This report is automatically generated by the ALS LIMS (Laboratory Information Management System) through evaluation of Quality Control (QC) results and other QA parameters associated with this submission, and is intended to facilitate rapid data validation by auditors or reviewers. The report highlights any exceptions and outliers to ALS Data Quality Objectives, provides holding time details and exceptions, summarizes QC sample frequencies, and lists applicable methodology references and summaries.

Key

- Anonymous: Refers to samples which are not part of this work order, but which formed part of the QC process lot.
- CAS Number: Chemical Abstracts Service number is a unique identifier assigned to discrete substances.
- DQO: Data Quality Objective.
- LOR: Limit of Reporting (detection limit).
- RPD: Relative Percent Difference.

Workorder Comments

Holding times are displayed as "----" if no guidance exists from CCME, Canadian provinces, or broadly recognized international references.

Summary of Outliers

Outliers : Quality Control Samples

- No Method Blank value outliers occur.
- No Laboratory Control Sample (LCS) outliers occur
- No Matrix Spike outliers occur.
- Duplicate outliers occur - please see following pages for full details.
- No Test sample Surrogate recovery outliers exist.

Outliers: Reference Material (RM) Samples

- No Reference Material (RM) Sample outliers occur.

Outliers : Analysis Holding Time Compliance (Breaches)

- No Analysis Holding Time Outliers exist.

Outliers : Frequency of Quality Control Samples

- No Quality Control Sample Frequency Outliers occur.



Outliers : Quality Control Samples

Duplicates, Method Blanks, Laboratory Control Samples and Matrix Spikes

Matrix: **Soil/Solid**

Analyte Group	Laboratory sample ID	Client/Ref Sample ID	Analyte	CAS Number	Method	Result	Limits	Comment
Duplicate (DUP) RPDs								
Metals	VA23A3361-001	BA2306-A-1	Cobalt	7440-48-4	E440	130 % DUP-H	30%	Duplicate RPD does not meet the DQO for this test.
Metals	VA23A3361-001	BA2306-A-1	Copper	7440-50-8	E440	52.7 % DUP-H	30%	Duplicate RPD does not meet the DQO for this test.
Metals	VA23A3361-001	BA2306-A-1	Molybdenum	7439-98-7	E440	172 % DUP-H	40%	Duplicate RPD does not meet the DQO for this test.
Metals	VA23A3361-001	BA2306-A-1	Nickel	7440-02-0	E440	68.6 % DUP-H	30%	Duplicate RPD does not meet the DQO for this test.
Metals	VA23A3361-001	BA2306-A-1	Phosphorus	7723-14-0	E440	39.3 % DUP-H	30%	Duplicate RPD does not meet the DQO for this test.
Metals	VA23A3361-001	BA2306-A-1	Silver	7440-22-4	E440	136 % DUP-H	40%	Duplicate RPD does not meet the DQO for this test.
Metals	VA23A3361-001	BA2306-A-1	Zinc	7440-66-6	E440	30.8 % DUP-H	30%	Duplicate RPD does not meet the DQO for this test.

Result Qualifiers

Qualifier	Description
DUP-H	Duplicate results outside ALS DQO, due to sample heterogeneity.



Analysis Holding Time Compliance

This report summarizes extraction / preparation and analysis times and compares each with ALS recommended holding times, which are selected to meet known provincial and /or federal requirements. In the absence of regulatory hold times, ALS establishes recommendations based on guidelines published by organizations such as CCME, US EPA, APHA Standard Methods, ASTM, or Environment Canada (where available). Dates and holding times reported below represent the first dates of extraction or analysis. If subsequent tests or dilutions exceeded holding times, qualifiers are added (refer to COA).

If samples are identified below as having been analyzed or extracted outside of recommended holding times, measurement uncertainties may be increased, and this should be taken into consideration when interpreting results.

Where actual sampling date is not provided on the chain of custody, the date of receipt with time at 00:00 is used for calculation purposes.

Where only the sample date without time is provided on the chain of custody, the sampling date at 00:00 is used for calculation purposes.

Matrix: Soil/Solid

Evaluation: * = Holding time exceedance ; ✓ = Within Holding Time

Analyte Group Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
Metals : Mercury in Soil/Solid by CVAAS										
LDPE bag BA2306-A-1	E510	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	28 days	14 days	✓
Metals : Mercury in Soil/Solid by CVAAS										
LDPE bag BA2306-A-10	E510	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	28 days	14 days	✓
Metals : Mercury in Soil/Solid by CVAAS										
LDPE bag BA2306-A-11	E510	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	28 days	14 days	✓
Metals : Mercury in Soil/Solid by CVAAS										
LDPE bag BA2306-A-12	E510	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	28 days	14 days	✓
Metals : Mercury in Soil/Solid by CVAAS										
LDPE bag BA2306-A-2	E510	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	28 days	14 days	✓
Metals : Mercury in Soil/Solid by CVAAS										
LDPE bag BA2306-A-3	E510	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	28 days	14 days	✓
Metals : Mercury in Soil/Solid by CVAAS										
LDPE bag BA2306-A-4	E510	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	28 days	14 days	✓



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2306-A-5	E510	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	28 days	14 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2306-A-6	E510	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	28 days	14 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2306-A-7	E510	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	28 days	14 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2306-A-8	E510	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	28 days	14 days	✔	
Metals : Mercury in Soil/Solid by CVAAS											
LDPE bag BA2306-A-9	E510	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	28 days	14 days	✔	
Metals : Metals in Soil/Solid by CRC ICNMS											
LDPE bag BA2306-A-1	E440	08-Feb-2023	22-Feb-2023	----	----		23-Feb-2023	180 days	15 days	✔	
Metals : Metals in Soil/Solid by CRC ICNMS											
LDPE bag BA2306-A-10	E440	08-Feb-2023	22-Feb-2023	----	----		23-Feb-2023	180 days	15 days	✔	
Metals : Metals in Soil/Solid by CRC ICNMS											
LDPE bag BA2306-A-11	E440	08-Feb-2023	22-Feb-2023	----	----		23-Feb-2023	180 days	15 days	✔	
Metals : Metals in Soil/Solid by CRC ICNMS											
LDPE bag BA2306-A-12	E440	08-Feb-2023	22-Feb-2023	----	----		23-Feb-2023	180 days	15 days	✔	



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
Metals : Metals in Soil/Solid by CRC ICMS											
LDPE bag BA2306-A-2	E440	08-Feb-2023	22-Feb-2023	----	----		23-Feb-2023	180 days	15 days	✔	
Metals : Metals in Soil/Solid by CRC ICMS											
LDPE bag BA2306-A-3	E440	08-Feb-2023	22-Feb-2023	----	----		23-Feb-2023	180 days	15 days	✔	
Metals : Metals in Soil/Solid by CRC ICMS											
LDPE bag BA2306-A-4	E440	08-Feb-2023	22-Feb-2023	----	----		23-Feb-2023	180 days	15 days	✔	
Metals : Metals in Soil/Solid by CRC ICMS											
LDPE bag BA2306-A-5	E440	08-Feb-2023	22-Feb-2023	----	----		23-Feb-2023	180 days	15 days	✔	
Metals : Metals in Soil/Solid by CRC ICMS											
LDPE bag BA2306-A-6	E440	08-Feb-2023	22-Feb-2023	----	----		23-Feb-2023	180 days	15 days	✔	
Metals : Metals in Soil/Solid by CRC ICMS											
LDPE bag BA2306-A-7	E440	08-Feb-2023	22-Feb-2023	----	----		23-Feb-2023	180 days	15 days	✔	
Metals : Metals in Soil/Solid by CRC ICMS											
LDPE bag BA2306-A-8	E440	08-Feb-2023	22-Feb-2023	----	----		23-Feb-2023	180 days	15 days	✔	
Metals : Metals in Soil/Solid by CRC ICMS											
LDPE bag BA2306-A-9	E440	08-Feb-2023	22-Feb-2023	----	----		23-Feb-2023	180 days	15 days	✔	
Physical Tests : Moisture Content by Gravimetry											
LDPE bag BA2306-A-1	E144	08-Feb-2023	----	----	----		19-Feb-2023	----	----		



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2306-A-10	E144	08-Feb-2023	----	----	----		19-Feb-2023	----	----	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2306-A-11	E144	08-Feb-2023	----	----	----		19-Feb-2023	----	----	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2306-A-12	E144	08-Feb-2023	----	----	----		19-Feb-2023	----	----	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2306-A-2	E144	08-Feb-2023	----	----	----		19-Feb-2023	----	----	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2306-A-3	E144	08-Feb-2023	----	----	----		19-Feb-2023	----	----	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2306-A-4	E144	08-Feb-2023	----	----	----		19-Feb-2023	----	----	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2306-A-5	E144	08-Feb-2023	----	----	----		19-Feb-2023	----	----	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2306-A-6	E144	08-Feb-2023	----	----	----		19-Feb-2023	----	----	
Physical Tests : Moisture Content by Gravimetry										
LDPE bag BA2306-A-7	E144	08-Feb-2023	----	----	----		19-Feb-2023	----	----	



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
Physical Tests : Moisture Content by Gravimetry											
LDPE bag BA2306-A-8	E144	08-Feb-2023	----	----	----		19-Feb-2023	----	----		
Physical Tests : Moisture Content by Gravimetry											
LDPE bag BA2306-A-9	E144	08-Feb-2023	----	----	----		19-Feb-2023	----	----		
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2306-A-1	E108	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	30 days	14 days		✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2306-A-10	E108	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	30 days	14 days		✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2306-A-11	E108	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	30 days	14 days		✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2306-A-12	E108	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	30 days	14 days		✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2306-A-2	E108	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	30 days	14 days		✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2306-A-3	E108	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	30 days	14 days		✔
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2306-A-4	E108	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	30 days	14 days		✔



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2306-A-5	E108	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	30 days	14 days	✔	
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2306-A-6	E108	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	30 days	14 days	✔	
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2306-A-7	E108	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	30 days	14 days	✔	
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2306-A-8	E108	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	30 days	14 days	✔	
Physical Tests : pH by Meter (1:2 Soil:Water Extraction)											
LDPE bag BA2306-A-9	E108	08-Feb-2023	22-Feb-2023	----	----		22-Feb-2023	30 days	14 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2306-A-1	E512	17-Feb-2023	19-Feb-2023	----	----		19-Feb-2023	28 days	11 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2306-A-10	E512	17-Feb-2023	19-Feb-2023	----	----		19-Feb-2023	28 days	11 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2306-A-11	E512	17-Feb-2023	19-Feb-2023	----	----		19-Feb-2023	28 days	11 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2306-A-12	E512	17-Feb-2023	19-Feb-2023	----	----		19-Feb-2023	28 days	11 days	✔	



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2306-A-2	E512	17-Feb-2023	19-Feb-2023	----	----		19-Feb-2023	28 days	11 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2306-A-3	E512	17-Feb-2023	19-Feb-2023	----	----		19-Feb-2023	28 days	11 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2306-A-4	E512	17-Feb-2023	19-Feb-2023	----	----		19-Feb-2023	28 days	11 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2306-A-5	E512	17-Feb-2023	19-Feb-2023	----	----		19-Feb-2023	28 days	11 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2306-A-6	E512	17-Feb-2023	19-Feb-2023	----	----		19-Feb-2023	28 days	11 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2306-A-7	E512	17-Feb-2023	19-Feb-2023	----	----		19-Feb-2023	28 days	11 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2306-A-8	E512	17-Feb-2023	19-Feb-2023	----	----		19-Feb-2023	28 days	11 days	✔	
TCLP Metals : Mercury by CVAAS (TCLP)											
Glass vial - total (lab preserved) BA2306-A-9	E512	17-Feb-2023	19-Feb-2023	----	----		19-Feb-2023	28 days	11 days	✔	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2306-A-1	E444	17-Feb-2023	19-Feb-2023	----	----		21-Feb-2023	180 days	13 days	✔	



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis				
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval	
				Rec	Actual			Rec	Actual		
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2306-A-10	E444	17-Feb-2023	19-Feb-2023	----	----		21-Feb-2023	180 days	13 days	✔	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2306-A-11	E444	17-Feb-2023	19-Feb-2023	----	----		21-Feb-2023	180 days	13 days	✔	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2306-A-12	E444	17-Feb-2023	19-Feb-2023	----	----		21-Feb-2023	180 days	13 days	✔	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2306-A-2	E444	17-Feb-2023	19-Feb-2023	----	----		21-Feb-2023	180 days	13 days	✔	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2306-A-3	E444	17-Feb-2023	19-Feb-2023	----	----		21-Feb-2023	180 days	13 days	✔	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2306-A-4	E444	17-Feb-2023	19-Feb-2023	----	----		21-Feb-2023	180 days	13 days	✔	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2306-A-5	E444	17-Feb-2023	19-Feb-2023	----	----		21-Feb-2023	180 days	13 days	✔	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2306-A-6	E444	17-Feb-2023	19-Feb-2023	----	----		21-Feb-2023	180 days	13 days	✔	
TCLP Metals : Metals by CRC ICPMS (TCLP)											
HDPE - total (lab preserved) BA2306-A-7	E444	17-Feb-2023	19-Feb-2023	----	----		21-Feb-2023	180 days	13 days	✔	



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
TCLP Metals : Metals by CRC ICPMS (TCLP)										
HDPE - total (lab preserved) BA2306-A-8	E444	17-Feb-2023	19-Feb-2023	----	----		21-Feb-2023	180 days	13 days	✔
TCLP Metals : Metals by CRC ICPMS (TCLP)										
HDPE - total (lab preserved) BA2306-A-9	E444	17-Feb-2023	19-Feb-2023	----	----		21-Feb-2023	180 days	13 days	✔
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2306-A-1	EPP444	08-Feb-2023	17-Feb-2023	----	----		----	----	----	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2306-A-10	EPP444	08-Feb-2023	17-Feb-2023	----	----		----	----	----	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2306-A-11	EPP444	08-Feb-2023	17-Feb-2023	----	----		----	----	----	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2306-A-12	EPP444	08-Feb-2023	17-Feb-2023	----	----		----	----	----	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2306-A-2	EPP444	08-Feb-2023	17-Feb-2023	----	----		----	----	----	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2306-A-3	EPP444	08-Feb-2023	17-Feb-2023	----	----		----	----	----	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2306-A-4	EPP444	08-Feb-2023	17-Feb-2023	----	----		----	----	----	



Matrix: Soil/Solid

Evaluation: ✖ = Holding time exceedance ; ✔ = Within Holding Time

Analyte Group Container / Client Sample ID(s)	Method	Sampling Date	Extraction / Preparation				Analysis			
			Preparation Date	Holding Times		Eval	Analysis Date	Holding Times		Eval
				Rec	Actual			Rec	Actual	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2306-A-5	EPP444	08-Feb-2023	17-Feb-2023	----	----		----	----	----	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2306-A-6	EPP444	08-Feb-2023	17-Feb-2023	----	----		----	----	----	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2306-A-7	EPP444	08-Feb-2023	17-Feb-2023	----	----		----	----	----	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2306-A-8	EPP444	08-Feb-2023	17-Feb-2023	----	----		----	----	----	
TCLP Metals : TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)										
Lab Split - Non-Volatile Leach: 28 day HT (e.g. Hg, CrVI, PFAS) BA2306-A-9	EPP444	08-Feb-2023	17-Feb-2023	----	----		----	----	----	

Legend & Qualifier Definitions

Rec. HT: ALS recommended hold time (see units).



Quality Control Parameter Frequency Compliance

The following report summarizes the frequency of laboratory QC samples analyzed within the analytical batches (QC lots) in which the submitted samples were processed. The actual frequency should be greater than or equal to the expected frequency.

Matrix: **Soil/Solid**

Evaluation: ✖ = QC frequency outside specification; ✔ = QC frequency within specification.

Quality Control Sample Type	Method	QC Lot #	Count		Frequency (%)		
			QC	Regular	Actual	Expected	Evaluation
Analytical Methods							
Laboratory Duplicates (DUP)							
Mercury in Soil/Solid by CVAAS	E510	839859	1	12	8.3	5.0	✔
Metals in Soil/Solid by CRC ICPMS	E440	839860	1	12	8.3	5.0	✔
Moisture Content by Gravimetry	E144	839862	1	12	8.3	5.0	✔
pH by Meter (1:2 Soil:Water Extraction)	E108	839861	1	12	8.3	5.0	✔
Laboratory Control Samples (LCS)							
Mercury in Soil/Solid by CVAAS	E510	839859	2	12	16.6	10.0	✔
Metals in Soil/Solid by CRC ICPMS	E440	839860	2	12	16.6	10.0	✔
Moisture Content by Gravimetry	E144	839862	1	12	8.3	5.0	✔
pH by Meter (1:2 Soil:Water Extraction)	E108	839861	1	12	8.3	5.0	✔
Method Blanks (MB)							
Mercury by CVAAS (TCLP)	E512	839770	1	12	8.3	5.0	✔
Mercury in Soil/Solid by CVAAS	E510	839859	1	12	8.3	5.0	✔
Metals by CRC ICPMS (TCLP)	E444	839771	1	12	8.3	5.0	✔
Metals in Soil/Solid by CRC ICPMS	E440	839860	1	12	8.3	5.0	✔
Moisture Content by Gravimetry	E144	839862	1	12	8.3	5.0	✔
Matrix Spikes (MS)							
Mercury by CVAAS (TCLP)	E512	839770	1	12	8.3	5.0	✔
Metals by CRC ICPMS (TCLP)	E444	839771	1	12	8.3	5.0	✔



Methodology References and Summaries

The analytical methods used by ALS are developed using internationally recognized reference methods (where available), such as those published by US EPA, APHA Standard Methods, ASTM, ISO, Environment Canada, BC MOE, and Ontario MOE. Reference methods may incorporate modifications to improve performance (indicated by "mod").

Analytical Methods	Method / Lab	Matrix	Method Reference	Method Descriptions
pH by Meter (1:2 Soil:Water Extraction)	E108 Vancouver - Environmental	Soil/Solid	BC Lab Manual	pH is determined by potentiometric measurement with a pH electrode at ambient laboratory temperature (normally $20 \pm 5^{\circ}\text{C}$), and is carried out in accordance with procedures described in the BC Lab Manual (prescriptive method). The procedure involves mixing the dried (at $<60^{\circ}\text{C}$) and sieved (10mesh/2mm) sample with ultra pure water at a 1:2 ratio of sediment to water. The pH is then measured by a standard pH probe.
Moisture Content by Gravimetry	E144 Vancouver - Environmental	Soil/Solid	CCME PHC in Soil - Tier 1	Moisture is measured gravimetrically by drying the sample at 105°C . Moisture content is calculated as the weight loss (due to water) divided by the wet weight of the sample, expressed as a percentage.
Metals in Soil/Solid by CRC ICPMS	E440 Vancouver - Environmental	Soil/Solid	EPA 6020B (mod)	This method is intended to liberate metals that may be environmentally available. Samples are dried, then sieved through a 2 mm sieve, and digested with HNO_3 and HCl . Dependent on sample matrix, some metals may be only partially recovered, including Al, Ba, Be, Cr, Sr, Ti, Tl, V, W, and Zr. Silicate minerals are not solubilized. Volatile forms of sulfur (including sulfide) may not be captured, as they may be lost during sampling, storage, or digestion. This method does not adequately recover elemental sulfur, and is unsuitable for assessment of elemental sulfur standards or guidelines. Analysis is by Collision/Reaction Cell ICPMS.
Metals by CRC ICPMS (TCLP)	E444 Vancouver - Environmental	Soil/Solid	EPA 1311/6020B (mod)	An extract produced by the Toxicity Characteristic Leachate Procedure (TCLP) as per EPA 1311 is analyzed by Collision/Reaction Cell ICPMS.
Mercury in Soil/Solid by CVAAS	E510 Vancouver - Environmental	Soil/Solid	EPA 200.2/1631 Appendix (mod)	Samples are dried, then sieved through a 2 mm sieve, and digested with HNO_3 and HCl , followed by CVAAS analysis.
Mercury by CVAAS (TCLP)	E512 Vancouver - Environmental	Soil/Solid	SW 846 -1311/245.1 CVAA ON TCLP LEACHATE	An extract produced by the Toxicity Characteristic Leachate Procedure (TCLP) as per EPA 1311 is analyzed by CVAAS.
Preparation Methods	Method / Lab	Matrix	Method Reference	Method Descriptions
Leach 1:2 Soil:Water for pH/EC	EP108 Vancouver - Environmental	Soil/Solid	BC WLAP METHOD: PH, ELECTROMETRIC, SOIL	The procedure involves mixing the dried (at $<60^{\circ}\text{C}$) and sieved (No. 10 / 2mm) sample with deionized/distilled water at a 1:2 ratio of sediment to water.



<i>Preparation Methods</i>	<i>Method / Lab</i>	<i>Matrix</i>	<i>Method Reference</i>	<i>Method Descriptions</i>
Digestion for Metals and Mercury	EP440 Vancouver - Environmental	Soil/Solid	EPA 200.2 (mod)	Samples are dried, then sieved through a 2 mm sieve, and digested with HNO ₃ and HCl. This method is intended to liberate metals that may be environmentally available.
TCLP Leachate Preparation (Metals, Inorganics, and SVOCs)	EPP444 Vancouver - Environmental	Soil/Solid	EPA 1311	Preparation of a Toxicity Characteristic Leaching Procedure (TCLP) solid sample involves particle size reduction, homogenization, then determination of appropriate extraction fluid. A measured portion of fresh subsample is placed in an extraction bottle with the appropriate extraction fluid then tumbled in a rotary extractor for 18+/- 2 hours at 23 +/- 2 C. The liquid leachate is filtered to separate from solids then bottled and prepared for analytical tests.

QUALITY CONTROL REPORT

Work Order	: VA23A3361	Page	: 1 of 11
Client	: Covanta Burnaby Renewable Energy, ULC	Laboratory	: Vancouver - Environmental
Contact	: Nicole Victor	Account Manager	: Brent Mack
Address	: 5150 Riverbend Drive Burnaby BC Canada V3N 4V3	Address	: 8081 Lougheed Highway Burnaby, British Columbia Canada V5A 1W9
Telephone	:	Telephone	: 778-370-3279
Project	: Weekly Bottom Ash - Suite	Date Samples Received	: 14-Feb-2023 14:00
PO	: VANCO0000051998	Date Analysis Commenced	: 17-Feb-2023
C-O-C number	: ----	Issue Date	: 23-Feb-2023 13:39
Sampler	: ---- ----		
Site	: ----		
Quote number	: Standing Offer (BC work)		
No. of samples received	: 12		
No. of samples analysed	: 12		

This report supersedes any previous report(s) with this reference. Results apply to the sample(s) as submitted. This document shall not be reproduced, except in full.

This Quality Control Report contains the following information:

- Laboratory Duplicate (DUP) Report; Relative Percent Difference (RPD) and Data Quality Objectives
- Matrix Spike (MS) Report; Recovery and Data Quality Objectives
- Reference Material (RM) Report; Recovery and Data Quality Objectives
- Method Blank (MB) Report; Recovery and Data Quality Objectives
- Laboratory Control Sample (LCS) Report; Recovery and Data Quality Objectives

Signatories

This document has been electronically signed by the authorized signatories below. Electronic signing is conducted in accordance with US FDA 21 CFR Part 11.

<i>Signatories</i>	<i>Position</i>	<i>Laboratory Department</i>
Alex Thornton	Analyst	Vancouver Metals, Burnaby, British Columbia
Brianna Allen	Production/Validation Manager	Vancouver Organics, Burnaby, British Columbia
Kevin Duarte	Supervisor - Metals ICP Instrumentation	Vancouver Metals, Burnaby, British Columbia



General Comments

The ALS Quality Control (QC) report is optionally provided to ALS clients upon request. ALS test methods include comprehensive QC checks with every analysis to ensure our high standards of quality are met. Each QC result has a known or expected target value, which is compared against predetermined Data Quality Objectives (DQOs) to provide confidence in the accuracy of associated test results. This report contains detailed results for all QC results applicable to this sample submission. Please refer to the ALS Quality Control Interpretation report (QCI) for applicable method references and methodology summaries.

Key :

Anonymous = Refers to samples which are not part of this work order, but which formed part of the QC process lot.

CAS Number = Chemical Abstracts Service number is a unique identifier assigned to discrete substances.

DQO = Data Quality Objective.

LOR = Limit of Reporting (detection limit).

RPD = Relative Percent Difference

= Indicates a QC result that did not meet the ALS DQO.

Workorder Comments

Holding times are displayed as "---" if no guidance exists from CCME, Canadian provinces, or broadly recognized international references.



Laboratory Duplicate (DUP) Report

A Laboratory Duplicate (DUP) is a randomly selected intralaboratory replicate sample. Laboratory Duplicates provide information regarding method precision and sample heterogeneity. ALS DQOs for Laboratory Duplicates are expressed as test-specific limits for Relative Percent Difference (RPD), or as an absolute difference limit of 2 times the LOR for low concentration duplicates within ~ 4-10 times the LOR (cut-off is test-specific).

Sub-Matrix: Soil/Solid

					Laboratory Duplicate (DUP) Report						
Laboratory sample ID	Client sample ID	Analyte	CAS Number	Method	LOR	Unit	Original Result	Duplicate Result	RPD(%) or Difference	Duplicate Limits	Qualifier
Physical Tests (QC Lot: 839861)											
VA23A3361-001	BA2306-A-1	pH (1:2 soil:water)	----	E108	0.10	pH units	12.0	11.9	0.8%	5%	----
Physical Tests (QC Lot: 839862)											
VA23A3361-001	BA2306-A-1	Moisture	----	E144	0.25	%	20.1	21.4	6.42%	20%	----
Metals (QC Lot: 839859)											
VA23A3361-001	BA2306-A-1	Mercury	7439-97-6	E510	0.0500	mg/kg	<0.0500	<0.0500	0	Diff <2x LOR	----
Metals (QC Lot: 839860)											
VA23A3361-001	BA2306-A-1	Aluminum	7429-90-5	E440	50	mg/kg	58600	52600	10.8%	40%	----
		Antimony	7440-36-0	E440	0.10	mg/kg	128	132	3.36%	30%	----
		Arsenic	7440-38-2	E440	0.10	mg/kg	19.7	22.1	11.3%	30%	----
		Barium	7440-39-3	E440	0.50	mg/kg	644	638	0.981%	40%	----
		Beryllium	7440-41-7	E440	0.10	mg/kg	0.45	0.50	0.05	Diff <2x LOR	----
		Bismuth	7440-69-9	E440	0.20	mg/kg	9.57	10.6	10.7%	30%	----
		Boron	7440-42-8	E440	5.0	mg/kg	390	355	9.51%	30%	----
		Cadmium	7440-43-9	E440	0.020	mg/kg	12.3	9.85	22.0%	30%	----
		Calcium	7440-70-2	E440	50	mg/kg	185000	164000	11.7%	30%	----
		Chromium	7440-47-3	E440	0.50	mg/kg	160	171	6.46%	30%	----
		Cobalt	7440-48-4	E440	0.10	mg/kg	58.1	274	130%	30%	DUP-H
		Copper	7440-50-8	E440	0.50	mg/kg	1290	2210	52.7%	30%	DUP-H
		Iron	7439-89-6	E440	50	mg/kg	45800	53600	15.7%	30%	----
		Lead	7439-92-1	E440	0.50	mg/kg	470	404	15.0%	40%	----
		Lithium	7439-93-2	E440	2.0	mg/kg	22.8	28.8	23.2%	30%	----
		Magnesium	7439-95-4	E440	20	mg/kg	11000	11500	4.15%	30%	----
		Manganese	7439-96-5	E440	1.0	mg/kg	841	967	13.9%	30%	----
		Molybdenum	7439-98-7	E440	0.10	mg/kg	196	14.5	172%	40%	DUP-H
		Nickel	7440-02-0	E440	0.50	mg/kg	107	218	68.6%	30%	DUP-H
		Phosphorus	7723-14-0	E440	50	mg/kg	13900	9350	39.3%	30%	DUP-H
		Potassium	7440-09-7	E440	100	mg/kg	4890	4940	1.03%	40%	----
		Selenium	7782-49-2	E440	0.20	mg/kg	0.37	0.40	0.03	Diff <2x LOR	----
		Silver	7440-22-4	E440	0.10	mg/kg	3.91	20.6	136%	40%	DUP-H
		Sodium	7440-23-5	E440	50	mg/kg	15000	15900	5.47%	40%	----



Sub-Matrix: Soil/Solid					Laboratory Duplicate (DUP) Report						
Laboratory sample ID	Client sample ID	Analyte	CAS Number	Method	LOR	Unit	Original Result	Duplicate Result	RPD(%) or Difference	Duplicate Limits	Qualifier
Metals (QC Lot: 839860) - continued											
VA23A3361-001	BA2306-A-1	Strontium	7440-24-6	E440	0.50	mg/kg	298	294	1.15%	40%	----
		Sulfur	7704-34-9	E440	1000	mg/kg	8900	9200	3.42%	30%	----
		Thallium	7440-28-0	E440	0.050	mg/kg	<0.050	<0.050	0	Diff <2x LOR	----
		Tin	7440-31-5	E440	2.0	mg/kg	120	157	26.8%	40%	----
		Titanium	7440-32-6	E440	1.0	mg/kg	572	530	7.50%	40%	----
		Tungsten	7440-33-7	E440	0.50	mg/kg	4.84	3.85	22.7%	30%	----
		Uranium	7440-61-1	E440	0.050	mg/kg	4.02	4.11	2.13%	30%	----
		Vanadium	7440-62-2	E440	0.20	mg/kg	40.6	45.1	10.5%	30%	----
		Zinc	7440-66-6	E440	2.0	mg/kg	2760	3770	30.8%	30%	DUP-H
		Zirconium	7440-67-7	E440	1.0	mg/kg	4.5	2.5	1.9	Diff <2x LOR	----

Qualifiers

Qualifier	Description
DUP-H	Duplicate results outside ALS DQO, due to sample heterogeneity.



Method Blank (MB) Report

A Method Blank is an analyte-free matrix that undergoes sample processing identical to that carried out for test samples. Method Blank results are used to monitor and control for potential contamination from the laboratory environment and reagents. For most tests, the DQO for Method Blanks is for the result to be < LOR.

Sub-Matrix: Soil/Solid

Analyte	CAS Number	Method	LOR	Unit	Result	Qualifier
Physical Tests (QCLot: 839862)						
Moisture	---	E144	0.25	%	<0.25	---
Metals (QCLot: 839859)						
Mercury	7439-97-6	E510	0.005	mg/kg	<0.0050	---
Metals (QCLot: 839860)						
Aluminum	7429-90-5	E440	50	mg/kg	<50	---
Antimony	7440-36-0	E440	0.1	mg/kg	<0.10	---
Arsenic	7440-38-2	E440	0.1	mg/kg	<0.10	---
Barium	7440-39-3	E440	0.5	mg/kg	<0.50	---
Beryllium	7440-41-7	E440	0.1	mg/kg	<0.10	---
Bismuth	7440-69-9	E440	0.2	mg/kg	<0.20	---
Boron	7440-42-8	E440	5	mg/kg	<5.0	---
Cadmium	7440-43-9	E440	0.02	mg/kg	<0.020	---
Calcium	7440-70-2	E440	50	mg/kg	<50	---
Chromium	7440-47-3	E440	0.5	mg/kg	<0.50	---
Cobalt	7440-48-4	E440	0.1	mg/kg	<0.10	---
Copper	7440-50-8	E440	0.5	mg/kg	<0.50	---
Iron	7439-89-6	E440	50	mg/kg	<50	---
Lead	7439-92-1	E440	0.5	mg/kg	<0.50	---
Lithium	7439-93-2	E440	2	mg/kg	<2.0	---
Magnesium	7439-95-4	E440	20	mg/kg	<20	---
Manganese	7439-96-5	E440	1	mg/kg	<1.0	---
Molybdenum	7439-98-7	E440	0.1	mg/kg	<0.10	---
Nickel	7440-02-0	E440	0.5	mg/kg	<0.50	---
Phosphorus	7723-14-0	E440	50	mg/kg	<50	---
Potassium	7440-09-7	E440	100	mg/kg	<100	---
Selenium	7782-49-2	E440	0.2	mg/kg	<0.20	---
Silver	7440-22-4	E440	0.1	mg/kg	<0.10	---
Sodium	7440-23-5	E440	50	mg/kg	<50	---
Strontium	7440-24-6	E440	0.5	mg/kg	<0.50	---
Sulfur	7704-34-9	E440	1000	mg/kg	<1000	---
Thallium	7440-28-0	E440	0.05	mg/kg	<0.050	---
Tin	7440-31-5	E440	2	mg/kg	<2.0	---



Sub-Matrix: **Soil/Solid**

Analyte	CAS Number	Method	LOR	Unit	Result	Qualifier
Metals (QCLot: 839860) - continued						
Titanium	7440-32-6	E440	1	mg/kg	<1.0	----
Tungsten	7440-33-7	E440	0.5	mg/kg	<0.50	----
Uranium	7440-61-1	E440	0.05	mg/kg	<0.050	----
Vanadium	7440-62-2	E440	0.2	mg/kg	<0.20	----
Zinc	7440-66-6	E440	2	mg/kg	<2.0	----
Zirconium	7440-67-7	E440	1	mg/kg	<1.0	----
TCLP Metals (QCLot: 839770)						
Mercury, TCLP	7439-97-6	E512	0.001	mg/L	<0.0010	----
TCLP Metals (QCLot: 839771)						
Antimony, TCLP	7440-36-0	E444	0.1	mg/L	<0.10	----
Arsenic, TCLP	7440-38-2	E444	1	mg/L	<1.0	----
Barium, TCLP	7440-39-3	E444	2.5	mg/L	<2.5	----
Beryllium, TCLP	7440-41-7	E444	0.025	mg/L	<0.025	----
Boron, TCLP	7440-42-8	E444	0.5	mg/L	<0.50	----
Cadmium, TCLP	7440-43-9	E444	0.05	mg/L	<0.050	----
Calcium, TCLP	7440-70-2	E444	10	mg/L	<10	----
Chromium, TCLP	7440-47-3	E444	0.25	mg/L	<0.25	----
Cobalt, TCLP	7440-48-4	E444	0.05	mg/L	<0.050	----
Copper, TCLP	7440-50-8	E444	0.05	mg/L	<0.050	----
Iron, TCLP	7439-89-6	E444	5	mg/L	<5.0	----
Lead, TCLP	7439-92-1	E444	0.25	mg/L	<0.25	----
Magnesium, TCLP	7439-95-4	E444	2.5	mg/L	<2.5	----
Nickel, TCLP	7440-02-0	E444	0.25	mg/L	<0.25	----
Selenium, TCLP	7782-49-2	E444	0.1	mg/L	<0.10	----
Silver, TCLP	7440-22-4	E444	0.05	mg/L	<0.050	----
Thallium, TCLP	7440-28-0	E444	1	mg/L	<1.0	----
Uranium, TCLP	7440-61-1	E444	0.2	mg/L	<0.20	----
Vanadium, TCLP	7440-62-2	E444	0.15	mg/L	<0.15	----
Zinc, TCLP	7440-66-6	E444	0.5	mg/L	<0.50	----
Zirconium, TCLP	7440-67-7	E444	10	mg/L	<10	----



Laboratory Control Sample (LCS) Report

A Laboratory Control Sample (LCS) is an analyte-free matrix that has been fortified (spiked) with test analytes at known concentration and processed in an identical manner to test samples. LCS results are expressed as percent recovery, and are used to monitor and control test method accuracy and precision, independent of test sample matrix.

Sub-Matrix: Soil/Solid

					Laboratory Control Sample (LCS) Report				
					Spike	Recovery (%)	Recovery Limits (%)		
Analyte	CAS Number	Method	LOR	Unit	Concentration	LCS	Low	High	Qualifier
Physical Tests (QCLot: 839861)									
pH (1:2 soil:water)	----	E108	----	pH units	6 pH units	99.5	95.0	105	----
Physical Tests (QCLot: 839862)									
Moisture	----	E144	0.25	%	50 %	100	90.0	110	----
Metals (QCLot: 839859)									
Mercury	7439-97-6	E510	0.005	mg/kg	0.1 mg/kg	94.8	80.0	120	----
Metals (QCLot: 839860)									
Aluminum	7429-90-5	E440	50	mg/kg	200 mg/kg	98.8	80.0	120	----
Antimony	7440-36-0	E440	0.1	mg/kg	100 mg/kg	109	80.0	120	----
Arsenic	7440-38-2	E440	0.1	mg/kg	100 mg/kg	107	80.0	120	----
Barium	7440-39-3	E440	0.5	mg/kg	25 mg/kg	100	80.0	120	----
Beryllium	7440-41-7	E440	0.1	mg/kg	10 mg/kg	104	80.0	120	----
Bismuth	7440-69-9	E440	0.2	mg/kg	100 mg/kg	103	80.0	120	----
Boron	7440-42-8	E440	5	mg/kg	100 mg/kg	99.6	80.0	120	----
Cadmium	7440-43-9	E440	0.02	mg/kg	10 mg/kg	98.5	80.0	120	----
Calcium	7440-70-2	E440	50	mg/kg	5000 mg/kg	99.1	80.0	120	----
Chromium	7440-47-3	E440	0.5	mg/kg	25 mg/kg	95.7	80.0	120	----
Cobalt	7440-48-4	E440	0.1	mg/kg	25 mg/kg	99.0	80.0	120	----
Copper	7440-50-8	E440	0.5	mg/kg	25 mg/kg	97.1	80.0	120	----
Iron	7439-89-6	E440	50	mg/kg	100 mg/kg	94.5	80.0	120	----
Lead	7439-92-1	E440	0.5	mg/kg	50 mg/kg	101	80.0	120	----
Lithium	7439-93-2	E440	2	mg/kg	25 mg/kg	107	80.0	120	----
Magnesium	7439-95-4	E440	20	mg/kg	5000 mg/kg	109	80.0	120	----
Manganese	7439-96-5	E440	1	mg/kg	25 mg/kg	97.8	80.0	120	----
Molybdenum	7439-98-7	E440	0.1	mg/kg	25 mg/kg	100	80.0	120	----
Nickel	7440-02-0	E440	0.5	mg/kg	50 mg/kg	98.0	80.0	120	----
Phosphorus	7723-14-0	E440	50	mg/kg	1000 mg/kg	99.0	80.0	120	----
Potassium	7440-09-7	E440	100	mg/kg	5000 mg/kg	98.9	80.0	120	----
Selenium	7782-49-2	E440	0.2	mg/kg	100 mg/kg	104	80.0	120	----
Silver	7440-22-4	E440	0.1	mg/kg	10 mg/kg	81.4	80.0	120	----
Sodium	7440-23-5	E440	50	mg/kg	5000 mg/kg	104	80.0	120	----
Strontium	7440-24-6	E440	0.5	mg/kg	25 mg/kg	103	80.0	120	----
Sulfur	7704-34-9	E440	1000	mg/kg	5000 mg/kg	103	80.0	120	----



Sub-Matrix: Soil/Solid

					Laboratory Control Sample (LCS) Report				
					Spike	Recovery (%)	Recovery Limits (%)		
Analyte	CAS Number	Method	LOR	Unit	Concentration	LCS	Low	High	Qualifier
Metals (QCLot: 839860) - continued									
Thallium	7440-28-0	E440	0.05	mg/kg	100 mg/kg	95.8	80.0	120	----
Tin	7440-31-5	E440	2	mg/kg	50 mg/kg	100.0	80.0	120	----
Titanium	7440-32-6	E440	1	mg/kg	25 mg/kg	98.3	80.0	120	----
Tungsten	7440-33-7	E440	0.5	mg/kg	10 mg/kg	94.4	80.0	120	----
Uranium	7440-61-1	E440	0.05	mg/kg	0.5 mg/kg	99.2	80.0	120	----
Vanadium	7440-62-2	E440	0.2	mg/kg	50 mg/kg	101	80.0	120	----
Zinc	7440-66-6	E440	2	mg/kg	50 mg/kg	97.1	80.0	120	----
Zirconium	7440-67-7	E440	1	mg/kg	10 mg/kg	92.9	80.0	120	----



Matrix Spike (MS) Report

A Matrix Spike (MS) is a randomly selected intra-laboratory replicate sample that has been fortified (spiked) with test analytes at known concentration, and processed in an identical manner to test samples. Matrix Spikes provide information regarding analyte recovery and potential matrix effects. MS DQO exceedances due to sample matrix may sometimes be unavoidable; in such cases, test results for the associated sample (or similar samples) may be subject to bias. ND – Recovery not determined, background level >= 1x spike level.

Sub-Matrix: Soil/Solid

					Matrix Spike (MS) Report					
					Spike		Recovery (%)	Recovery Limits (%)		
Laboratory sample ID	Client sample ID	Analyte	CAS Number	Method	Concentration	Target	MS	Low	High	Qualifier
TCLP Metals (QCLot: 839770)										
VA23A3361-001	BA2306-A-1	Mercury, TCLP	7439-97-6	E512	0.0010 mg/L	0.001 mg/L	99.0	50.0	140	----
TCLP Metals (QCLot: 839771)										
VA23A3361-001	BA2306-A-1	Antimony, TCLP	7440-36-0	E444	4.93 mg/L	5 mg/L	98.6	50.0	140	----
		Arsenic, TCLP	7440-38-2	E444	4.8 mg/L	5 mg/L	95.8	50.0	140	----
		Barium, TCLP	7440-39-3	E444	12.9 mg/L	12.5 mg/L	103	50.0	140	----
		Beryllium, TCLP	7440-41-7	E444	0.236 mg/L	0.25 mg/L	94.4	50.0	140	----
		Boron, TCLP	7440-42-8	E444	9.37 mg/L	10 mg/L	93.7	50.0	140	----
		Cadmium, TCLP	7440-43-9	E444	0.236 mg/L	0.25 mg/L	94.4	50.0	140	----
		Calcium, TCLP	7440-70-2	E444	ND mg/L	250 mg/L	ND	50.0	140	----
		Chromium, TCLP	7440-47-3	E444	1.18 mg/L	1.25 mg/L	94.2	50.0	140	----
		Cobalt, TCLP	7440-48-4	E444	ND mg/L	0.25 mg/L	ND	50.0	140	----
		Copper, TCLP	7440-50-8	E444	2.26 mg/L	2.5 mg/L	90.5	50.0	140	----
		Iron, TCLP	7439-89-6	E444	231 mg/L	250 mg/L	92.5	50.0	140	----
		Lead, TCLP	7439-92-1	E444	9.75 mg/L	10 mg/L	97.5	50.0	140	----
		Magnesium, TCLP	7439-95-4	E444	254 mg/L	250 mg/L	102	50.0	140	----
		Nickel, TCLP	7440-02-0	E444	2.31 mg/L	2.5 mg/L	92.4	50.0	140	----
		Selenium, TCLP	7782-49-2	E444	4.56 mg/L	5 mg/L	91.1	50.0	140	----
		Silver, TCLP	7440-22-4	E444	0.094 mg/L	0.1 mg/L	94.2	50.0	140	----
		Thallium, TCLP	7440-28-0	E444	4.9 mg/L	5 mg/L	98.8	50.0	140	----
		Uranium, TCLP	7440-61-1	E444	4.91 mg/L	5 mg/L	98.2	50.0	150	----
		Vanadium, TCLP	7440-62-2	E444	0.72 mg/L	0.75 mg/L	95.6	50.0	140	----
		Zinc, TCLP	7440-66-6	E444	9.19 mg/L	10 mg/L	91.9	50.0	140	----
		Zirconium, TCLP	7440-67-7	E444	9 mg/L	10 mg/L	86.3	50.0	150	----



Reference Material (RM) Report

A Reference Material (RM) is a homogenous material with known and well-established analyte concentrations. RMs are processed in an identical manner to test samples, and are used to monitor and control the accuracy and precision of a test method for a typical sample matrix. RM results are expressed as percent recovery of the target analyte concentration. RM targets may be certified target concentrations provided by the RM supplier, or may be ALS long-term mean values (for empirical test methods).

Sub-Matrix:

Laboratory sample ID	Reference Material ID	Analyte	CAS Number	Method	Reference Material (RM) Report				
					RM Target Concentration	Recovery (%) RM	Recovery Limits (%)		Qualifier
		Low	High						
Metals (QCLot: 839859)									
	SCP SS-2	Mercury	7439-97-6	E510	0.059 mg/kg	93.0	70.0	130	----
Metals (QCLot: 839860)									
	SCP SS-2	Aluminum	7429-90-5	E440	9817 mg/kg	102	70.0	130	----
	SCP SS-2	Antimony	7440-36-0	E440	3.99 mg/kg	112	70.0	130	----
	SCP SS-2	Arsenic	7440-38-2	E440	3.73 mg/kg	106	70.0	130	----
	SCP SS-2	Barium	7440-39-3	E440	105 mg/kg	96.8	70.0	130	----
	SCP SS-2	Beryllium	7440-41-7	E440	0.349 mg/kg	104	70.0	130	----
	SCP SS-2	Boron	7440-42-8	E440	8.5 mg/kg	123	40.0	160	----
	SCP SS-2	Cadmium	7440-43-9	E440	0.91 mg/kg	97.4	70.0	130	----
	SCP SS-2	Calcium	7440-70-2	E440	31082 mg/kg	108	70.0	130	----
	SCP SS-2	Chromium	7440-47-3	E440	101 mg/kg	106	70.0	130	----
	SCP SS-2	Cobalt	7440-48-4	E440	6.9 mg/kg	97.0	70.0	130	----
	SCP SS-2	Copper	7440-50-8	E440	123 mg/kg	96.2	70.0	130	----
	SCP SS-2	Iron	7439-89-6	E440	23558 mg/kg	96.6	70.0	130	----
	SCP SS-2	Lead	7439-92-1	E440	267 mg/kg	96.8	70.0	130	----
	SCP SS-2	Lithium	7439-93-2	E440	9.5 mg/kg	99.5	70.0	130	----
	SCP SS-2	Magnesium	7439-95-4	E440	5509 mg/kg	105	70.0	130	----
	SCP SS-2	Manganese	7439-96-5	E440	269 mg/kg	103	70.0	130	----
	SCP SS-2	Molybdenum	7439-98-7	E440	1.03 mg/kg	105	70.0	130	----
	SCP SS-2	Nickel	7440-02-0	E440	26.7 mg/kg	101	70.0	130	----
	SCP SS-2	Phosphorus	7723-14-0	E440	752 mg/kg	88.2	70.0	130	----
	SCP SS-2	Potassium	7440-09-7	E440	1587 mg/kg	107	70.0	130	----
	SCP SS-2	Sodium	7440-23-5	E440	797 mg/kg	94.4	70.0	130	----
	SCP SS-2	Strontium	7440-24-6	E440	86.1 mg/kg	99.3	70.0	130	----
	SCP SS-2	Thallium	7440-28-0	E440	0.0786 mg/kg	89.0	40.0	160	----
	SCP SS-2	Tin	7440-31-5	E440	10.6 mg/kg	95.2	70.0	130	----
	SCP SS-2	Titanium	7440-32-6	E440	839 mg/kg	110	70.0	130	----

Page : 11 of 11
 Work Order : VA23A3361
 Client : Covanta Burnaby Renewable Energy, ULC
 Project : Weekly Bottom Ash - Suite



Sub-Matrix:

Laboratory sample ID	Reference Material ID	Analyte	CAS Number	Method	Reference Material (RM) Report				
					RM Target Concentration	Recovery (%) RM	Recovery Limits (%)		Qualifier
							Low	High	
Metals (QCLot: 839860) - continued									
	SCP SS-2	Uranium	7440-61-1	E440	0.52 mg/kg	96.0	70.0	130	----
	SCP SS-2	Vanadium	7440-62-2	E440	32.7 mg/kg	103	70.0	130	----
	SCP SS-2	Zinc	7440-66-6	E440	297 mg/kg	95.0	70.0	130	----
	SCP SS-2	Zirconium	7440-67-7	E440	5.73 mg/kg	92.2	70.0	130	----



ALS Environmental

Chain of Custody / Analytical Request Form

Canada Toll Free: 1 800 668 9878


www.alsglobal.com

COC #

Page of

Report To		Report Format / Distribution		Service Requested (Rush for routine analysis subject to availability)					
Company:	Covanta Energy	<input type="checkbox"/> Standard <input type="checkbox"/> Other		<input checked="" type="radio"/> Regular (Standard Turnaround Times - Business Days)					
Contact:	Nicole Victor / Dan Skrypyk	<input checked="" type="checkbox"/> PDF <input type="checkbox"/> Excel <input type="checkbox"/> Digital <input type="checkbox"/> Fax		<input type="radio"/> Priority (2-4 Business Days) - 50% Surcharge - Contact ALS to Confirm TAT					
Address:	5150 Riverbend Drive Burnaby BC	Email 1:	nvictor@covanta.com	<input type="radio"/> Emergency (1-2 Bus. Days) - 100% Surcharge - Contact ALS to Confirm TAT					
Phone:	604-521-1025	Fax:		<input type="radio"/> Same Day or Weekend Emergency - Contact ALS to Confirm TAT					
	<input type="checkbox"/> Yes <input type="checkbox"/> No	Email 2:	rjohnson4@covanta.com	Analysis Request					
		Email 3:	dskrypyk@covanta.com						
			brent.kirkpatrick@metrovancover.org Sarah.Wellman@metrovancover.org						

Invoice To Same as Report ?		Client / Project Information		Please indicate below Filtered, Preserved or both (F, P, F/P)																																																												
Hardcopy of Invoice with Report? <input type="checkbox"/> Yes <input type="checkbox"/> No		Job #:		<table border="1"> <tr><td>MET-TCLP-VA (all metals, Hg)</td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td></tr> <tr><td>MOISTURE</td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td></tr> <tr><td>Chrome 6</td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td></tr> <tr><td>MET-CSR-FULL-VA (all metals)</td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td></tr> <tr><td>Number of Containers</td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td></td></tr> </table>						MET-TCLP-VA (all metals, Hg)											MOISTURE											Chrome 6											MET-CSR-FULL-VA (all metals)											Number of Containers										
MET-TCLP-VA (all metals, Hg)																																																																
MOISTURE																																																																
Chrome 6																																																																
MET-CSR-FULL-VA (all metals)																																																																
Number of Containers																																																																
Company:		PO / AFE:	PO# 46693 Weekly Bottom Ash - Suite																																																													
Contact:		LSD:	(includes 2:1 pH)																																																													
Address:		Quote #:																																																														
Phone:		ALS Contact:		Sampler:																																																												

Sample #	Sample Identification (This description will appear on the report)	Date (dd-mmm-yy)	Time (hh:mm)	Sample Type	MET-TCLP-VA (all metals, Hg)	MOISTURE	Chrome 6	MET-CSR-FULL-VA (all metals)	Number of Containers
BA2306-A-1	Environmental Division Vancouver Work Order Reference VA23A3361  Telephone : +1 804 263 4188	08-Feb-23	9:00	Soil	X	X	X	1	
BA2306-A-2		08-Feb-23	9:00	Soil	X	X	X	1	
BA2306-A-3		08-Feb-23	9:00	Soil	X	X	X	1	
BA2306-A-4		08-Feb-23	9:00	Soil	X	X	X	1	
BA2306-A-5		08-Feb-23	9:00	Soil	X	X	X	1	
BA2306-A-6		08-Feb-23	9:00	Soil	X	X	X	1	
BA2306-A-7		08-Feb-23	9:00	Soil	X	X	X	1	
BA2306-A-8		08-Feb-23	9:00	Soil	X	X	X	1	
BA2306-A-9		08-Feb-23	9:00	Soil	X	X	X	1	
BA2306-A-10		08-Feb-23	9:00	Soil	X	X	X	1	
BA2306-A-11		08-Feb-23	9:00	Soil	X	X	X	1	
BA2306-A-12		08-Feb-23	9:00	Soil	X	X	X	1	

Special Instructions / Regulations with water or land use (CCME-Freshwater Aquatic Life/BC CSR - Commercial/AB Tier 1 - Natural, etc) / Hazardous Details

Failure to complete all portions of this form may delay analysis. Please fill in this form LEGIBLY.
 By the use of this form the user acknowledges and agrees with the Terms and Conditions as provided on a separate Excel tab.
 Also provided on another Excel tab are the ALS location addresses, phone numbers and sample container / preservation / holding time table for common analyses.

SHIPMENT RELEASE (client use)			SHIPMENT RECEPTION (lab use only)				SHIPMENT VERIFICATION (lab use only)			
Released by:	Date (dd-mmm-yy)	Time (hh-mm)	Received by:	Date:	Time:	Temperature:	Verified by:	Date:	Time:	Observations:
	14 Feb-23	800				17 °C	PL	14/2/23	2:00	Yes / No ? If Yes add SIF